

# Evaluation of the behaviour of corroded beams

Autor(en): **Capozucca, Roberto / Cerri, M. Nilde**

Objekttyp: **Article**

Zeitschrift: **IABSE reports = Rapports AIPC = IVBH Berichte**

Band (Jahr): **77 (1998)**

PDF erstellt am: **03.05.2024**

Persistenter Link: <https://doi.org/10.5169/seals-58187>

## Nutzungsbedingungen

Die ETH-Bibliothek ist Anbieterin der digitalisierten Zeitschriften. Sie besitzt keine Urheberrechte an den Inhalten der Zeitschriften. Die Rechte liegen in der Regel bei den Herausgebern.

Die auf der Plattform e-periodica veröffentlichten Dokumente stehen für nicht-kommerzielle Zwecke in Lehre und Forschung sowie für die private Nutzung frei zur Verfügung. Einzelne Dateien oder Ausdrucke aus diesem Angebot können zusammen mit diesen Nutzungsbedingungen und den korrekten Herkunftsbezeichnungen weitergegeben werden.

Das Veröffentlichen von Bildern in Print- und Online-Publikationen ist nur mit vorheriger Genehmigung der Rechteinhaber erlaubt. Die systematische Speicherung von Teilen des elektronischen Angebots auf anderen Servern bedarf ebenfalls des schriftlichen Einverständnisses der Rechteinhaber.

## Haftungsausschluss

Alle Angaben erfolgen ohne Gewähr für Vollständigkeit oder Richtigkeit. Es wird keine Haftung übernommen für Schäden durch die Verwendung von Informationen aus diesem Online-Angebot oder durch das Fehlen von Informationen. Dies gilt auch für Inhalte Dritter, die über dieses Angebot zugänglich sind.

Ein Dienst der *ETH-Bibliothek*

ETH Zürich, Rämistrasse 101, 8092 Zürich, Schweiz, [www.library.ethz.ch](http://www.library.ethz.ch)

<http://www.e-periodica.ch>



## Evaluation of the Behaviour of Corroded Beams

**Roberto CAPOZUCCA**

Associate Researcher  
University of Ancona  
Ancona, Italy

R. Capozucca, born 1956,  
received his civil engineering  
degree in 1981. He is  
associate researcher at Univ.  
of Ancona since 1991.



**M. Nilde CERRI**

Civil Engineer  
University of Ancona  
Ancona, Italy

M.N. Cerri, born 1963,  
received her civil  
engineering degree in 1989.  
She received Ph.D. in  
Structural Eng. In 1997.



### Summary

To analyse the behaviour of corroded beams, in the paper a model based on damage function D.F. is shown linked to a global damage coefficient D.C. of the beam that may be obtained by means of dynamic tests.

### 1. Analysis of damaged beam

In the r. c. beams, the damage due to reinforcement corrosion may cause cracking of concrete around the bars both at the compressive and tensile zone of section [1]. Cracks due to rust create a *compressive softening* effect [2] in the concrete with an influence on the strength and ductility and load-deflection response of the concrete beam. The damage of concrete subjected to tension by rust causes a reduction of stiffness that has consequence on the dynamic behaviour of the beam [3]. The comparison between natural frequency of an undamaged beam,  $\omega_{0,r}$ , and a damaged beam due to corrosion,  $\omega_{1,r}$ , can define the state of damage if there are significant changes in the dynamic characteristics.

In the paper, we consider that the beam has a stiffness uniformly reduced on the length by diffused cracks due to corrosion. This situation is, for example, characteristic of cantilever beams. In this case, it is sufficient to use only one value of frequency to evaluate the undamaged and damaged state of the beam by means of global value damaged coefficient D.C.:

$$D.C. = 1 - (\omega_{1,r} / \omega_{0,r})^2, \quad r=1 \quad (1)$$

In the Fig.1, undamaged and damaged r.c. sections are shown with own strain - stress diagrams. The global coefficient of damage D.C. expressed in (1), considering the bending stiffness in undamaged ( $EI_0$ ) and damaged state ( $EI_1$ ), is defined in this way:

$$D.C. = \frac{(EI)_0 - (EI)_1}{(EI)_0} \quad (2)$$

$$M = \chi_1 (1 - D.C.) (EI)_0 \quad (3)$$

respectively for the curvature  $\chi_1$  and bending moment M in a damaged section (Fig.1).

To define the modified strain - stress state in the section, we assume a linear function D.F. which reaches the value D for  $\eta = -k_1$ :

$$D.F. = D \cdot \left(1 - \frac{k_1}{2 \cdot \alpha}\right) - \left(\frac{D}{2 \cdot \alpha}\right) \cdot \eta \quad (4)$$

where  $\eta = \frac{y}{d}$ .




Fig. 1 - (a) Undamaged section ; (b) Damaged section

The value of  $D$  may be related to the strain  $\epsilon_{c1}$  of the extreme fiber of compressive concrete of damaged section :

$$D = \gamma \cdot \epsilon_{c1} \cdot E_c \quad (10)$$

using a coefficient  $\gamma$  enclosed between 0 and 1.

In the damaged section of Fig. 1b, considering the compatibility and equilibrium relations, we obtain two relations in the unknown parameters  $\gamma$ ,  $k_1$  and  $D.C.$ . These relations together to the (1) permit to evaluate the stress-strain state in a r.c. damaged section.

## 2. Conclusions

The deterioration of r.c. beams due to corrosion reduces the bending capacity of the section with increase of curvature and deflection. The corrosion especially influences the strength of compressive concrete by means of the biaxial stress state due to the rust on the bars. Using dynamic tests it is possible to estimate the state of damage expressed by a global coefficient  $D.C..$  Above we have defined also a linear damage function  $D.F.$  to analyse the stress distribution in the damaged compressive concrete.

## 3. References

- [1] Capozucca, R. 'Damage to reinforced concrete due to reinforcement corrosion' *Construction and Building Materials*, 9 (5) (1995) 295-303.
- [2] Capozucca, R. 'Statical and dynamical behaviour of reinforced concrete beams subjected to reinforcement corrosion' Proc. Conf. RILEM, Bratislava (1995) 189-194
- [3] Vestrone, F., Cerri, M.N. and Antonacci, E. 'Damage detection in vibrating structures' Proc. of Structural Dynamics - EURODYN'96, Firenze (1996) 41-50.