

XPS investigation of the YBa₂CuO₃O₇₋₆

Autor(en): **del Fennino, U. / Di Bona, A. / Tombesi, A.**

Objekttyp: **Article**

Zeitschrift: **Helvetica Physica Acta**

Band (Jahr): **62 (1989)**

Heft 6-7

PDF erstellt am: **15.05.2024**

Persistenter Link: <https://doi.org/10.5169/seals-116119>

Nutzungsbedingungen

Die ETH-Bibliothek ist Anbieterin der digitalisierten Zeitschriften. Sie besitzt keine Urheberrechte an den Inhalten der Zeitschriften. Die Rechte liegen in der Regel bei den Herausgebern.

Die auf der Plattform e-periodica veröffentlichten Dokumente stehen für nicht-kommerzielle Zwecke in Lehre und Forschung sowie für die private Nutzung frei zur Verfügung. Einzelne Dateien oder Ausdrucke aus diesem Angebot können zusammen mit diesen Nutzungsbedingungen und den korrekten Herkunftsbezeichnungen weitergegeben werden.

Das Veröffentlichen von Bildern in Print- und Online-Publikationen ist nur mit vorheriger Genehmigung der Rechteinhaber erlaubt. Die systematische Speicherung von Teilen des elektronischen Angebots auf anderen Servern bedarf ebenfalls des schriftlichen Einverständnisses der Rechteinhaber.

Haftungsausschluss

Alle Angaben erfolgen ohne Gewähr für Vollständigkeit oder Richtigkeit. Es wird keine Haftung übernommen für Schäden durch die Verwendung von Informationen aus diesem Online-Angebot oder durch das Fehlen von Informationen. Dies gilt auch für Inhalte Dritter, die über dieses Angebot zugänglich sind.

Ein Dienst der *ETH-Bibliothek*

ETH Zürich, Rämistrasse 101, 8092 Zürich, Schweiz, www.library.ethz.ch

XPS INVESTIGATION OF THE YBa₂Cu₃O_{7-x}

U. del Fennino, A. Di Bona, A. Tombesi and S. Valeri
Dipartimento di Fisica, Via Campi 213/a
41100 MODENA, ITALY

In the latest years many papers reported about XPS investigations on YBa₂Cu₃O_{7-x} (YBCO) samples [1]. Most of these reports dealt with Cu 2p and/or O 1s lines in $\delta \approx 0$ samples. Very few papers reported XPS spectra of all the four YBCO elements and, in our knowledge, none of them in both the semiconductor and superconductor phases. On the contrary, we think very important to study the spectra of all the four elements and their evolution with the stoichiometry to try to find possible correlations helpful in the understanding of the superconductive behaviour.

In this preliminary report we show the most relevant peaks of Cu, O, Ba and Y in samples with values of $\delta \approx 0$ and $\delta \approx 1$.

Samples were synterized ceramic disks annealed for 12 hours at 500 C in flowing oxygen. After the introduction in the UHV system they were scraped before each measurement. They were also exposed to oxygen at increasing exposures between 10 and 1000 Langmuir (1L=1s at 10^{-6} torr). Some samples were sputtered with Ar ions at 5 KeV. The measuring apparatus was a Leybold emispherical analyser with a 15 KV X-ray Mg source. The overall resolution was 0.9 eV.

To a careful analysis each spectrum shows a composite structure which changes with δ and the surface treatment. A first semi-quantitative analysis of these spectra enables the following conclusions:

- Cu 2p_{3/2}. As well known this spectrum is formed by a main line and a satellite corresponding to

differently screened complex final states. Limiting ourself to the main line (as the d⁹ satellite shows a multiplet structure) it is possible to fit it with the sum of two components that we associate to Cu²⁺ and Cu¹⁺ in analogy to what shown for CuO [2]. Their relative weights change with the stoichiometry from about 49% and 51% respectively in samples with $J \approx 1$ to about 83% and 17% for $J \approx 0$. It is worth noting that upon oxygen exposure it is the Cu¹⁺ component which increases.

- O 1s. It is well established [1] that even in "good" superconductor two peaks appears in the O 1s spectrum. One at -528.5 eV and the second at -531.5 eV with a weight at least 70% of the main one. We found this second peak about 90% for $J \approx 0$ and about 60% for $J \approx 1$. In both samples upon oxygen exposure the relative intensity of these peaks increases slightly.

- Ba 3d_{5/2}. In the superconductor samples a clear asymmetry is observed on the low binding energy (B.E.) side of the peak at -779.3. The difference between the spectra corresponding to the two J values is a small peak at -777.7 eV B.E., with a weight of about 12.5 %. A similar shifted component had been observed in the 4d doublet by Steiner et al.[3].

- Y 3d. This spectrum shows a tail on the high B.E. side and can be fairly well fitted by the sum of two doublets identical in shape with the larger at -156.1 and the smaller shifted by about 2 eV at higher B.E.. Its weight is about 12% for $J \approx 0$ and reduces to about 9% for $J \approx 1$. It also reduces upon oxygen exposure or sputtering.

A more detailed analysis of these data is in progress with particular attention to the role of the screening of O 2p holes.

- [1] J.C. Fuggle et al.: Int. J. Mod. Phys. B1, 1185 (1989)
- [2] F. Farmiggiani and G. Samoggia: to be published
- [3] P. Steiner et al.: Z. Phys. B69, 449 (1988)