

High energy neutron spectroscopy in crystal field split 5f systems

Autor(en): **Amoretti, G. / Caciuffo, R. / Blaise, A.**

Objekttyp: **Article**

Zeitschrift: **Helvetica Physica Acta**

Band (Jahr): **62 (1989)**

Heft 6-7

PDF erstellt am: **09.05.2024**

Persistenter Link: <https://doi.org/10.5169/seals-116096>

Nutzungsbedingungen

Die ETH-Bibliothek ist Anbieterin der digitalisierten Zeitschriften. Sie besitzt keine Urheberrechte an den Inhalten der Zeitschriften. Die Rechte liegen in der Regel bei den Herausgebern.

Die auf der Plattform e-periodica veröffentlichten Dokumente stehen für nicht-kommerzielle Zwecke in Lehre und Forschung sowie für die private Nutzung frei zur Verfügung. Einzelne Dateien oder Ausdrucke aus diesem Angebot können zusammen mit diesen Nutzungsbedingungen und den korrekten Herkunftsbezeichnungen weitergegeben werden.

Das Veröffentlichen von Bildern in Print- und Online-Publikationen ist nur mit vorheriger Genehmigung der Rechteinhaber erlaubt. Die systematische Speicherung von Teilen des elektronischen Angebots auf anderen Servern bedarf ebenfalls des schriftlichen Einverständnisses der Rechteinhaber.

Haftungsausschluss

Alle Angaben erfolgen ohne Gewähr für Vollständigkeit oder Richtigkeit. Es wird keine Haftung übernommen für Schäden durch die Verwendung von Informationen aus diesem Online-Angebot oder durch das Fehlen von Informationen. Dies gilt auch für Inhalte Dritter, die über dieses Angebot zugänglich sind.

Ein Dienst der *ETH-Bibliothek*

ETH Zürich, Rämistrasse 101, 8092 Zürich, Schweiz, www.library.ethz.ch

HIGH ENERGY NEUTRON SPECTROSCOPY IN CRYSTAL FIELD SPLIT 5f SYSTEMS

G. Amoretti*, R. Caciuffo*, A. Blaise[†], J.M. Fournier[†], M.T. Hutchings[‡], R. Osborn[◊]
and A.D. Taylor[◊]

*Dipartimento di Fisica dell'Università, 43100 PARMA, Italy

*Dipartimento di Scienze dei Materiali dell'Università, 60131 ANCONA, Italy

[†]DRF, Centre d'Études Nucléaires, 38041 GRENOBLE, France

[‡]Material Physics and Metallurgy Division, Harwell Lab., DIDCOT, OX11 0RA, U.K.

[◊]Neutron Science Division, Rutherford Appleton Lab., CHILTON, OX11 0QX, U.K.

Abstract: The new generation of spallation neutron sources, characterized by an intense epithermal flux, allows the observation of magnetic excitations up to several hundreds of meV. It is then possible to determine the crystal field transitions in a number of actinide systems, as it is illustrated in the case of UO_2 , UOS and NpO_2 .

1. Introduction

The knowledge of the crystal field (CF) is often essential to describe the magnetic and thermodynamic properties of actinide systems and also to answer fundamental questions about the behaviour of the $5f$ electrons. As known, neutron inelastic scattering provides the most effective method to observe CF transitions in opaque samples. In the case of actinide systems, the kinematic constraint of the scattering process becomes particularly severe at high energy transfer, because the form factor $f(Q)$ falls very rapidly with Q . Neutrons with high incident energy must then be used and, for this reason, spallation neutron sources with a large slowing down component in the epithermal region of the neutron spectrum are better suited than steady-state reactors. We present here a short review of some experiments recently performed on the HET spectrometer at the UK spallation source ISIS of the Rutherford Appleton Laboratory.

2. Results and Discussion

The first example is the CaF_2 structure compound UO_2 for which the ninefold degeneracy of the ground multiplet is resolved into two triplets, one doublet and one singlet by the cubic CF above the ordering temperature $T_N = 30.8K$. Below T_N , an internal distortion of the oxygen sublattice reduces the symmetry, giving rise to a further splitting of the levels. The inelastic neutron scattering cross section at $T = 50K$ shows two peaks, at 150 and 166 meV, which can be attributed to the $\Gamma_5 \rightarrow \Gamma_3$ and $\Gamma_5 \rightarrow \Gamma_4$ transitions respectively. No more excitations have been observed up to ~ 700 meV. This allowed the determination of the two coefficients in the CF hamiltonian, namely $V_4 = -123$ meV and $V_6 = 26.5$ meV [1,2]. It has been shown also that J -mixing effects are far less important than previously assumed. Below the Néel temperature, more structure appears in the

neutron spectra. Detailed CF calculations have been performed [2] assuming either a 2-k magnetic structure and monoclinic lattice distortion or a 3-k magnetic structure and lattice distortion. The comparison with the experimental splittings is in favour of the second case.

The second compound we have examined is UOS , which belongs to the tetragonal $PbFCI$ crystal structure and orders antiferromagnetically below $T_N = 55K$. Two main excitation peaks have been found at 74 and 82 meV for $T > T_N$. A redistribution of the intensities together with a slight shift of the peak positions is observed below T_N . No other CF excitations appear up to at least 200 meV [3]. The spectra have been interpreted [3,4] in the frame of a CF model accounting for the Schottky contribution to the specific heat, from which the splitting of the $J = 4$ manifold into two groups of states with a separation not greater than 100 meV was expected. The peaks in the neutron spectra have been attributed to the transitions from the ground $\Gamma_{t5}^{(1)}$ doublet to the second group of states. The intensity variation and the level shifts have also been interpreted as an effect of the molecular field.

Finally, a neutron spectroscopy study has been performed on NpO_2 , which is isostructural to UO_2 and contains Np^{4+} ions with $5f^3$ electronic configuration. The tenfold degeneracy of the $J = 9/2$ ground multiplet is split by the cubic CF into two quartets and one doublet. This compound presents a phase transition at $T_c = 25K$ whose origin is as yet unexplained. We have examined a sample of 32g of powder, together with a similar ThO_2 sample, allowing us to perform a reliable phonon density of state subtraction. Although no sharp peaks have been found up to 350 meV, magnetic scattering is clearly visible from our spectra around ~ 60 meV. The difference of NpO_2 and ThO_2 spectra shows in fact a broad peak centered at this energy value, having ~ 20 meV FWHM. No significant changes have been observed in passing through the transition temperature. CF calculations starting from the CF parameters determined for UO_2 predict for NpO_2 a strong $\Gamma_8^{(2)} \rightarrow \Gamma_8^{(1)}$ transition at ~ 55 meV. We believe to have observed this CF excitation, the broadening of the peak being probably due to interaction with optical phonons at the same energy.

3. References

- [1] R. Osborn, A.D. Taylor, Z.A. Bowden, M.A. Hackett, W. Hayes, M.T. Hutchings, G. Amoretti, R. Caciuffo, A. Blaise, J.M. Fournier, J. Phys. C: Solid State Phys. **21**, L931 (1988).
- [2] G. Amoretti, A. Blaise, R. Caciuffo, J.M. Fournier, M.T. Hutchings, R. Osborn and A.D. Taylor, RAL-88-096, and Phys. Rev. B, in print.
- [3] G. Amoretti, A. Blaise, J.M. Fournier, R. Caciuffo, J. Larroque, R. Osborn, A.D. Taylor and Z.A. Bowden, J. Magn. Magn. Mat. **76-77**, 432 (1988).
- [4] G. Amoretti, A. Blaise, R. Caciuffo, J.M. Fournier, J. Larroque and R. Osborn, RAL-88-095, and J. Phys.: Condens. Matter, in print.
- [5] J.M. Fournier, A. Blaise, G. Amoretti, R. Caciuffo, J. Larroque, M.T. Hutchings, R. Osborn and A.D. Taylor, 19èmes Journées des Actinides, March 1989, Madonna di Campiglio, Italy, and to be published.