

**Zeitschrift:** Archives des sciences [1948-1980]  
**Herausgeber:** Société de Physique et d'Histoire Naturelle de Genève  
**Band:** 13 (1960)  
**Heft:** 9: Colloque Ampère

**Artikel:** Dielectric anisotropy and dielectric loss of some liquid crystals  
**Autor:** Maier, W. / Meier, G.  
**DOI:** <https://doi.org/10.5169/seals-738539>

### **Nutzungsbedingungen**

Die ETH-Bibliothek ist die Anbieterin der digitalisierten Zeitschriften auf E-Periodica. Sie besitzt keine Urheberrechte an den Zeitschriften und ist nicht verantwortlich für deren Inhalte. Die Rechte liegen in der Regel bei den Herausgebern beziehungsweise den externen Rechteinhabern. Das Veröffentlichen von Bildern in Print- und Online-Publikationen sowie auf Social Media-Kanälen oder Webseiten ist nur mit vorheriger Genehmigung der Rechteinhaber erlaubt. [Mehr erfahren](#)

### **Conditions d'utilisation**

L'ETH Library est le fournisseur des revues numérisées. Elle ne détient aucun droit d'auteur sur les revues et n'est pas responsable de leur contenu. En règle générale, les droits sont détenus par les éditeurs ou les détenteurs de droits externes. La reproduction d'images dans des publications imprimées ou en ligne ainsi que sur des canaux de médias sociaux ou des sites web n'est autorisée qu'avec l'accord préalable des détenteurs des droits. [En savoir plus](#)

### **Terms of use**

The ETH Library is the provider of the digitised journals. It does not own any copyrights to the journals and is not responsible for their content. The rights usually lie with the publishers or the external rights holders. Publishing images in print and online publications, as well as on social media channels or websites, is only permitted with the prior consent of the rights holders. [Find out more](#)

**Download PDF:** 04.04.2026

**ETH-Bibliothek Zürich, E-Periodica, <https://www.e-periodica.ch>**

## Dielectric anisotropy and dielectric loss of some liquid crystals

by W. MAIER und G. MEIER

Institut für Physikalische Chemie der Universität Freiburg i. Br.

---

A homogeneously oriented layer of a liquid crystalline melt has the optical and dielectric properties of an uniaxial crystal [1] as the result of a molecular order of degree  $S = 1 - \frac{3}{2} \overline{\sin^2 \theta}$ .  $\theta$  is the angle between the optical axis of the layer and the axis of greatest length of the molecules (molecular axis). Let the directions parallel respectively perpendicular to the optical axis be designed by 1 respectively 2. The simple molecular statistical theory [2] of nematic liquid crystals combined with the Onsager theory of dielectric polarization gives the two principal dielectric susceptibilities as functions of the following quantities: Permanent dipole moment  $\mu$ , its angle  $\beta$  with the molecular axis, the two principal polarizabilities parallel ( $\alpha_{\parallel}$ ) and perpendicular ( $\alpha_{\perp}$ ) to the molecular axis (the polarizability is supposed to be of rotational symmetry relative to the molecular axis), the degree of order  $S$ , the mean value of the dielectric constant  $\epsilon$ , the density and the temperature. For some nematic melts, viz. 4,4'-Di-n-hexyloxy-azobenzene, 4,4'-Di-n-hexyloxy-, -heptyloxy- and -octyloxy-azobenzene, we measured  $\epsilon_1$  and  $\epsilon_2$  at the frequencies 0,1; 0,26; 0,65; 1,6 and 4,0 Mhz and determined  $S$  from the infrared dichroism and  $\mu$  from the dielectric constant of the isotropic liquid phase as well as from solutions in benzene. In the case of the three azobenzenes  $\beta$  is known and one gets  $\alpha_{\parallel}$  and  $\alpha_{\perp}$ . The values obtained are in good agreement with those derived from bond polarizabilities.

The azoxybenzene-compound furnishes an interesting example for a further test of the theory. As far as their electrical properties are concerned its molecules differ from those of the corresponding azobenzene derivative only by the additional dipole moment of the azoxy-group, the principal polarizabilities being essentially the same. Taking the latter from the azobenzene-compound we calculated  $\beta$  from the anisotropy of the dielectric susceptibility and found it to be in good agreement with the value for 4,4'-Di-methoxy-azoxybenzene.

The hexyloxy-azoxybenzene is interesting yet in another sense. We found a pronounced dispersion of  $\epsilon_1$  ( $\epsilon_1'$ ) and a corresponding dielectric loss  $\epsilon_1''$  in our frequency range, whereas  $\epsilon_2$  shows no such a frequency dependence. According to the molecular statistical theory such a behaviour is to be expected. The dispersion step  $\epsilon_{10} - \epsilon_{1\infty}$  calculated from the theory and the molecular data above is in good agreement with the experimental value.

1. MAIER, W., G. BARTH and H. E. WIEHL, *Z. Elektrochem.*, *58*, 674 (1954).  
— und G. MEIER, *Z. physik. Chem.*, *13*, 251 (1957).
  2. MAIER, W. and A. SAUPE, *Z. Naturf.*, *14a*, 882 (1959) and *Z. Naturf.*, *15a*, 287 (1960).
-