

Zeitschrift: IABSE congress report = Rapport du congrès AIPC = IVBH
Kongressbericht

Band: 2 (1936)

Artikel: Steel pipes of large diameter subject to heavy internal pressure

Autor: Roš, M.

DOI: <https://doi.org/10.5169/seals-3356>

Nutzungsbedingungen

Die ETH-Bibliothek ist die Anbieterin der digitalisierten Zeitschriften auf E-Periodica. Sie besitzt keine Urheberrechte an den Zeitschriften und ist nicht verantwortlich für deren Inhalte. Die Rechte liegen in der Regel bei den Herausgebern beziehungsweise den externen Rechteinhabern. Das Veröffentlichen von Bildern in Print- und Online-Publikationen sowie auf Social Media-Kanälen oder Webseiten ist nur mit vorheriger Genehmigung der Rechteinhaber erlaubt. [Mehr erfahren](#)

Conditions d'utilisation

L'ETH Library est le fournisseur des revues numérisées. Elle ne détient aucun droit d'auteur sur les revues et n'est pas responsable de leur contenu. En règle générale, les droits sont détenus par les éditeurs ou les détenteurs de droits externes. La reproduction d'images dans des publications imprimées ou en ligne ainsi que sur des canaux de médias sociaux ou des sites web n'est autorisée qu'avec l'accord préalable des détenteurs des droits. [En savoir plus](#)

Terms of use

The ETH Library is the provider of the digitised journals. It does not own any copyrights to the journals and is not responsible for their content. The rights usually lie with the publishers or the external rights holders. Publishing images in print and online publications, as well as on social media channels or websites, is only permitted with the prior consent of the rights holders. [Find out more](#)

Download PDF: 06.08.2025

ETH-Bibliothek Zürich, E-Periodica, <https://www.e-periodica.ch>

VII b 6

Steel Pipes of Large Diameter Subject to Heavy Internal Pressure.

Stahlrohre für Druckleitungen mit großem Durchmesser und hohem Innendruck.

Tuyaux en acier pour conduites forcées de grand diamètre, sous de hautes pressions intérieures.

Dr. Ing. h. c. M. Roš,

Professeur à l'Ecole Polytechnique Fédérale et Président de la Direction du Laboratoire fédéral d'essai des matériaux et Institut de recherches — Industrie, Génie civil, Arts et Métiers — Zurich.

It has been found possible to obtain valuable information as to the distribution of stresses and strains, and to arrive at the factors of safety enumerated below, by means of tests carried out in the Swiss Federal Laboratory for Testing Materials during the years 1930 to 1935. The tests were carried through until the pipes burst under the effect of the internal pressure and they were correlated with extensive tests and investigations of actual pipe lines as well as of the materials employed. Diameter D = 1.8 — 4.6 m; pressure head H up to 1750 m; coefficient of capacity $H \cdot D^2 = 1500 — 3000$:

Type	Factors of safety as calculated		
	for static failure	for yield	fatigue rupture
1. Welded pipes with normal or helical welds, "Sulzer Winterthur" Normal quality steel, tensile strength $\beta_z = 38—42 \text{ kg/mm}^2$	3.5	2.4	1.6
High quality steel, tensile strength $\beta_z = 42—48 \text{ kg/mm}^2$	3.5	2.4	1.4
2. Hot bound pipes, "Ferrum" Katowice Tensile strengths $\beta_z \approx 38 \text{ kg/mm}^2$ in pipes $\beta_z \approx 60 \text{ kg/mm}^2$ in binding	3.4	2.3	—
3. Cold drawn, previously bound pipes, "Autofrettage G. Ferrand" by Bouchayer et Viallet, Grenoble Tensile strengths $\beta_z \approx 38 \text{ kg/mm}^2$ in pipes $\beta_z \approx 94 \text{ kg/mm}^2$ in binding	3.9	2.0	—
4. Pipes bound with steel wire from a reel, "Monteux", Paris Tensile strengths $\beta_z \approx 42 \text{ kg/mm}^2$ in pipes $\beta_z \approx 197 \text{ kg/mm}^2$ in binding	4.5	2.0	—

The four types which were subjected to close investigation are found to compete with one another technically and economically, and the helical welding is seen to make the competition keener. Each type offers technical and economic advantages of its own — whether with respect to weight, freedom from rusting, maintenance or safety — which require to be established by careful comparative experiments in each particular case.

As regards complicated shapes such as branches, junctions, inlets to turbines, large manholes, and sockets an accurate estimate of the true conditions of stress and safety can be obtained merely by measuring the stresses and strains under a multi-axial system of loading. Further valuable information can be obtained from a study of crack formation and lines of flow in specially applied coatings of lacquer. Fatigue tests and photo-elastic experiments offer means of estimating reductions in concentrations of stress.

The system of stresses and strains corresponding to the operating pressure must nowhere reach the yield value. Nothing but a combined application of all these methods of testing, in a perfected form, will allow the effective degree of safety of pressure pipe lines to be correctly assessed.

Leere Seite
Blank page
Page vide