

Zeitschrift: IABSE congress report = Rapport du congrès AIPC = IVBH
Kongressbericht

Band: 7 (1964)

Artikel: Supplement: studies on the application of high-strength bolted joints to
bridges

Autor: Konishi, Ichiro

DOI: <https://doi.org/10.5169/seals-7950>

Nutzungsbedingungen

Die ETH-Bibliothek ist die Anbieterin der digitalisierten Zeitschriften auf E-Periodica. Sie besitzt keine Urheberrechte an den Zeitschriften und ist nicht verantwortlich für deren Inhalte. Die Rechte liegen in der Regel bei den Herausgebern beziehungsweise den externen Rechteinhabern. Das Veröffentlichen von Bildern in Print- und Online-Publikationen sowie auf Social Media-Kanälen oder Webseiten ist nur mit vorheriger Genehmigung der Rechteinhaber erlaubt. [Mehr erfahren](#)

Conditions d'utilisation

L'ETH Library est le fournisseur des revues numérisées. Elle ne détient aucun droit d'auteur sur les revues et n'est pas responsable de leur contenu. En règle générale, les droits sont détenus par les éditeurs ou les détenteurs de droits externes. La reproduction d'images dans des publications imprimées ou en ligne ainsi que sur des canaux de médias sociaux ou des sites web n'est autorisée qu'avec l'accord préalable des détenteurs des droits. [En savoir plus](#)

Terms of use

The ETH Library is the provider of the digitised journals. It does not own any copyrights to the journals and is not responsible for their content. The rights usually lie with the publishers or the external rights holders. Publishing images in print and online publications, as well as on social media channels or websites, is only permitted with the prior consent of the rights holders. [Find out more](#)

Download PDF: 21.02.2026

ETH-Bibliothek Zürich, E-Periodica, <https://www.e-periodica.ch>

IIb 1

Supplement - Complément - Ergänzung

Studies on the Application of High-Strength Bolted Joints to Bridges¹⁾

Recherches sur l'utilisation, dans les ponts, d'assemblages réalisés avec des boulons à haute résistance

Untersuchungen über die Verwendung von hochfest verschraubten Stößen im Brückenbau

ICHIRO KONISHI

Kyoto University, Kyoto, Japan

This is the additional exposition to the question of the general reporter, Prof. DUBAS, to the paper IIb 1 of the Preliminary Publication.

The state of the faying surfaces was as rolled, and expectable friction coefficient is about $\mu = 0.25$. This value was determined from the experiments for regular test specimens done until 1958 in my laboratory. The design of the test beams was done based on the above experimental value during 1959. Bolted connection is not considered to be overstrengthened for the friction coefficient given. Special treatments to increase friction of the surface were not performed in this experiment although it is necessary for economical design of the bolted connection, especially for the European design.

The theoretical load-stress relations of bolted beams are as follows: This load P means that indicated in Fig. 1 of the original paper.

$P = 43.5$ ton	$\sigma = 1900$ kg/cm ²	design load
$P = 75.6$ ton	$\sigma = 3300$ kg/cm ²	yield load
$P = 86.4$ ton	slip of the connection occurs for $\mu = 0.25$	
$P = 88.8$ ton	welded section is of fully plastic.	

If some kinds of treatments are performed on the friction surface, and, for example, 0.45 friction coefficient is expected, a number of high strength bolts is about 8 instead of 12. It might be concluded that almost the same results could be obtained if a fatigue test for the beam with reduced bolts is performed, because there are only few differences between slip distributions near the first row bolts of the beams with 12 bolts and 8 bolts.

The fatigue tests of this paper were performed near the design load and fatigue properties of bolted and riveted beams under design loads were ob-

¹⁾ See "Preliminary Publication" — voir «Publication Préliminaire» — siehe «Vorbericht», IIb 1, p. 363.

tained. The fatigue tests near the slip load must be done with ordinary test specimens instead of composed beams.

Fatigue test near the slip load, using regular test specimens which are the same as those used for static tests for determining the friction coefficient, had been done by the author for various stress levels, but the effects of frequencies of repeated cycles are seems to be very important, and careful considerations on these must be paid.

Summary

The additional exposition to the paper II b 1 of the Preliminary Publication is given in this paper. It includes the condition of faying surfaces, the theoretical load-stress relations of the test beams, and the conditions of fatigue tests. The presumed characteristics of the beams with higher friction coefficient and, in consequence, less connection bolts are explained referring the results of original paper.

Résumé

Cet exposé complète le mémoire II b de la Publication préliminaire. Y sont décrits: l'état des surfaces de contact, les relations théoriques charges — contraintes des poutres d'essai et les conditions des essais de fatigue. Partant des résultats présentés dans le mémoire original, on indique les caractéristiques présumées des poutres possédant un coefficient de frottement plus élevé et, donc, un moins grand nombre de boulons d'assemblage.

Zusammenfassung

Dieser Beitrag enthält zusätzliche Erklärungen zum Beitrag II b 1 im «Vorbericht». Es werden folgende Fragen behandelt: Beschaffenheit der Kontaktflächen, theoretische Spannungsverhältnisse an Versuchsbalken sowie das Verhalten bei Ermüdungsversuchen. Die mutmaßlichen Eigenschaften von Trägern mit höherem Reibungskoeffizient, und demzufolge mit weniger Verbindungsschrauben, werden dargelegt unter Bezugnahme auf die im Originalbeitrag enthaltenen Ergebnisse.