

Zeitschrift: IABSE reports of the working commissions = Rapports des commissions de travail AIPC = IVBH Berichte der Arbeitskommissionen

Band: 6 (1970)

Artikel: Free discussion

Autor: Hollington, M.R.

DOI: <https://doi.org/10.5169/seals-7795>

Nutzungsbedingungen

Die ETH-Bibliothek ist die Anbieterin der digitalisierten Zeitschriften auf E-Periodica. Sie besitzt keine Urheberrechte an den Zeitschriften und ist nicht verantwortlich für deren Inhalte. Die Rechte liegen in der Regel bei den Herausgebern beziehungsweise den externen Rechteinhabern. Das Veröffentlichen von Bildern in Print- und Online-Publikationen sowie auf Social Media-Kanälen oder Webseiten ist nur mit vorheriger Genehmigung der Rechteinhaber erlaubt. [Mehr erfahren](#)

Conditions d'utilisation

L'ETH Library est le fournisseur des revues numérisées. Elle ne détient aucun droit d'auteur sur les revues et n'est pas responsable de leur contenu. En règle générale, les droits sont détenus par les éditeurs ou les détenteurs de droits externes. La reproduction d'images dans des publications imprimées ou en ligne ainsi que sur des canaux de médias sociaux ou des sites web n'est autorisée qu'avec l'accord préalable des détenteurs des droits. [En savoir plus](#)

Terms of use

The ETH Library is the provider of the digitised journals. It does not own any copyrights to the journals and is not responsible for their content. The rights usually lie with the publishers or the external rights holders. Publishing images in print and online publications, as well as on social media channels or websites, is only permitted with the prior consent of the rights holders. [Find out more](#)




Download PDF: 20.08.2025

ETH-Bibliothek Zürich, E-Periodica, <https://www.e-periodica.ch>

Free Discussion / Discussion libre / Freie Diskussion

M.R. HOLLINGTON
 Dr.
 Cement and Concrete Association
 Stough, England

The 1963 edition of the American Building Code Requirements for Reinforced Concrete (ACI 318-63) states that the additional long-term deflexion is a multiple of the instantaneous deflexion as shown in the following table :

REINFORCEMENT	SECTION	RATIO OF ADDITIONAL LONG-TERM DEFLEXION TO INSTANTANEOUS DEFLEXION
$A_{SC} = 0$	 (1)	2.0
$A_{SC} = 0.5 A_{St}$	 (2) A_{SC} A_{St}	1.2
$A_{SC} = A_{St}$	 (3) (4)	0.8

The results given in the Cement and Concrete Association Technical Report TRA.442 - "A series of long-term tests to investigate the deflexion of a representative precast concrete floor component" showed that the provision of compression steel in a lightly reinforced member did not reduce the long-term deflexions by the amounts predicted by the ACI Code. This investigation indicated that it was incorrect to assume that the long-term behaviour of the lightly reinforced section (4) would be the same as the heavily reinforced section (3) although the ratio of compression to tension steel areas is the same in both cases. The tests showed that section (4) behaved in a similar manner to section (2), and that the amount of restraint to long-term deformation was dependent on the arrangement of reinforcement in the compression zone, which need not be related to the area of tension steel determined by a collapse method of design as suggested by the American Code.