Zeitschrift:	IABSE reports = Rapports AIPC = IVBH Berichte
Band:	42 (1983)
Artikel:	Punching of concrete shells under ship collision
Autor:	Kavyrchine, M. / Ashtari, Nader
DOI:	https://doi.org/10.5169/seals-32421

Nutzungsbedingungen

Die ETH-Bibliothek ist die Anbieterin der digitalisierten Zeitschriften auf E-Periodica. Sie besitzt keine Urheberrechte an den Zeitschriften und ist nicht verantwortlich für deren Inhalte. Die Rechte liegen in der Regel bei den Herausgebern beziehungsweise den externen Rechteinhabern. Das Veröffentlichen von Bildern in Print- und Online-Publikationen sowie auf Social Media-Kanälen oder Webseiten ist nur mit vorheriger Genehmigung der Rechteinhaber erlaubt. <u>Mehr erfahren</u>

Conditions d'utilisation

L'ETH Library est le fournisseur des revues numérisées. Elle ne détient aucun droit d'auteur sur les revues et n'est pas responsable de leur contenu. En règle générale, les droits sont détenus par les éditeurs ou les détenteurs de droits externes. La reproduction d'images dans des publications imprimées ou en ligne ainsi que sur des canaux de médias sociaux ou des sites web n'est autorisée qu'avec l'accord préalable des détenteurs des droits. <u>En savoir plus</u>

Terms of use

The ETH Library is the provider of the digitised journals. It does not own any copyrights to the journals and is not responsible for their content. The rights usually lie with the publishers or the external rights holders. Publishing images in print and online publications, as well as on social media channels or websites, is only permitted with the prior consent of the rights holders. <u>Find out more</u>

Download PDF: 27.07.2025

ETH-Bibliothek Zürich, E-Periodica, https://www.e-periodica.ch

Punching of Concrete Shells under Ship Collision

Poinçonnement de coques en béton lors des collisions de navires Durchstanzen von Betonschalen bei Schiffskollisionen

M. KAVYRCHINE

Head of Struct. Dep. C.E.B.T.P. Paris, France



Engineer for French Administration of Highways for a short time, then Director of works and chief design engineer for French contractors. Since 1972 Head of C.E.B.T.P. Structural Studies Department Field of Activity Civil Engineering Buildings, Tall Buildings, Bridges, Prestressed and Reinforced Concrete, Structural Steel.

N. ASHTARI Doctor Engineer CETEN-APAVE Paris, France



Nader Ashtari, born 1945, got his Civil engineering degree at Lausanne Institute of Technology, Switzerland and his Ph. D. from Paris University. For nine years he was involved in teaching and researches. He was for many years a consulting engineer. Nader Ashtari, now in an inspection office, is expert in structure analysis.

SUMMARY

In connection with the problems of ship collision with supporting systems of concrete gravity structures, many concrete cylinder specimens were subjected to impact load with a speed of about 1.5 m/s. The local effects of the tests are compared with the effects of concentrated load on concrete cylinders. In the tests the size and shape of the load application area, the rate of reinforcements and the level of prestressing were varied in order to investigate the effect of this upon the failure load. A design method for punching shear of concrete cylinder is presented.

RÉSUMÉ

Pour étudier le comportement des piliers des structures offshore en béton sous l'effet de la collision de bateaux, plusieurs coques cylindriques en béton ont été soumises à l'impact d'un projectile avec une vitesse de 1,5 m/s. L'effet local d'impact a été comparé avec l'effet de la charge concentrée sur des cylindres en béton. Les dimensions et la forme de la zone d'application de la charge ont été modifiées ainsi que le pourcentage d'armature, afin de voir leur influence sur la charge de rupture. Une méthode de calcul de la résistance au poinçonnement des coques cylindriques est présentée.

ZUSAMMENFASSUNG

Um das Verhalten der Betonpfeiler von Offshore-Bauten unter dem Zusammenstoß von Schiffen zu studieren, sind mehrere zylindrische Betonschalen an einem Geschoßeinschlag von 1,5 m/sek Geschwindigkeit unterworfen. Die lokale Stoßwirkung wurde mit einer Einzelkraftswirkung auf einer Betonschale verglichen. Die Größe und die Form der Stoßzone wurden verändert, ebenfalls der Bewährungsprozent, um den Einfluß auf der Bruchlast zu bestimmen. Eine Durchstanzwiderstandrechnungsmethode wurde für zylindrische Schalen vorgestellt.

1. INTRODUCTION

To study the local effect of ship collision on offshore gravity structures, C.E.B.T.P.* has undertaken a research program since 1979. At first the aim was to determine the nature of impact and see the difference between its local effect and punching shear failure.

An attempt is made to find the influence of reinforcement and longitudinal prestressing. In this field many tests have been performed on cylindrical concrete shells. These tests allowed us to propose a design method for punching shear. We wish to mention that this research program was financially supported by ARBEM (French Association for concrete at Sea) and French Ministry of Transport.

2. DESCRIPTION OF TESTS

2.1 Models and test equipments

The tower of structure receiving the collision was modelized by a cylindrical concrete shell showing an approximate ratio of 1/10 between thickness and diameter. We consider only the accidental collision (see definition - Ref [1]) of the supply boat with a collision speed about 1.5 m/s. In this case the duration of impact is longer than the shaft's own period and the problem of dynamic amplification, due to structure vibration, is not encountered. Therefore in our test we have not studied the effect of vibration. To reduce the flexural effects we maintened our concrete cylinder in a special steel device (fig. 1). Mortar was injected between the steel cylinder and concrete shell.

A 30 x 60 cm opening is left at the top of the device to allow load application.

2.2 Orientation tests

The aim of these tests was to compare the local effect of impact of a rigid body at a low speed (about 1.5 m/s) with punching shear failure (load applied by a hydraulic jack).

In both cases, the load was applied by a circular, 120 mm diameter, steel puncheon.

The impact tests were carried out by fall of a steel ram. The ram was made of 300 mm diameter steel discs, assembled around a steel rod (see fig. 2). The mass may be modified according to the needs of the test. The ram falls from heights of 115 mm (v = 1.5 m/s). The deformations and local deflections in several points of the cylinder and also the impact force were recorded.

It emerged from the tests that at failure, the impact loads are nearly the same as punching shear loads.

In both cases, at failure, a concrete plug is punched out in the direction of the load, the rest of the cylinder remaining intact. The upper part of the plug keeps the shape of the puncheon. The dimensions and shape of failure surface are very similar (see fig. 3).

After this phase we continued our tests with static concentrated load. Many tests were performed with different shape (circular and elliptic) and different size of puncheon.

In some cases to achieve a good contact between concrete and puncheon we used a concave puncheon with a interposed rubber sheet. In these particular cases we observed an increase of failure load about 18 %.

* C.E.B.T.P. : Centre Expérimental de Recherches et d'Etudes du Bâtiment et des Travaux Publics.







Fig. 1 Testing equipment



Fig. 2 Steel ram



Longitudinal cross section



Essai Amm Bmm MJ1.1 270 440 Static Test MJ2.1 290 400 M.11.7 260 230 430 M.J1.9 M.J1.13 M.J2.5 420 460 Dynamic Test 260 290 440

Fig. 3 Failure surface

Reference of test	Form of Steel nose	Fa ilure load (KN)	Ratio <u>Test failure</u> Theoretical failure	Ratio <u>Experimental B</u> Theoretical B	Ratio <u>Experimental A</u> Theoretical A
1.1	circular 120 mm	233.7	0.98	0.99	1 1/
2.1	circular 120 mm	254.8	0.95	0,90	1,14
3.2	circular 100 mm	225,4	0,99	1.08	1.07
3.3	elliptic	054 0		,,,,,,,,,,,,,,,,,,,,,,,,,,,,,,,,,,,,,,,	1,07
2.4	150 x 100 mm	254,8	0,98	0,93	1,11
3.4	circular 140 mm	401,8	1,1	1,04	1,22
5.5	circular 50 mm	1/0,5	1,23	1,1	1,26
4.1	elliptic				
	150 x 100 mm	235,2	0,91	1.00	1.11
4.2	elliptic			.,	.,,.
	150 x 100 mm	331,1	1,09	0.97	1,16
	with neoprene				,,
4.3	elliptic		8		
	150 x 100 mm	313,ú	1,03	1.00	1.16
	curved		-		.,
	with neoprene				
5.1	11	224 ú	0.94	0.01	0.00
5.2	11	234 6	0,99	0,21	0,99
5.3	11	234 6	0,92	1 00	1,18
5.4	11	244 8	0,28	1,00	1,04
5.5	n	265 2	1.06	0,99	1,10
5.6	н	244 8	0.94		1,13
5.7		153 0	0.87	0,77	1,18
5.8		145 9	0,83	0,00	1,08
5.9	n –	153.0	0,81	0,07	1,12
5.10	н	161.2	0.85	0,07	1,04
		102,2	0,09	0,70	1,10
·				L	

224

The observation of failure surface confirmed the previous results. All these tests were carried out on the standard ducts produced by BONNA (716 mm external diameter and 58 mm thickness). The rate of reinforcement was not very high.

2.3 Tests with prestressed concrete

In order to investigate, the influence of concrete strength, reinforcements and prestressing, we used five specially made concrete cylinders. Two types of reinforcement (\emptyset 6 mm spaced 5 cm in two directions and \emptyset 6 mm spaced 8 cm in two directions) are considered. The reinforcement was in the mid thickness of cylinder. The ultimate strength of concrete varied between 28 to 58 MPa. The prestressing force varied from 0 to 500 KN.

The effect of reinforcement and longitudinal prestressing upon the failure load turns to be slight, on the other hand a higher rate of reinforcement leads to higher ductility of failure.

3. DESIGN METHOD

Our tests have shown that local effect of ship collision with offshore plateforms is similar to punching shear failure. To estimate the punching shear strength of cylindrical concrete shells an analytical solution is developped. The method is a generalization of the method presented by BRAESTRUP [2] for punching shear in concrete slabs.

A plastic limit analysis based upon the failure mechanism is used to calculate the punching load, we equate the external work produced by the punching force with the internal work dissipated in the failure surface. To satisfy the requirements of limit analysis, we assumed that concrete is a rigid, perfectly plastic material with the modified coulomb failure criterion as yield condition and the deformations governed by the associated flow rule (normality condition).

The load found by equating the rate of external and internal work is an upper bound solution for the punching load. By minizing this load, we approach the real punching load. For more details see réf [3].

This solution does not give only the punching load but it also determines the failure surface and takes in account the exact shape of puncheon. A comparison between calculated and experimental failure load and failure surface is given in table 1. To compare the experimental and calculated failure surface, we have chosen the length of the two perpendicular axes at the base of plug, as comparison criterion. See fig. 3.

REFERENCES

- 1. Bo CARLIN, Chris MORLAY, Industrial and Offshore Division Det Norske Veritas, Technical Report, November 1977
- BRAESTRUP M.W., Punching shear in concrete slabs. IABSE Colloquium on Plasticity in Reinforced Concrete, Introductory Report p ; 115-136, Copenhagen 1979
- 3. ASHTARI N., Poinçonnement des coques en béton armé, calcul et justification expérimentale, Annales de l'I.T.B.T.P. nº 411, Janvier 1983
- KAVYRCHINE M., ASHTARI N., Choc de bateaux sur les structures offshore en béton, étude du poinçonnement, 2nd international Symposium on Behaviour of Offshore Concrete Structures, Paris, Octobre 1982

Leere Seite Blank page Page vide