Zeitschrift: IABSE reports = Rapports AIPC = IVBH Berichte

Band: 54 (1987)

Artikel: Tests of size effect in pull-out of reinforcing bars from concrete

Autor: Bazant, Zdenek P. / Sener, Siddik

DOI: https://doi.org/10.5169/seals-41925

Nutzungsbedingungen

Die ETH-Bibliothek ist die Anbieterin der digitalisierten Zeitschriften auf E-Periodica. Sie besitzt keine Urheberrechte an den Zeitschriften und ist nicht verantwortlich für deren Inhalte. Die Rechte liegen in der Regel bei den Herausgebern beziehungsweise den externen Rechteinhabern. Das Veröffentlichen von Bildern in Print- und Online-Publikationen sowie auf Social Media-Kanälen oder Webseiten ist nur mit vorheriger Genehmigung der Rechteinhaber erlaubt. Mehr erfahren

Conditions d'utilisation

L'ETH Library est le fournisseur des revues numérisées. Elle ne détient aucun droit d'auteur sur les revues et n'est pas responsable de leur contenu. En règle générale, les droits sont détenus par les éditeurs ou les détenteurs de droits externes. La reproduction d'images dans des publications imprimées ou en ligne ainsi que sur des canaux de médias sociaux ou des sites web n'est autorisée qu'avec l'accord préalable des détenteurs des droits. En savoir plus

Terms of use

The ETH Library is the provider of the digitised journals. It does not own any copyrights to the journals and is not responsible for their content. The rights usually lie with the publishers or the external rights holders. Publishing images in print and online publications, as well as on social media channels or websites, is only permitted with the prior consent of the rights holders. Find out more

Download PDF: 19.11.2025

ETH-Bibliothek Zürich, E-Periodica, https://www.e-periodica.ch




Tests of Size Effect in Pull-Out of Reinforcing Bars from Concrete

Influence de la dimension lors de l'extraction des barres d'armatures du béton Versuche zum Masstabseinfluss auf das Verbundverhalten von Bewehrungsstäben

Zdenek P. BAZANT Prof. of Civil Eng. Northwestern University Evanston, IL, U.S.A.



Born and educated at Prague, Dr. Bažant joined the faculty of Northwestern University in 1969, where he has been professor since 1973 and served as Structural Engineering Coordinator and as Director of the Center for Concrete and Geomaterials.



Siddik SENER Visiting Scholar Northwestern University Evanston, IL, U.S.A.

SUMMARY

The paper gives a brief preliminary report on pull-out tests of geometrically similar specimens of very different sizes. The test results indicate a significant size effect which can be described by Bažant's approximate size effect law.

RÉSUMÉ

L'article donne un bref rapport préliminaire d'essais d'extraction de spécimen géométriquement semblables mais de dimension très différentes. Les résultats d'essais montrent un effet très important de la dimension qui peut être décrit comme la loi de l'effet de la dimension approximative de Bažant.

ZUSAMMENFASSUNG

Das Ziel dieses Beitrags ist, einen kurzen Bericht über Ausziehversuche an geometrisch ähnlichen Probekörpern verschiedener Grösse zu geben. Die Ergebnisse zeigen einen deutlichen Massstabseinfluss, der mit dem Modell von Bažant beschrieben werden kann.



Introduction

The pull-out failure of reinforcing bars embedded in concrete is known to be a brittle failure in which the maximum load decreases after its peak value rather than remaining constant. For this type of failure, theoretical analysis shows there should be a significant size effect, such that the nominal stress at failure decreases as the specimen size increases. Although the fracture mechanics aspects of pull-out failures have been pointed out by various authors, e.g., by S. P. Shah and A. Ingraffea, and the presence of fracture mechanics type size effect have been suspected, no test data which would clearly document this effect have apparently been obtained so far. Experimental verification requires testing specimens that are geometrically similar and a brief preliminary report on such tests which were carried out at Northwestern University is the purpose of this paper.

Tests and Their Evaluation

The test specimen was a cube with a steel bar embedded in it, parallel to one edge of the cube and sticking out at the center of one face. The sides of the cubes tested were d=1.5in., 3 in., and 6 in., and the reinforcing bars were scaled in proportion to the size of the cubes, having nominal diameters 0.125 in., 0.25 in., and 0.5 in. respectively (1 in. = 25.4mm). The yield strength of steel was 60,000 psi (1 psi = 6895 N). The embeddment lengths were 0.5in., 1 in., and 2 in., respectively, which ensured the specimen to fail before the yielding of the bars coud occur. One specimen of each size was cast from the same batch of concrete. The concrete mix ratio of water:cement:sand:gravel was 0.6:1:2:2, by weight. The maximum gravel size was $d_a=0.25$ in., and the maximum sand grain size was 0.132 in. The aggregate was crushed limestone, and the sand was a siliceous river sand. The aggregate and sand were Portland cement C150, of ASTM Type I, with no air-dried prior to mixing. admixtures, was used. Companion cylinders of 3 in. diameter and 6 in. length were cast from each batch of concrete. The mean compression strength of these cylinders after standard 28-day moist curing was f'=6,650 psi. The cubes were removed from their plywood forms 1 day after casting and were subsequently cured in a moist room of relative humidity 95% and temperature 78° F for 28-days. Then the tests were made in a 60-ton Baldwin frame modified as a servo-controlled closed loop machine with an MTS controller. The ends of the steel bars were gripped in the machine, and the reaction was provided by a square sleeve made of split reinforcing bars as shown in Fig. 2, the sides of these squares being 0.5 in., 1 in., and 2 in. for the small, medium and large These reaction square sleeves were glued to concrete by epoxy shortly before testing.

Orangun et al. [1] developed for the bond strength the formula:

$$v_u = k_1 \left[1.22 + 3.23 \text{ C/d}_b + 53d_b/\ell_d \right] \sqrt{f}_c'$$
 (1)

in which $v_c = 28$ -day bond strength in psi, C = minimum clear cover of concrete in inches, $\ell_d = embeddment$ length in inches, $d_b = nominal$ bar diameter in inches, $f'_c = standard$ 28-day cylinder strength of concrete in psi, and $k_1 = an$ empirical coefficient. According to Bažant's approximate size effect law for failures due to distributed cracking, this formula may be extended as follows:

$$v_u = c_1 k_1 (1 + \frac{d_b}{\lambda_0 d_a})^{-1/2}, \quad c_1 = (1.22 + 3.23 \frac{c}{d_b} + 53 \frac{d_b}{\lambda_d}) \sqrt{f_c'}$$
 (2)

in which d_a = the maximum size of aggregate and λ_0 = a coefficient



characterizing the center of the transition from failures dominated by plastic limit analysis to failures dominated by linear elastic fracture mechanics. The formula of Orangun et al., yielded better agreement with the present test results than other formulas such as that of ACI [5] or of Aboona [6]. The nominal bond strength given by Eq. 2 is defined as $v_u = T/s_d$ where $T = \max tensile$ force in the bar and s = nominal surface area of the reinforcing bar embedded in concrete.

Eq. 2 can be algebraically rearranged to a linear plot in which Y = $(C_1/v_u)^2$ is plotted versus X = d_b/d_a . The present test results, listed in Table I, are plotted in this manner in Fig. 3 (left). The optimum fit can be obtained by linear regression, and the regression parameters are given in the figure along with the coefficient of variation of the vertical deviations from the regression line $\omega_{V|X}$, the correlation coefficient r, and the coordinates X and Y of the data centroid. Based on linear regression, one may then plot the diagram of log (v_u/C_1) versus log (d_b/d_a) , as shown in Fig. 3 on the right. The test results in these plots represent the individual tests made. If the averages for each size are plotted, the scatter is of course considerably reduced.

Conclusions

Despite the significant scatter of the test results, probably inevitable in this type of test, the size effect is clearly apparent. Although the test results cannot be said to validate the applicability of the size effect law, they are nevertheless described by this law adequately.

Acknowledgment. - Financial support for the theoretical research which underlies the present approach was received from U. S. Air Force Office of Scientific Research under Contract No. F49620-87-C-0030DEF with Northwestern University, monitored by Dr. Spencer T. Wu.

References

- ORANGUN, C. D., JIRSA, J. O., and BREEN, J. E., A Re-evaluation of Test Data on Develoment Length and Splices, ACI Journal, 74, pp. 114-122, 1977.
- 2. BAŽANT, Z. P., Size Effect in Blunt Fracture: Concrete, Rock, Metal, ASCE Journal of Engineering Mechanics, 110, pp. 518,535, 1984
- 3. BAŽANT, Z. P., Mechanics of Distributed Cracking, Applied Mecanics Reviews 39, May, No. 5, pp. 675-705,1986.
- 4. BAŽANT, Z. P., Fracture Energy of a Heterogeneous Brittle Material and Similitude, Preprints, RILEM-SEM Int. Conf. on Fracture of Concrete and Rock, held in Houston, 1987, ed. by S. P. Shah and S. Swartz, Publ. by Soc. of Exper. Mechanics in press, 1987.
- 5. ACI Committee 318, Building Code Requirements for Reinforced Concrete, ACI, Detroit, pp. 87, 1983.
- 6. ABOONA, L. R., Development of a Design Type Solution for Predicting the Ultimate Shear Force in Reinforced Concrete Beams, M.S. Thesis, Northwestern University, Evanston, Illinois, U.S.A., 1985.






Fig. 1 - Size Effect Law

Fig. 2 - Specimen Geometry




Fig. 3 - Size Effect Observed in pullout Tests

Table 1. Pullout Test Results

Beam No	d _b	l _d in.	da in.	fc' psi	F _u p
A1 A2 A3 A4 A5 A6 A7 A8 A9 A10 A11	.5 .5 .5 .25 .25 .25 .113 .113	2. 2. 2. 1. 1. 0.5	. 25	6650 6650 6650 6650 6650 6650 6650 6650	5040 4801 5592 6624 1512 1800 1836 1560 502 468 656