

Zeitschrift: IABSE reports = Rapports AIPC = IVBH Berichte
Band: 55 (1987)

Artikel: New arch construction technique
Autor: Melbourne, Clive
DOI: <https://doi.org/10.5169/seals-42818>

Nutzungsbedingungen

Die ETH-Bibliothek ist die Anbieterin der digitalisierten Zeitschriften auf E-Periodica. Sie besitzt keine Urheberrechte an den Zeitschriften und ist nicht verantwortlich für deren Inhalte. Die Rechte liegen in der Regel bei den Herausgebern beziehungsweise den externen Rechteinhabern. Das Veröffentlichen von Bildern in Print- und Online-Publikationen sowie auf Social Media-Kanälen oder Webseiten ist nur mit vorheriger Genehmigung der Rechteinhaber erlaubt. [Mehr erfahren](#)

Conditions d'utilisation

L'ETH Library est le fournisseur des revues numérisées. Elle ne détient aucun droit d'auteur sur les revues et n'est pas responsable de leur contenu. En règle générale, les droits sont détenus par les éditeurs ou les détenteurs de droits externes. La reproduction d'images dans des publications imprimées ou en ligne ainsi que sur des canaux de médias sociaux ou des sites web n'est autorisée qu'avec l'accord préalable des détenteurs des droits. [En savoir plus](#)

Terms of use

The ETH Library is the provider of the digitised journals. It does not own any copyrights to the journals and is not responsible for their content. The rights usually lie with the publishers or the external rights holders. Publishing images in print and online publications, as well as on social media channels or websites, is only permitted with the prior consent of the rights holders. [Find out more](#)

Download PDF: 01.04.2026

ETH-Bibliothek Zürich, E-Periodica, <https://www.e-periodica.ch>

New Arch Construction Technique

Un nouveau mode de construction des voûtes

Neue Bauweise für Bogenbrücken

Clive MELBOURNE

Senior Lecturer

Bolton Inst. of higher education

Bolton, UK


1. INTRODUCTION

The majority of the world's stock of arches are constructed of brick or stone and have stood for hundreds of years. They have shown themselves to be durable structures, capable of carrying loads very much greater than those envisaged by their designers.

The Department of Transport and the Science and Engineering Research Council are funding a nationwide research programme to study the performance of arch bridges. The Bolton Institute of Higher Education is one of the centres contributing to the research programme. In the course of his research, the author has developed a new arch construction technique.

2. DEVELOPMENT OF NEW TECHNIQUE

Consideration was given to the feasibility of producing arches using mass concrete. The first model was constructed using plastic sheeting 1mm thick which was cut to shape and glued together to form through thickness crack inducers (Figure 1)



(A) PARTS OF A MASONRY ARCH BRIDGE




FIGURE 1 DEVELOPMENT OF CONSTRUCTION TECHNIQUE



These were positioned against the skewbacks. Subsequent crack inducers were installed with diaphragms. The latter acted as both stiffeners and spacers. The whole procedure was repeated until the entire soffit shutter was covered with crack inducers in a pattern similar to the joints in a stone voussoir arch. The stepped shutter arrangement allowed concrete to be placed without a top shutter - even at the springings. Subsequent testing of the arch showed that it performed in a similar manner to a voussoir arch, forming four hinges at collapse. The hinges occurred at the springings and in the region of the quarterpoints.

The construction technique was simplified to make it viable for full scale bridges. The crack inducers were restricted to the springings and quarterpoints. A simple procedure was followed as shown in Figure 2.

A series of tests were performed in the laboratory using various shapes of arch. In each case, the performance was similar to that of a voussoir arch.

3. PROTOTYPES

Two bridges have been constructed satisfactorily using the technique. Although they were relatively small with spans of 2.8m and 10.2m respectively. They have shown the method is viable for full scale construction. Both bridges have received SERC awards to be instrumented and tested. In each case the bridges performed well.




FIGURE 2 CONSTRUCTION SEQUENCE

4. CONCLUSIONS

The construction technique has many advantages over that of its equivalent reinforced concrete arch:

- (1) it is potentially more durable as there is no reinforcement to corrode;
- (2) it is simple and quick to construct;
- (3) the analysis and design are straightforward which makes design details simple and hence contract drawings minimal;
- (4) Voussoir arches are less sensitive to thermal, shrinkage and settlement movements. The articulation of the voussoirs allows the stresses to redistribute without loss of structural integrity.