

Zeitschrift: IABSE reports = Rapports AIPC = IVBH Berichte
Band: 60 (1990)

Artikel: Load carrying capacity of a new composite column
Autor: Inoue, Kazuo / Igarashi, S. / Chulhwan, E.
DOI: <https://doi.org/10.5169/seals-46475>

Nutzungsbedingungen

Die ETH-Bibliothek ist die Anbieterin der digitalisierten Zeitschriften auf E-Periodica. Sie besitzt keine Urheberrechte an den Zeitschriften und ist nicht verantwortlich für deren Inhalte. Die Rechte liegen in der Regel bei den Herausgebern beziehungsweise den externen Rechteinhabern. Das Veröffentlichen von Bildern in Print- und Online-Publikationen sowie auf Social Media-Kanälen oder Webseiten ist nur mit vorheriger Genehmigung der Rechteinhaber erlaubt. [Mehr erfahren](#)

Conditions d'utilisation

L'ETH Library est le fournisseur des revues numérisées. Elle ne détient aucun droit d'auteur sur les revues et n'est pas responsable de leur contenu. En règle générale, les droits sont détenus par les éditeurs ou les détenteurs de droits externes. La reproduction d'images dans des publications imprimées ou en ligne ainsi que sur des canaux de médias sociaux ou des sites web n'est autorisée qu'avec l'accord préalable des détenteurs des droits. [En savoir plus](#)

Terms of use

The ETH Library is the provider of the digitised journals. It does not own any copyrights to the journals and is not responsible for their content. The rights usually lie with the publishers or the external rights holders. Publishing images in print and online publications, as well as on social media channels or websites, is only permitted with the prior consent of the rights holders. [Find out more](#)

Download PDF: 01.04.2026

ETH-Bibliothek Zürich, E-Periodica, <https://www.e-periodica.ch>

Load Carrying Capacity of a New Composite Column

Capacité portante d'une nouvelle colonne mixte

Tragfähigkeit einer neuartigen Verbundstütze

Kazuo INOUE

Assoc. Prof.
Osaka Univ.
Osaka, Japan

S. IGARASHI

Professor
Osaka Univ.
Osaka, Japan

E. CHULHWAN

Graduate Student
Osaka Univ.
Osaka, Japan

Tsutomu ARAI

Struct. Engineer
Ohbayashi Corp.
Osaka, Japan

INTRODUCTION

The elastic stiffness and the ultimate flexural strength of a new type composite column is presented. A concept of this composite structure is shown in Fig.1. Four precast-concrete panels (hereafter, denoted as PCa panel) are fixed to the steel square tube with headed studs. The studs have two functions; one is to transmit the shear stress of PCa panels to steel tube, and the other is to prevent the split off action of PCa panels. Holes are made in PCa panels to be fixed on all the sides of the steel tube on which studs are welded. These holes are filled up with high-strength mortar.

The purposes of the composite column are as follows :

- [1] To increase the stiffness and strength of steel columns by combining the PCa panels. These panels are also useful as the fire resistance material for steel tube.
- [2] To improve the quality and productivity of structural system by eliminating the work of bar arrangement and the work of paneling at construction sites.




Fig. 1 The Concept of the Composite Column Structural System

TEST RESULTS

Test specimens shown in Fig. 2 are subjected to combined anti-symmetrical bending moment and axial force. Fig. 3 shows the loading setup. Nineteen specimens, five of steel column and fourteen of composite column, were tested. Four specimens including one steel column were subjected to bi-axial bending. The PCa panels of three composite columns out of fourteen are conventionally reinforced with steel bars. For the remaining eleven composite columns, PCa panels are reinforced with the steel fibers only. Volume fraction of the fiber is 2%. The degree of reinforcement is so determined as to transmit the shear stress of PCa panel to headed studs.

Typical axial force(N)-to-axial deformation(u) relation, and the terminal moment(M)-to-rotation(θ) relation under the constant axial force are shown in Fig. 4 and Fig. 5, respectively. In the figures, the test results of composite column are compared with those of the bare steel columns subjected to the same axial force. Fig. 6 shows the bending moment-axial force interaction curves of the steel column and the composite column. The maximum flexural strength of each specimen is also plotted in this figure.

It is clear from the above results that the stiffness and the strength of composite columns are much greater than those of steel columns. No shear cracks were observed in PCa panels throughout the test. As shown in Fig. 6, under the axial force, the maximum flexural strength of composite columns with PCa panels reinforced with steel bars does not reach the theoretical strength due to the premature compressive fracture of PCa panels. On the other hand, the use of steel fibrous concrete in PCa panels has led to the increase in the ultimate flexural strength of composite columns. Consequently, the flexural strength of all these columns is beyond the theoretical value regardless of the axial force.




Fig. 2 Composite column specimen




Fig. 3 Loading setup and moment distribution of specimen




Fig. 4 Axial force-to-axial deformation relations




Fig. 5 Terminal moment-to-rotation relations




Fig. 6 M-N interaction curves

— Uniaxial bending - - - - - Biaxial bending