Zeitschrift:	IABSE reports = Rapports AIPC = IVBH Berichte
Band:	62 (1991)
Artikel:	Effects of residual strength of cracked concrete on bond
Autor:	Giuriani, Ezio / Plizzari, Giovanni / Schumm, Cristiano
DOI:	https://doi.org/10.5169/seals-47631

Nutzungsbedingungen

Die ETH-Bibliothek ist die Anbieterin der digitalisierten Zeitschriften auf E-Periodica. Sie besitzt keine Urheberrechte an den Zeitschriften und ist nicht verantwortlich für deren Inhalte. Die Rechte liegen in der Regel bei den Herausgebern beziehungsweise den externen Rechteinhabern. Das Veröffentlichen von Bildern in Print- und Online-Publikationen sowie auf Social Media-Kanälen oder Webseiten ist nur mit vorheriger Genehmigung der Rechteinhaber erlaubt. <u>Mehr erfahren</u>

Conditions d'utilisation

L'ETH Library est le fournisseur des revues numérisées. Elle ne détient aucun droit d'auteur sur les revues et n'est pas responsable de leur contenu. En règle générale, les droits sont détenus par les éditeurs ou les détenteurs de droits externes. La reproduction d'images dans des publications imprimées ou en ligne ainsi que sur des canaux de médias sociaux ou des sites web n'est autorisée qu'avec l'accord préalable des détenteurs des droits. <u>En savoir plus</u>

Terms of use

The ETH Library is the provider of the digitised journals. It does not own any copyrights to the journals and is not responsible for their content. The rights usually lie with the publishers or the external rights holders. Publishing images in print and online publications, as well as on social media channels or websites, is only permitted with the prior consent of the rights holders. <u>Find out more</u>

Download PDF: 08.07.2025

ETH-Bibliothek Zürich, E-Periodica, https://www.e-periodica.ch



Effects of Residual Strength of Cracked Concrete on Bond

Effets sur l'adhérence des contraintes résiduelles du béton éclaté

Einfluss der Restzugfestigkeit gerissenen Betons auf den Verbund

Ezio GIURIANI

Prof. of Civil Eng. University of Brescia Brescia, Italy

Ezio Giuriani, born 1945, Professor of reinforced concrete and performance concrete structures at the Dep. of Civil Eng., University of Brescia, member of Commission VI of CEB, since 1983 Professor of Steel Concrete Composite Structures at «Corso di Perfezionamento F. III Pasenti», Politecnico of Milan, for post graduate students.

Giovanni PLIZZARI

Res. Eng. University of Brescia Brescia, Italy

Giovanni Plizzari, born 1959, received his civil engineering degrees at the Politecnico of Milan, has a fellowship at the Dep. of Civil Eng. University of Brescia, is involved in laboratory research works especially on concrete materials and reinforced concrete structures.

Cristiano SCHUMM

Res. Eng. Politecnico of Milan Milan, Italy

Cristiano Schumm, born 1959, obtained the civil engineering degree at Politecnico of Milan, presently Ph.D. student at the same University, since 1986 research involved in activities on reinforced concrete structures and fiber reinforced concrete.

SUMMARY

The local bond-slip law of an anchored ribbed bar after the complete cracking of the surrounding concrete is studied. The theoretical approach is based on the confining effects due both to the transverse reinforcement and the residual tensile strength of cracked concrete. Experimental confirmations and theoretical results are presented. In particular the confining effects produced by the residual strength of cracked concrete are investigated and discussed.

RÉSUMÉ

On étudie ici la loi localisée d'«adhérence-glissement» apparaissant dans le cas d'une barre nervurée ancrée après éclatement complet du béton d'enrobage. L'approche théorique se base sur des effets confinants dûs conjointement à l'armature transversale ainsi qu'aux contraintes de traction résiduelles du béton éclaté. Des confirmations expérimentales et des résultats théoriques sont présentés; les effets confinants provoqués par la contrainte résiduelle du béton éclaté sont examinés et discutés en détail.

ZUSAMMENFASSUNG

Das örtliche Verbundgesetz für die Verankerung eines gerippten Bewehrungsstabs in vollständig gerissenem Beton wird untersucht. Grundlage für die theoretische Untersuchung sind die Umschnürungseffekte infolge der Querbewehrung und der Restzugfestigkeit des gerissenen Betons. Theoretische Ergebnisse und experimentelle Bestätigungen werden vorgestellt. Insbesondere werden die Einflüsse einer Umschnürung infolge der Restfestigkeit des Betons untersucht und diskutiert.



1. INTRODUCTION

The importance of the tensile strength of concrete on bond was underlined in [1]. In the same paper this phenomenon was theoretically modelled and the bond strength was evaluated taking into consideration the tensile strength of solid concrete that surrounds the split core. Experimental tests [2] showed that the bond stress-slip relationship is influenced both by the amount of stirrups and by the thickness of the concrete cover. A theoretical interpretation and modelling of the phenomena involved around an anchored bar were proposed in [3,4], where the relevance of the confining action produced by the residual tensile strength of the split concrete was underlined. At the beginning, the splitting crack opens near the anchored bar (Fig.1a,b) and propagates both transversally and along the bar. When it is completely propagated throughout the cross-section, bond strength is still locally possible owing to the confining actions produced by the transverse reinforcement and the residual stress transmitted by the crack faces [5,6]. For light or no transverse reinforcement, bond stress decreases as slip increases, so that an unstable local behaviour occurs. When the split zone is limited as in Fig.1, bond stress redistribution along the bar can occur and a ductile global behaviour of the anchorage is still possible. The bigger the concrete cover and bar spacing become, the more relevant the confining contribution of cracked concrete is. This is because a small residual stress acting on a large split surface can produce a considerable confining action. Since the splitting crack opening is variable both across the transverse section and along the anchored bar, the local response of the cracked concrete is also variable. The cracked concrete confining contribution should be evaluated by means of the tensile stress-crack opening law. The well known specific fracture energy GF, which is the integral of this law, is not sufficient to express the cracked concrete confining capacity, at least in the present theory on bond.

2. ANALYTICAL FUNDAMENTALS

In anchorages with completely propagated splitting cracks, bond is still possible when an adequate transversal confining action is assured. This confinement can be produced both by the transverse reinforcement (secondary bars or stirrups) and by the residual strength of cracked concrete.

The modelling of the local bond behaviour in anchorages when splitting occurs is developed on the basis of the following assumptions:

1. The splitting crack is completely propagated along the bar spacing and cover in influence zone Δz of one transverse bar (Fig.1c).

2. Δz is small and has the same value of stirrup spacing, so that average crack opening w and bond stress τ can be assumed as the local values.

3. All the principal bars have the same diameter ϕ_P and all the transverse bars have the same diameter $\phi_{\rm st}.$

According to these assumptions, the following equations were proposed in [3,4]. For bond:

$$\tau = \tau_{m,0} (1 - \gamma_1 w/\phi_p) (1 - e^{-(\beta_1 + \beta_2 w/\phi_p)(s/\phi_p - \gamma_2 w/\phi_p)})$$
(1)

$$\tau = \tau_0(1/(1+K_1w/\phi_p)) + \tau_1\sigma_n(1/(1+K_2w/\phi_p))$$
(2)

where $\tau_{m,0}$ = maximum bond stress for w=0; γ_1 , γ_2 , β_1 , β_2 , K1 and K2= coefficients experimentally determined on the basis of the curves plotted in Fig.2a,b and obtained in [7]; s = principal bar slip and σ_n = radial stress produced by the principal bar. The limitation $\tau = \tau_{m,0}$ when $\tau > \tau_{m,0}$ was adopted. For stirrup stress (1st confining action) equation:

$$\sigma_{st} = E_{s} \sqrt{a_{2}(w/(\alpha \phi_{st}))^{2} + a_{1}(w/(\alpha \phi_{st})) + a_{0}}$$
(3)

plotted in Fig.2c, was assumed according to [8] where Es = Young's modulus for

steel; a0, a1 and a2 = coefficients of the ideal trilateral local bond stressslip law of the transverse bars and α = factor characterizing the position of the splitting crack (Fig.4d). For tensile stress transmitted by the splitting crack faces (2nd confining action) equation:

$$\sigma_{\rm rc} = f_{\rm ct0} / (\kappa \, w/\phi_{\rm a} + 1) \tag{4}$$

plotted in Fig.2d, was adopted according to [6] where fcto and κ = coefficients experimentally determined and ϕ_a = maximum aggregate size.

Eq.1 is based on the following similitude criterion: both crack opening w and slip s are proportional to bar diameter ϕ_p . In this way, for the same value of ratios s/ϕ_p and w/ϕ_p all the coefficients γ_1 , γ_2 , β_1 and β_2 should be independent of ϕ_p . Even coefficients τ_0 , τ_1 , K1 and K2 in Eq.2 should be independent of ϕ_p , having adopted ratio w/ϕ_p in the place of w. The first confining action produced by the stirrup legs increases with the splitting crack opening (Eq.3) and this phenomenon is governed by the progressive unsticking of the bar studied in [8]. For the second confining action due to the tensile strength of cracked concrete (Eq.4), a similitude criterion for the relationship between w and the maximum aggregate size ϕ_a was also proposed in [6], so that coefficient κ turned out to be be independent of ϕ_a .

For equilibrium, the global confining action in zone Δz , given by Eqs.3 and 4, is equal to the global radial force produced by the anchored bars, so that: $\sigma = \Omega \sigma + B \sigma$ (5)

$$\sigma_{\rm p} = \Omega \sigma_{\rm st} + B \sigma_{\rm rc}$$

where Ω = stirrup index of confinement, defined as the ratio between global cross section area Ast of the stirrup legs and area Ap of the principal bar in the split plane (Fig.4f), B = concrete index of confinement, defined as the ratio between the net area $(b-n_p\phi_p)\Delta z$ of concrete in the split plane and the afore mentioned area Ap.

From Eqs.2 and 5, bond stress τ as a function of $\sigma_{\text{st}}, \ \sigma_{\text{rc}}$ and w can be obtained:

 $\tau = \tau_0 (1/(1 + K_1 w/\phi_p)) + \tau_1 (\Omega \sigma_{st} + B \sigma_{rc}) (1/(1 + K_2 w/\phi_p))$

Owing to the nonlinear equations involved, the relationship of bond stress τ as a function of slip s is obtained for the principal bar by means of a numerical approach which is based on the following procedure. Attributing a value w to crack opening, Eqs.3 and 4 give σ_{st} and σ_{rc} . Then bond stress τ can be calculated by means of Eq.6 and finally slip s is obtained from Eq.1.

3. RESULTS

In Fig.3 curves τ -s obtained by the present theory fit the experimental results well. Curves 1-4 (Fig.3a) concern the cases examined in [2] with different transverse reinforcement diameters ϕ_{st} . Fig.3b, referring to a specific test studied carefully in [3] to check this theory, shows a very good agreement also for crack opening and stirrup stress. This agreement still emphasizes the importance of the confining contribution due to the residual tensile strength of split concrete.

Theoretical diagrams of Fig.4 show the role of some significant parameters. Curves τ -s, w-s, σ st-s refer to the following governing parameter values:

- Eq.1:	$\tau_{m,0} = 18 \text{ MPa}$	β ₁ = 75	β ₂ = 0	$\gamma_{1} = 42$	$\gamma_2 = 0.8;$
- Eq.2:	$\tau_0 = 1.8 \text{ MPa}$	$\tau_{1} = 0.8$	$k_{1} = 115$	k ₂ = 35;	
- Eq.3:	$\tau_{02}^{}$ = 2.5 MPa	$\tau_{12}\phi_{st} = 5$	00 MPa	$\tau_{12}^{\prime}/\tau_{11}^{\prime} =$	0.3;
- Eq.4:	$f_{c+0} = 3$	l.O MPa		$\kappa = 250;$	

- geometrical and mechanical characteristics: $n = 2 \quad \phi_p = 20 \text{ mm} \quad \alpha = 2 \quad E_s = 206000 \text{ MPa} \quad \Delta z = 100 \text{ mm} \quad \phi_a = 15 \text{ mm} \quad b = 200 \text{ mm}$ Different values of the geometrical or mechanical characteristics adopted for each curve are indicated in Tab.1. Figs.4a,b,c show the role of the transversal extension of the concrete split-area dependent on section width b. Three different amounts of confining reinforcement are adopted and expressed through stirrup index of confinement Ω . Figs.4g,h,i show the influence of fracture energy \Im F obtained by integrating the σ rc-w curve (Eq.4) from w=0 to w=wu. High values of \Im F, correspondent to an appreciable residual strength of cracked concrete, and large values of width b both increase the value of bond stress τ .

Note that fracture energy 9r could be assumed as one of the governing parameters of the present bond stress-slip relationship, but some specifications and remarks are necessary. In reality, the bond stress-slip relationship obtained in [4] showed the importance of the parameters fcto, κ and ϕ_{a} , characterizing the σ_{rc} -w relationship. These results were independent of the ultimate crack opening wu (correspondent to stress-free crack surface). In fact, the maximum value of the splitting crack opening involved was 0.2-0.3mm, which was remarkably less than values wu=0.4-0.7 mm indicated by experiments [6]. Fracture energy \Im F depends on the same governing parameters fcto, κ and ϕ_a , but also on we. This ultimate crack opening seems to be only variable with maximum aggregate size ϕ_a , according to both the similitude criterion introduced in Eq.4 and to some experiments in progress, so that the ratio Wu/ϕ_a could be assumed as a constant for every type of concrete, as well as coefficient κ . In this way \Im and ϕ_a can become the only governing parameters involved in σ_{rc} -w relationship. Diagrams of Fig.4g,h,i refer to an aggregate size $\phi_a=15$ mm (wu/ $\phi_a=0.05$) and three values of \Im r (50,100,150 J/m²) correspondent to low, medium and high residual strength.

4. CONCLUDING REMARKS

The analytical model here proposed for the local bond stress-slip relationship after concrete splitting gives results which have a good agreement with the experimental tests (Figs.3a,b). The theoretical curves considerably depend on the residual tensile strength of cracked concrete especially when light or no transverse reinforcement is present. This residual tensile strength of split concrete is here introduced by means of two governing parameters which are fracture energy \Im F and maximum aggregate size ϕ_a . In the present theory the single parameter \Im F is not sufficient to describe this confining action due to the split concrete.

REFERENCES

- 1. TEPFERS R., Cracking of Concrete Cover along Anchored Deformed Reinforcing Bars. Magazine of Concrete Research, V.31(106), March 1979, pp.3-12.
- 2. ELIGEHAUSEN R., BERTERO V. V., and POPOV E. P., Local Bond Stress-Slip Relationships of Deformed Bars Under Generalized Excitations, Tests and Analytical Model. *Report No.UCB/EERC-83, Earthquake Engineering Research Center*, University of California, Berkeley, 10, 1983.
- GIURIANI E., and PLIZZARI G., Local Bond-Slip Law After Splitting of Concrete (in Italian). Studi e Ricerche, Corso di Perfezionamento per le Costruzioni in Cemento Armato, Politecnico di Milano, Milano, Italy, Vol.7, 1985, pp.57-118.
- 4. GIURIANI E., PLIZZARI G., and SCHUMM, C., Role of Stirrups and Residual Tensile Strength of Cracked Concrete on Bond. ASCE Journal of Structural Division, Vol. 117, No. ST1, January 1991.
- 5. HILLERBORG A., MODÉER M., and PETERSSON P.E., Analysis of Crack Formation and Crack Growth in Concrete by means of Fracture Mechanics and Finite Elements. Cement and Concrete Research, Vol.6, 1976, pp. 773-782.



- 6. GIURIANI E., and ROSATI G. P., An Analytical Model for the Study of the Crack Propagation in Plain Concrete Elements under Bending. Studi e Ricerche, Corso di Perfezionamento per le Costruzioni in Cemento Armato, Politecnico di Milano, Milano, Italy, 9, 1987, pp.107-127.
- GAMBAROVA P. G., ROSATI G. P., and ZASSO, B., Steel-to-Concrete Bond After Concrete Splitting: Test Results. *Materials and Structures*, 22(127), 1989, PP.35-47.
- GIURIANI E., On the effective Axial Stiffness of a Bar in Cracked Concrete. Bond in Concrete. Ed. by P. Bartos, Applied Science Publishers, London, 1982, pp.107-126.





 $\frac{\rm Fig.~4}{\rm after}$ splitting.