**Zeitschrift:** IABSE reports = Rapports AIPC = IVBH Berichte

**Band:** 999 (1997)

**Artikel:** Creep and shear-lag effects in composite beams with flexible

connection

Autor: Dezi, Luigino / Leoni, Graziano / Tarantino, Angelo Marcello

**DOI:** https://doi.org/10.5169/seals-1085

# Nutzungsbedingungen

Die ETH-Bibliothek ist die Anbieterin der digitalisierten Zeitschriften auf E-Periodica. Sie besitzt keine Urheberrechte an den Zeitschriften und ist nicht verantwortlich für deren Inhalte. Die Rechte liegen in der Regel bei den Herausgebern beziehungsweise den externen Rechteinhabern. Das Veröffentlichen von Bildern in Print- und Online-Publikationen sowie auf Social Media-Kanälen oder Webseiten ist nur mit vorheriger Genehmigung der Rechteinhaber erlaubt. Mehr erfahren

# **Conditions d'utilisation**

L'ETH Library est le fournisseur des revues numérisées. Elle ne détient aucun droit d'auteur sur les revues et n'est pas responsable de leur contenu. En règle générale, les droits sont détenus par les éditeurs ou les détenteurs de droits externes. La reproduction d'images dans des publications imprimées ou en ligne ainsi que sur des canaux de médias sociaux ou des sites web n'est autorisée qu'avec l'accord préalable des détenteurs des droits. En savoir plus

### Terms of use

The ETH Library is the provider of the digitised journals. It does not own any copyrights to the journals and is not responsible for their content. The rights usually lie with the publishers or the external rights holders. Publishing images in print and online publications, as well as on social media channels or websites, is only permitted with the prior consent of the rights holders. Find out more

**Download PDF:** 02.12.2025

ETH-Bibliothek Zürich, E-Periodica, https://www.e-periodica.ch

# Creep and Shear-Lag Effects in Composite Beams with Flexible Connection

Luigino DEZI Professor University of Ancona

Ancona, Italy

Graziano LEONI Dr. Eng. University of Ancona Ancona, Italy Angelo Marcello TARANTINO Research Assistant University of Ancona Ancona, Italy

#### 1. Problem statement

In modeling steel-concrete composite beams, two kinematical aspects should be considered: the deformability of the shear connection and the non-uniform distribution of the longitudinal displacements in the slab (shear-lag). The deformability of the shear connection allows a slip at the beam-slab interface, increasing the global flexibility of the structure, while the shear-lag effect implies a non-uniform distribution of stresses in the slab. Furthermore, the behaviour of the composite beam is strongly influenced by the concrete time-dependent effects [1]. Although the effects of creep, connection deformability and shear-lag have been extensively examined in literature, their interaction is not completely known. For this purpose, a general analysis for composite beams has been developed to encompass shear-lag effect, flexible shear connection, creep and shrinkage of the concrete [2]. Starting from the definition of a suitable displacement field which takes into account slipping at beam-slab interface and slab shear deformation, a global balance condition is obtained by means of the virtual work principle. By assuming a linear elastic behaviour for steel beam and shear connection, and a linear viscoelastic behaviour for the concrete slab, the problem is governed by a coupled system of four integral-differential equations. The unknowns of the problem are the functions describing beam deflection, axial displacements of the steel beam and the concrete slab, and intensity (along the beam axis) of the shear-lag effect introduced by means of a suitable shape function for the shear warping of the slab cross section (depending on the point of the cross section only). In particular, the shape function is a quadratic function constant on the slab depth, null at the beamslab interface and satisfying conditions ensuring local equilibrium at the slab free edges. Given the generality of the creep function adopted, a closed form solution cannot be achieved for the system. In order to obtain an accurate numerical solution, the system is solved by introducing two discretizations; one for the time interval, which permits solving the integral-differential problem by a stepby-step procedure considering a set of simpler differential problems, and the other for the beam axis in order to apply the finite differences method.

# 2. Principal results

An extensive numerical parametric analysis, carried out for beams with different geometry and subjected to different restraints and load conditions, has made it possible to obtain some information on the complex time dependent behaviour of composite structures. In particular, the time evolution of the shear-lag and the mutual influence between shear-lag and connection deformability have been studied in detail. For the sake of brevity, only results related to an isolated case (but which can be qualitatively extended to a wide class of composite structure) are reported here.

Fig. 1 shows the numerical results obtained for a two-span continuous beam. The creep analysis was performed with the CEB creep function [3] by considering the following values for concrete strength and relative humidity:  $f_{ck}$ =30MPa and RH=50%. The solution at loading time  $t_0$ =28 days (elastic solution) is compared with the viscoelastic solution ( $t_{\infty}$ =25550 days). Furthermore, results obtained taking into account the shear-lag effect (curves denoted by SL) are compared with those obtained under the classical hypothesis adopted for composite beams with flexible shear connection, namely preservation of plane cross section for the steel beam and the concrete slab considered separately (curves denoted by P). The most important results are summarised in the sequel.

- 1. The beam axis deflections notably increase as a consequence of the time-dependent behaviour of the concrete, while they are less sensitive to the shear-lag effect (Fig. 1a).
- 2. The shear-lag effect, as is well known, strongly modifies the stress distribution in the slab only in the neighbourhood of the intermediate support, by significantly increasing the value which would be obtained by assuming the plane cross section hypothesis for concrete slab and steel beam (Fig. 1b).

- 3. Influence of the shear connection stiffness ( $\rho$ ) on shear-lag is shown in Fig. 1c, where the elastic values of the stresses  $\sigma_{SL}$  and  $\sigma_{P}$  at the intermediate support cross section are compared. Increasing  $\rho$ , shear-lag stress  $\sigma_{SL}$  increases more than  $\sigma_{P}$  as shown by the dashed curve related to the ratio  $\sigma_{SL}/\sigma_{P}$ . The coupling between the shear-lag effect and the shear connection stiffness is thus evident.
- 4. Fig. 1d shows the influence of creep on the shear-lag effect. The time evolution of the ratio between Δσ and σ<sub>SL</sub>(see Fig.1b) is reported for three different values of the shear connection stiffness. Such a ratio permits defining the slab effective width b<sub>eff</sub> (adopted by the principal technical codes, e.g. ENV 1994-2) as

$$b_{eff} = \frac{1}{\sigma_{SL}} \int_{-b/2}^{b/2} \sigma_c dx = b - \frac{\Delta \sigma}{\sigma_{SL}} \int_{-b/2}^{b/2} f(x) dx$$

where b is the real value of the slab width and f(x) is a function depending on the cross section only. It is evident that such a ratio, even if it depends on the  $\rho$  value, remains almost constant in time showing a substantial uncoupling between creep and shear-lag effect.




Fig. 1. (a) Influence of shear-lag and concrete creep on the beam deflections. (b) Concrete creep effect on the slab stress distribution. (c) Influence of the shear connection stiffness on the shear-lag effect. (d) Influence of the concrete creep on the shear-lag effect.

# 3. References

- 1 Dezi, L., and Tarantino, A.M. (1993), "Creep in composite continuous beams. I: Theoretical treatment." J. Struct. Engrg. ASCE, 119(7), 2095-2111.
- 2 Dezi, L., Leoni, L., and Tarantino, A.M. (1997), "Time dependent analysis of shear-lag effect in composite beams." (Submitted for the publication on J. Struct. Engrg. ASCE).
- 3 "CEB FIP model code 1990." (1988). C.E.B. Bullettin d'information n. 190, C.E.B. F.I.P. Comité Euro-International du Beton, Paris, France.