

Zeitschrift: IABSE reports = Rapports AIPC = IVBH Berichte
Band: 77 (1998)

Artikel: Long-term stability of joint repairs in building construction
Autor: Bolte, Hartmut / Boettger, Till
DOI: <https://doi.org/10.5169/seals-58219>

Nutzungsbedingungen

Die ETH-Bibliothek ist die Anbieterin der digitalisierten Zeitschriften auf E-Periodica. Sie besitzt keine Urheberrechte an den Zeitschriften und ist nicht verantwortlich für deren Inhalte. Die Rechte liegen in der Regel bei den Herausgebern beziehungsweise den externen Rechteinhabern. Das Veröffentlichen von Bildern in Print- und Online-Publikationen sowie auf Social Media-Kanälen oder Webseiten ist nur mit vorheriger Genehmigung der Rechteinhaber erlaubt. [Mehr erfahren](#)

Conditions d'utilisation

L'ETH Library est le fournisseur des revues numérisées. Elle ne détient aucun droit d'auteur sur les revues et n'est pas responsable de leur contenu. En règle générale, les droits sont détenus par les éditeurs ou les détenteurs de droits externes. La reproduction d'images dans des publications imprimées ou en ligne ainsi que sur des canaux de médias sociaux ou des sites web n'est autorisée qu'avec l'accord préalable des détenteurs des droits. [En savoir plus](#)

Terms of use

The ETH Library is the provider of the digitised journals. It does not own any copyrights to the journals and is not responsible for their content. The rights usually lie with the publishers or the external rights holders. Publishing images in print and online publications, as well as on social media channels or websites, is only permitted with the prior consent of the rights holders. [Find out more](#)

Download PDF: 05.09.2025

ETH-Bibliothek Zürich, E-Periodica, <https://www.e-periodica.ch>




Long-Term Stability of Joint Repairs in Building Construction

Hartmut BOLTE

Dr.-Ing.
University of Leipzig
Leipzig, Germany



Hartmut Bolte, born 1939, received his PhD in 1990. He is currently project leader in the durability of building materials group.



Till BOETTGER

Dr.
University of Leipzig
Leipzig, Germany

Till Boettger, born 1942, received his PhD in 1972. He is currently project leader in the durability of building materials group.

Summary

Trial results with elastomer jointing strips based on polysulphide and silicone rubber are evaluated from the aspect of long-term stability. The authors have based themselves on the applications maintained since 1974. A report is given on the following results:

- Trial on structure
- Seal against driving rain
- Extension-compression strain
- Adhesion on concrete
- Tensile strength and elongation at break

The verified long-term-stability up to now is 23 years for the best joint solution investigated. So as to be able to determine the probable long-term stability, work is taking place on a test method.

1. Introduction

It is preferable to renovate the joint seals on external walls with elastomer jointing strips. At this point, a few results should be updated from the point of view of long-term durability.

2. On-site testing

Testing on a construction site is the most practical form of ageing test. Site trials provide proven values for long-term durability, but the maximum values actually achievable could be slightly or considerably higher than these and an accurate estimate is rather difficult to make. We present two selected applications of silicone and polysulphide jointing strips which have been dealt with by the writers since 1974 respectively 1979.

3. Test evidence

It was investigated six polysulphide rubbers PS I-VI, one silicone rubber SI and three primers P I-III.

- Watertightness to driving rain

The test was carried out in a special rain chamber (see Fig. 1).

- Extension and compression strain

The exercise was carried out on a special extension/compression test machine, the clamping part of which can be positioned in a temperature-controlled chamber (Fig. 2).

- Adhesion to concrete

It can be concluded from the compression shear tests that the adhesion of jointing strips to concrete will not fail in the long term if it proved to be up to the mark in the first few years.

- Tensile strength and elongation at break

When exposed to the open-air, the values of the tensile strength only drop slightly or even increase a little.

The prediction period is an unknown quantity. As the elongation at break reduces continuously, it is suitable for predicting the long-term durability of jointing strips. We decided on a probable useful working life of 20 to 35 years for elastomer jointing strips.




Fig. 1 Evaluation of the watertightness to driving rain in the rain chamber

4. Conclusion

The long-term durability of the elastomer jointing strips tested turned out to be very high. In order to be able to assess this property in the case of the addition of colouring agents and other formula changes, or even completely new formulae, new rapid tests are necessary. The authors are working on the general problem of the artificial ageing of elastomeric building sealants. However we shall not be reporting on this at this stage, but at the CIB World Building Congress which takes place in Gävle (Sweden) from 7 to 12 June 1998.



Fig. 2 Extension/compression test machine