

**Zeitschrift:** IABSE reports = Rapports AIPC = IVBH Berichte  
**Band:** 77 (1998)

**Artikel:** Rain screen cladding based on steel structures - thermal and moisture physical behaviour of repaired wall structure  
**Autor:** Lehtinen, Teppo / Yrjölää, Reijo / Kettunen, Ari-Veikko  
**DOI:** <https://doi.org/10.5169/seals-58268>

#### **Nutzungsbedingungen**

Die ETH-Bibliothek ist die Anbieterin der digitalisierten Zeitschriften auf E-Periodica. Sie besitzt keine Urheberrechte an den Zeitschriften und ist nicht verantwortlich für deren Inhalte. Die Rechte liegen in der Regel bei den Herausgebern beziehungsweise den externen Rechteinhabern. Das Veröffentlichen von Bildern in Print- und Online-Publikationen sowie auf Social Media-Kanälen oder Webseiten ist nur mit vorheriger Genehmigung der Rechteinhaber erlaubt. [Mehr erfahren](#)

#### **Conditions d'utilisation**

L'ETH Library est le fournisseur des revues numérisées. Elle ne détient aucun droit d'auteur sur les revues et n'est pas responsable de leur contenu. En règle générale, les droits sont détenus par les éditeurs ou les détenteurs de droits externes. La reproduction d'images dans des publications imprimées ou en ligne ainsi que sur des canaux de médias sociaux ou des sites web n'est autorisée qu'avec l'accord préalable des détenteurs des droits. [En savoir plus](#)

#### **Terms of use**

The ETH Library is the provider of the digitised journals. It does not own any copyrights to the journals and is not responsible for their content. The rights usually lie with the publishers or the external rights holders. Publishing images in print and online publications, as well as on social media channels or websites, is only permitted with the prior consent of the rights holders. [Find out more](#)

**Download PDF:** 06.02.2026

**ETH-Bibliothek Zürich, E-Periodica, <https://www.e-periodica.ch>**



## Rain Screen Cladding Based on Steel Structures - Thermal and Moisture Physical Behavior of Repaired Wall Structure

**Teppo LEHTINEN**

Senior Research Scientist  
Helsinki University of Technology  
Espoo, Finland

**Reijo YRJÖLÄÄ**

Research Scientist  
Helsinki University of Technology  
Espoo, Finland

**Ari-Veikko KETTUNEN**

Senior Research Scientist  
Helsinki University of Technology  
Espoo, Finland

**Martti KARIMIES**

Project Manager  
Rautaruukki Ltd.  
Helsinki, Finland

### Summary

The thermal and physical behaviour of a rain screen cladding system with a steel structure was studied with field measurements in a block of flats, whose lightweight aerated concrete facades were repaired with the system. The building was located in central Finland. The results of the field measurements and numerical calculations show that with the system an old external wall structure can be dried out to a level at which further deterioration due to reinforcement corrosion is low under northern European climate conditions. The new, external thermal insulation layer also raised the temperatures of the old wall structure so that further deterioration due to frost is unlikely.

**Keywords:** Thermal and moisture physical behaviour of external walls, facade repair methods

### 1. Field measurements and numerical analysis of facade repair

In the field measurements the thermal and moisture physical behaviour of the rain screen cladding system was studied for example with temperature and relative humidity sensors placed in the wall structure. The time step in the continuous measurements was 30 minutes. The measurements began in January 1995 approximately one year before the actual repair and have now continued for 2.5 years. The objective of the field measurements was to find out how the cladding system, with its additional external thermal insulation layer and ventilated air gap, improves the thermal and moisture physical behaviour of the external wall structures.

The unrepaired and repaired external wall sections are shown in figure 1. The field measurements include continuous measurements of temperature and air relative humidity of the air, moisture content measurements of samples and local effective heat transfer coefficient measurements with heat flow meters.

In addition to the continuous measurements, the U-value of the unrepaired wall section was measured with heat flow meters combined with room temperature regulation. The moisture content of the lightweight aerated concrete of the old wall structure was measured by taking samples before and after the repair.

The magnitude of the apparent thermal resistance was estimated with transient numerical calculations using the measured outdoor temperature and the temperatures between the inner, load bearing concrete layer and the lightweight aerated concrete layer as boundary conditions. The apparent thermal resistance was defined using iterative calculations. The calculations were made using temperatures in January 1996 and 1997 since the effect of solar heat radiation is lower than at other times of the year.




Figure 1. The unrepaired (a) and repaired (b) test wall sections and the locations of the temperature and air relative humidity sensors in wall sections.

## 2. Thermal and moisture physical behaviour of repaired facade

The initial moisture content before the repair of the tested facade was, at its highest,  $26 \text{ kg} \cdot \text{m}^{-2}$ . The old wall structure started to dry out once the daily mean temperature of the ventilated air gap rose above  $0^\circ\text{C}$ . After one year, the additional moisture had dried out and the moisture content of the old lightweight concrete layer corresponded to material exposed to normal climate conditions. The corresponding relative humidities were 40-60 RH%, which indicates that further deterioration due to reinforcement corrosion would be very slow.

The exterior mineral wool thermal insulation layer raised the temperature of the old facade so that the temperature of the lightweight aerated concrete dropped below  $0^\circ\text{C}$  for only a few days on the first floor when the outdoor temperature was around  $-20^\circ\text{C}$ . This indicates that further deterioration of the old facade due to frost is unlikely.

The measured apparent U-values of the facade before repair were  $0.42\text{--}0.46 \text{ W} \cdot \text{m}^{-2} \cdot \text{K}^{-1}$ . These values were lower neighbouring values since the mean moisture content was lower, 5.3 w-%, than in the case of facades exposed to a greater amount of driving rain, the highest measured mean moisture content was 17 w-%. One year after the repair the apparent U-value was estimated to be at a level of  $0.18 \text{ W} \cdot \text{m}^{-2} \cdot \text{K}^{-1}$  according to numerical simulations. Taking the simulations into account, the thermal conductivity of the lightweight aerated concrete layer improved from a level of  $0.18 \text{ W} \cdot \text{m}^{-1} \cdot \text{K}^{-1}$  to  $0.14 \text{ W} \cdot \text{m}^{-1} \cdot \text{K}^{-1}$  due to the drying of the layer. In the numerical simulation the effective thermal resistance of the ventilated air gap was also studied. The effective thermal resistance was found out to be at a level of  $0.5 \text{ m}^{-2} \cdot \text{K}^{-1} \cdot \text{W}^{-1}$ . This effective thermal resistance is taken into account in the apparent U-value shown above.

The results support the use of the tested type facade repair method as a means of saving energy. In addition, when the structures are carefully designed and the cladding is properly installed, the old external wall structure dries out to a level that considerably extends the service life of the external wall structure.