

Zeitschrift: IABSE reports = Rapports AIPC = IVBH Berichte
Band: 77 (1998)

Artikel: Mechanical properties and bond behaviour of corroded deformed bars
Autor: García, Dolores / Gutiérrez, José Pedro / Rodríguez, Jesús
DOI: <https://doi.org/10.5169/seals-58182>

Nutzungsbedingungen

Die ETH-Bibliothek ist die Anbieterin der digitalisierten Zeitschriften auf E-Periodica. Sie besitzt keine Urheberrechte an den Zeitschriften und ist nicht verantwortlich für deren Inhalte. Die Rechte liegen in der Regel bei den Herausgebern beziehungsweise den externen Rechteinhabern. Das Veröffentlichen von Bildern in Print- und Online-Publikationen sowie auf Social Media-Kanälen oder Webseiten ist nur mit vorheriger Genehmigung der Rechteinhaber erlaubt. [Mehr erfahren](#)

Conditions d'utilisation

L'ETH Library est le fournisseur des revues numérisées. Elle ne détient aucun droit d'auteur sur les revues et n'est pas responsable de leur contenu. En règle générale, les droits sont détenus par les éditeurs ou les détenteurs de droits externes. La reproduction d'images dans des publications imprimées ou en ligne ainsi que sur des canaux de médias sociaux ou des sites web n'est autorisée qu'avec l'accord préalable des détenteurs des droits. [En savoir plus](#)

Terms of use

The ETH Library is the provider of the digitised journals. It does not own any copyrights to the journals and is not responsible for their content. The rights usually lie with the publishers or the external rights holders. Publishing images in print and online publications, as well as on social media channels or websites, is only permitted with the prior consent of the rights holders. [Find out more](#)

Download PDF: 01.04.2026

ETH-Bibliothek Zürich, E-Periodica, <https://www.e-periodica.ch>



Mechanical Properties and Bond Behaviour of Corroded Deformed Bars

Dolores GARCÍA

Dr Architect
Inst. of Constr. Science
Madrid, Spain

José Pedro GUTIÉRREZ

Dr Engineer
Inst. of Constr. Science
Madrid, Spain

Jesús RODRÍGUEZ

Dr Engineer
GEOCISA
Madrid, Spain

Summary

An experimental investigation of the effect of corrosion on the mechanical properties and bond behavior of deformed reinforcing bars is presented. Tensile tests on corroded rebars through an accelerated process and bond tests on concrete specimens reinforced in all four corners were carried out. Results indicate that corrosion affects ductility of steel, decreasing bar elongation at maximum load. Too corrosion affects steel-to-concrete bond, but the presence of stirrups improves significantly bond behavior of corroded reinforcing bars.

1. Experimental Program

Fresh and corroded deformed bars with diameters of 12 and 20 mm respectively were tested in tension to determine yield strength, tensile strength and elongation at maximum load. For corroding the samples, a direct current of a $1\text{mA}/\text{cm}^2$ density was impressed on the rebars immersed in 3% weight of NaCl solution or fresh water. These media reproduce, to a certain, the aggressive environment of a completely carbonated concrete and a chloride-contaminated concrete respectively. Several levels of corrosion were examined: no corrosion, corrosion associated to cross section losses from 7% to 20% and corrosion associated to cross section losses higher than 25%.

Pullout bond tests were carried out on $300 \times 350 \times 350$ mm concrete specimens with 20 mm diameter bars arranged in the four corners. A cover to diameter ratio of 1.5 was examined and the embedded length was 14ϕ in all cases. The test method used simulates anchorage conditions in a part of a beam submitted to constant shear force, and allows to reproduce the most usual bond failure on reinforced concrete structures: splitting failure in the concrete cover (Fig. 1). For corroding the rebars the concrete in which they were embedded was contaminated with 3% calcium chloride by weight of cement and later a direct current of a $0.1\text{mA}/\text{cm}^2$ density was impressed on each bar embedded in the pullout specimens. Several corrosion levels were reached producing crack widths ranging from 0.1 mm to 0.4 mm and cross section loss up to 5%. Various amounts of transverse reinforcement were also arranged: no stirrups, $\phi 6$ mm stirrups at 200 mm and $\phi 8$ mm stirrups at 10 mm.





Fig 1. Bond test arrangement

2. Results and Discussion

The results of tensile tests hint yield stress and tensile stress do not decrease for cross section losses lower than 20%, corrosion range that includes the majority of actual cases of generalized corrosion. On the other hand, a systematic and important reduction of elongation at maximum load was observed both for rebars corroded in water with chlorides and those damaged in fresh water (Fig. 2). The results indicate reductions of elongation at maximum load of about 20% for cross section losses of 10%. When corrosion level achieves values about of 25%-30%, elongation at maximum load decreases 40% approximately.

Pullout bond tests allowed to study the influence of bar cast position (top or bottom) and amount of transverse reinforcement on the bond strength of corroded rebars. As for the influence of the bar position, in noncorroded specimens the average values of bond strength for top bars were about 15%-20% lower than for bottom ones. Nevertheless, in corroded specimens a net difference between bond strength values of bottom and top bars was not observed, with the same specimen shape and corrosion level.

As for the influence of the amount of transverse reinforcement, the tests of specimens with no stirrups confirmed bond strength is significantly reduced when corrosion takes place. On the other



hand, the presence of stirrups improves considerably bond behavior of rebars damaged by corrosion. Thus, the presence of transverse reinforcement allows to count on residual bond strength at least equal to 1,6 Mpa, even for small amounts of stirrups.

Fig 2. Relationship between elongation at maximum load and corrosion level