

**Zeitschrift:** IABSE reports = Rapports AIPC = IVBH Berichte  
**Band:** 79 (1998)

**Artikel:** Suitability of recycled aggregate concrete in high-rise construction  
**Autor:** Prakash, K.B. / Krishnaswamy, K.T.  
**DOI:** <https://doi.org/10.5169/seals-59987>

#### Nutzungsbedingungen

Die ETH-Bibliothek ist die Anbieterin der digitalisierten Zeitschriften auf E-Periodica. Sie besitzt keine Urheberrechte an den Zeitschriften und ist nicht verantwortlich für deren Inhalte. Die Rechte liegen in der Regel bei den Herausgebern beziehungsweise den externen Rechteinhabern. Das Veröffentlichen von Bildern in Print- und Online-Publikationen sowie auf Social Media-Kanälen oder Webseiten ist nur mit vorheriger Genehmigung der Rechteinhaber erlaubt. [Mehr erfahren](#)

#### Conditions d'utilisation

L'ETH Library est le fournisseur des revues numérisées. Elle ne détient aucun droit d'auteur sur les revues et n'est pas responsable de leur contenu. En règle générale, les droits sont détenus par les éditeurs ou les détenteurs de droits externes. La reproduction d'images dans des publications imprimées ou en ligne ainsi que sur des canaux de médias sociaux ou des sites web n'est autorisée qu'avec l'accord préalable des détenteurs des droits. [En savoir plus](#)

#### Terms of use

The ETH Library is the provider of the digitised journals. It does not own any copyrights to the journals and is not responsible for their content. The rights usually lie with the publishers or the external rights holders. Publishing images in print and online publications, as well as on social media channels or websites, is only permitted with the prior consent of the rights holders. [Find out more](#)

**Download PDF:** 26.07.2025

**ETH-Bibliothek Zürich, E-Periodica, <https://www.e-periodica.ch>**

## Suitability of Recycled Aggregate Concrete in High-Rise Construction

**K.B. PRAKASH**

Assist. Prof.

T.K. Inst. of Eng & Technology  
Warananagar, India

**K.T. KRISHNASWAMY**

Head of Dept, Applied Mech.  
Walchand College of Eng.  
Sangli, India

### Summary

This paper presents the results of an experimental investigation carried out on the suitability of recycled aggregate concrete for the construction of high rise structures. The strength and workability of conventional natural aggregate concrete obtained from high grade cements (43 grade & 53 grade) is compared with recycled aggregate concrete obtained from high grade cements. Also, it is shown that, the shortcomings of recycled aggregate concrete in strength and workability can be overcome by the use of superplasticizers.

### 1. Experimental Work

In this experimental programme the strength parameters and workability of three different concretes (with different w/c ratios to cater the needs of workability) were compared. Viz -

- a. concrete with conventional natural aggregates (w/c = 0.45)
- b. concrete with recycled aggregates (w/c = 0.55)
- c. concrete with recycled aggregates and known dosage of superplasticizers (w/c = 0.45)

The tests were conducted on a mix of proportion 1:2:4. Zentrament Super BV superplasticizer (lignosulphonate based) was used with a dosage of 0.7%.

### 2. Experimental Results

Table 1 gives the strength parameters (compressive strength, tensile strength and flexural strength) of different categories of concretes produced from 43 grade & 53 grade cements.

Table 2 gives the workability of different categories of concretes produced from 43 grade & 53 grade cements. The workability of 43 grade & 53 grade concretes are almost same.



Table - 1 Results of strength parameters.

Particulars of concrete	Conventional natural aggregate concrete produced from		Recycled aggregate concrete produced from		Recycled aggregate concrete with superplasticizer produced from	
	43 grade	53 grade	43 grade	53 grade	43 grade	53 grade
Comp. strength (MPa)						
7 days	16.92	19.93	12.00	13.64	22.71	24.00
28 days	18.92	22.66	16.44	18.66	24.79	32.88
2 months	29.77	35.50	28.53	32.44	32.08	36.79
Tensile strength (MPa)						
7 days	1.95	3.27	1.79	2.19	2.40	3.96
28 days	2.70	3.82	2.06	3.13	3.97	4.52
2 months	4.38	4.78	4.07	3.90	5.45	5.27
Flexural strength (MPa)						
7 days	4.64	5.36	2.96	3.76	5.04	5.96
28 days	5.40	5.80	5.04	4.04	7.00	7.44
2 months	5.84	8.52	5.24	7.36	8.92	9.36

Table 2 - Results of Workability

Particulars of Concrete	w/c ratio	Slump (mm)	C.F.	V.B. Degree (sec)	% Flow
Conventional natural aggregate concrete	0.45	0	0.87	20	4
	0.60	10	0.90	12	13
	0.70	15	0.92	6	20
	0.80	20	0.94	4	60
	0.90	Collapse	0.97	2	80
Recycled aggregate concrete	0.45	0	0.84	25	2
	0.60	0	0.86	14	9
	0.70	12	0.90	8	15
	0.80	18	0.92	7	52
	0.90	Collapse	0.95	3	71
Recycled aggregate concrete with superplasticizer	0.45	0	0.89	18	5
	0.60	8	0.93	10	14
	0.70	14	0.94	5	21
	0.80	Collapse	0.96	4	60
	0.90	Collapse	0.98	2	80

### 3. Conclusions

The following conclusions can be drawn -

- The compressive strength, tensile strength and flexural strength of conventional natural aggregate concrete is more than that of recycled aggregate concrete. But the strength of recycled aggregate concrete with superplasticizer show a distinct rise in the strength compared to the conventional natural aggregate concrete. Thus the offset in the strength properties of recycled aggregate concrete can be overcome by using a right dosage of superplasticizer.
- The strength properties are distinctly greater for concrete produced from 53 grade cement as compared to concrete produced from 43 grade cement.
- The workability is distinctly more for recycled aggregate concrete with superplasticizer.
- Hence recycled aggregate concrete can be effectively used in the construction of high rise buildings, especially near the vicinity where recycled aggregates are available in plenty.