

**Zeitschrift:** IABSE reports = Rapports AIPC = IVBH Berichte  
**Band:** 79 (1998)

**Artikel:** Long term performance of anti-corrosion method using titanium clad steel  
**Autor:** Nakamura, Shunichi / Homma, Koji  
**DOI:** <https://doi.org/10.5169/seals-59869>

#### **Nutzungsbedingungen**

Die ETH-Bibliothek ist die Anbieterin der digitalisierten Zeitschriften auf E-Periodica. Sie besitzt keine Urheberrechte an den Zeitschriften und ist nicht verantwortlich für deren Inhalte. Die Rechte liegen in der Regel bei den Herausgebern beziehungsweise den externen Rechteinhabern. Das Veröffentlichen von Bildern in Print- und Online-Publikationen sowie auf Social Media-Kanälen oder Webseiten ist nur mit vorheriger Genehmigung der Rechteinhaber erlaubt. [Mehr erfahren](#)

#### **Conditions d'utilisation**

L'ETH Library est le fournisseur des revues numérisées. Elle ne détient aucun droit d'auteur sur les revues et n'est pas responsable de leur contenu. En règle générale, les droits sont détenus par les éditeurs ou les détenteurs de droits externes. La reproduction d'images dans des publications imprimées ou en ligne ainsi que sur des canaux de médias sociaux ou des sites web n'est autorisée qu'avec l'accord préalable des détenteurs des droits. [En savoir plus](#)

#### **Terms of use**

The ETH Library is the provider of the digitised journals. It does not own any copyrights to the journals and is not responsible for their content. The rights usually lie with the publishers or the external rights holders. Publishing images in print and online publications, as well as on social media channels or websites, is only permitted with the prior consent of the rights holders. [Find out more](#)

**Download PDF:** 07.02.2026

**ETH-Bibliothek Zürich, E-Periodica, <https://www.e-periodica.ch>**

## Long Term Performance of Anti-Corrosion Method Using Titanium Clad Steel

**Shunichi NAKAMURA**

Dr Eng.

Tokai Univ.

Hiratuka, Japan

**Koji HOMMA**

Dr Eng.

Nippon Steel Corp., Steel Struct. Dev. Center

Futtsu, Chiba, Japan

### Summary

A new anti-corrosion method using titanium clad steel plates has been developed and applied to the splash and tidal zones of steel piers. Titanium clad steel plates consist of 1 mm thick titanium plates and 4 mm thick steel plates and are welded to the steel piers. Steel pipes with diameter of 60cm using this anti-corrosion method have been tested and monitored in the actual marine environment for the last five years. The monitoring results show that no corrosion has been found on the titanium clad plates and prove that the new method has sufficient long term durability.

### 1. Structural forms of the new anti-corrosion method

It has been thought that titanium has excellent anti-corrosion resistance, but it is too expensive to be used for the actual structure. However, we have developed relatively inexpensive titanium clad steel plates, invented a new anti-corrosion method for the splash and tidal zones of steel piers using this material. Titanium clad steel plates consist of 1mm thick titanium plates and 4mm thick steel plates and are welded to the surface of steel piers by TIG welding. Various experiments have been carried out to investigate basic strength and behaviors of this new method, such as mechanical strength of clad plates, electro-chemical effects of electrolytic corrosion, weldability and paintability on clad plates. These tests have all shown satisfactory results. This new method has also shown economical competitiveness compared with other anti-corrosion methods for the severe marine environment, and has therefore been adopted for the steel piers on the Trans-Tokyo Bay Bridge(see fig.1, fig.2 and fig.3), one of the national projects in Japan. We have watched these actual steel piers since they were constructed three years ago, and at the same time we put the test pipes, on which this new anti-corrosion method were applied, into the sea water and monitored for the last five years to investigate the long term durability of this new system.

### 2. A test on long term durability of the new method

Steel pipes with diameter of 60 cm using this anti-corrosion method have been tested in the actual marine environment for the last five years (see fig.4). The behavior of these prototype specimens have been monitored by observing the thickness change, the electrolytic potential, the electric current from a sacrificial aluminum anode and the surface condition. The steel pipe specimens are covered with the titanium clad steel plates between 1 m above high water level and 1 m below low water level (The length is 4 m). Other than the titanium clad part, the steel pipes in the atmosphere are protected by a heavy duty coating system using fluorocarbon resin and the steel pipes in the sea water are protected by cathodic protection using aluminum anodes.




Fig. 1 Trans-Tokyo Bay Bridge




Fig. 2 Steel pier of Trans-Tokyo Bay Bridge




Fig. 3 Close-up of the titanium clad part

Fig.5 shows the cross section of titanium clad part after the exposure period. No thickness reduction was observed not only in the titanium clad steel plates, but also in the steel pile adjacent to the titanium clad steel plates(see fig.6). The countermeasures against electrolytic corrosion were the heavy duty coating in the upper boundary in the atmosphere and the cathodic protection using an aluminum anode in the lower boundary in the sea water. Fig.7 shows the change of electric current from an aluminum anode. It was observed that the electric current was settled and the cathodic protection of steel pipe with titanium clad worked successfully.



Fig. 4 Exposure test of specimens (when lifted)




Fig.5 Cross section of specimen




Fig.6 Change of thickness during 5 years




Fig.7 Change of current from a sacrificial aluminum anode

The monitoring results show that the titanium clad steel is perfectly healthy, and electrolytic corrosion does not occur in both upper and lower boundary areas between the steel pipe and the titanium clad part. Therefore, it was confirmed that the titanium clad showed an excellent anti-corrosion property and that the countermeasures against electrolytic corrosion were effective through the actual exposure test.