

Zeitschrift: IABSE reports = Rapports AIPC = IVBH Berichte
Band: 83 (1999)

Artikel: On the free vibration of honeycomb sandwich plates
Autor: Attaf, Brahim
DOI: <https://doi.org/10.5169/seals-62945>

Nutzungsbedingungen

Die ETH-Bibliothek ist die Anbieterin der digitalisierten Zeitschriften auf E-Periodica. Sie besitzt keine Urheberrechte an den Zeitschriften und ist nicht verantwortlich für deren Inhalte. Die Rechte liegen in der Regel bei den Herausgebern beziehungsweise den externen Rechteinhabern. Das Veröffentlichen von Bildern in Print- und Online-Publikationen sowie auf Social Media-Kanälen oder Webseiten ist nur mit vorheriger Genehmigung der Rechteinhaber erlaubt. [Mehr erfahren](#)

Conditions d'utilisation

L'ETH Library est le fournisseur des revues numérisées. Elle ne détient aucun droit d'auteur sur les revues et n'est pas responsable de leur contenu. En règle générale, les droits sont détenus par les éditeurs ou les détenteurs de droits externes. La reproduction d'images dans des publications imprimées ou en ligne ainsi que sur des canaux de médias sociaux ou des sites web n'est autorisée qu'avec l'accord préalable des détenteurs des droits. [En savoir plus](#)

Terms of use

The ETH Library is the provider of the digitised journals. It does not own any copyrights to the journals and is not responsible for their content. The rights usually lie with the publishers or the external rights holders. Publishing images in print and online publications, as well as on social media channels or websites, is only permitted with the prior consent of the rights holders. [Find out more](#)

Download PDF: 09.12.2025

ETH-Bibliothek Zürich, E-Periodica, <https://www.e-periodica.ch>



On the Free Vibration of Honeycomb Sandwich Plates

Brahim ATTAF
Associate Professor
University of Blida
Blida, Algeria



Brahim Attaf, born 1959, received in 1990 his civil engineering PhD degree from the Univ. of Surrey, UK. Since then, he joined the Univ. of Blida, Algeria, where he is investigating the vibration, stability and delamination of composite plates and sandwich panels.

Summary

The aim of this paper is to improve the dynamic effects of geometric design variables on a honeycomb sandwich plate. The variables of the honeycomb core were radius and thickness of the hexagonal cell while the mass of the honeycomb sandwich plate was kept constant. In addition, an attempt has been made to investigate the effect of material alteration relative to the upper and lower facings.

Keywords: Free vibration; sandwich plate; laminated facings; honeycomb core dimensions; finite element analysis.

1. Introduction

The increase or decrease in the natural frequency will depend on several design variables. Besides the material properties, the designer must consider the ratio r/L (honeycomb cell radius/plate length) and the ratio H/e (core thickness/facing thickness). All of these design variables will affect the sandwich plate natural frequencies. It is, therefore, required to undertake parameter studies which provide the means of selection and design of lightweight sandwich plates. However, difficulties inherent to transverse shear deformation, anisotropy of material and boundary conditions constitute a complex and tedious analysis and this make the solution of the equation system impossible. Finite element technique was, therefore, suggested to overcome these difficulties.

2. Numerical results and discussion

2.1 Vibration modes of homogeneous and sandwich plates

Two plate constructions having the same material (aluminium), same mass and same boundary conditions (fully clamped) were investigated. The former plate construction was thin and homogeneous; whereas the latter construction was a honeycomb sandwich plate. It was noted that the natural frequencies of a sandwich plate are greater than those of a homogeneous one. This gain in frequency is directly related to H , which rise the natural frequencies of the sandwich plate without materially increasing its mass. The first four mode shapes for both plates were seen to be identical.

2.2 Influence of honeycomb cell radius on the sandwich plate natural frequencies

According to Fig. 1, it can be noted that the frequency ratio Δ_i ($i=1,2,3,4$) decreases in hyperbolic form. Seen that Δ_i is high for small values of r/L ; it is, therefore, recommended to choose the smallest practical value of r/L .

2.3 Effect of core thickness on the sandwich plate natural frequencies

According to Fig. 2, the ratio Δ_i increases with H/e in logarithmic form. For small values of H/e (less than 25), the natural frequencies converge to the same value. Whereas, for high values of H/e , the condition of divergence is clearly observed.




Fig.1 Frequency ratio Δ_i versus hexagonal cell ratio r/L for aluminium honeycomb plate. Frequency mode: (—) 1st; (—) 2nd; (---) 3rd; (-----) 4th.

Fig.2 Frequency ratio Δ_i versus sandwich thickness ratio H/e for all aluminium sandwich plate. Frequency mode: as Fig.1.

2.4 Effect of facing material on the sandwich plate natural frequencies

A honeycombed sandwich plate with laminated composite facings was fully investigated. The source for increasing frequency and reducing vibration amplitude levels without introducing weight penalty is believed to be related to the fibre reinforcements which must be tailored in the plane where they will be most effective.

3. Conclusion

The present analysis reinforces the fact that vibration behaviour of complex systems must not be dependent upon one analysis procedure only. Comprehensive modelling of a finite element solution from an experimental procedure should be undertaken before parameter studies are made.