

**Zeitschrift:** IABSE reports = Rapports AIPC = IVBH Berichte  
**Band:** 83 (1999)  
  
**Artikel:** Performance of concrete structures in Argentine environments  
**Autor:** Traversa, Luis P. / Giovambattista, Alberto / Di Maio, Angel A.  
**DOI:** <https://doi.org/10.5169/seals-62833>

### **Nutzungsbedingungen**

Die ETH-Bibliothek ist die Anbieterin der digitalisierten Zeitschriften auf E-Periodica. Sie besitzt keine Urheberrechte an den Zeitschriften und ist nicht verantwortlich für deren Inhalte. Die Rechte liegen in der Regel bei den Herausgebern beziehungsweise den externen Rechteinhabern. Das Veröffentlichen von Bildern in Print- und Online-Publikationen sowie auf Social Media-Kanälen oder Webseiten ist nur mit vorheriger Genehmigung der Rechteinhaber erlaubt. [Mehr erfahren](#)

### **Conditions d'utilisation**

L'ETH Library est le fournisseur des revues numérisées. Elle ne détient aucun droit d'auteur sur les revues et n'est pas responsable de leur contenu. En règle générale, les droits sont détenus par les éditeurs ou les détenteurs de droits externes. La reproduction d'images dans des publications imprimées ou en ligne ainsi que sur des canaux de médias sociaux ou des sites web n'est autorisée qu'avec l'accord préalable des détenteurs des droits. [En savoir plus](#)

### **Terms of use**

The ETH Library is the provider of the digitised journals. It does not own any copyrights to the journals and is not responsible for their content. The rights usually lie with the publishers or the external rights holders. Publishing images in print and online publications, as well as on social media channels or websites, is only permitted with the prior consent of the rights holders. [Find out more](#)

**Download PDF:** 09.12.2025

**ETH-Bibliothek Zürich, E-Periodica, <https://www.e-periodica.ch>**



## **Performance of Concrete Structures in Argentine Environments**

**Luis P. TRAVERSA**

Civil Engineer  
CIC-LEMIT  
La Plata, Argentina

**Alberto GIOVAMBATTISTA**

Civil Engineer  
University of La Plata  
La Plata, Argentina

**Angel A. DI MAIO**

Mechanical Engineer  
CIC-LEMIT  
La Plata, Argentina

**Lilian N. EPERJESI**

Construction Engineer  
University of La Plata  
La Plata, Argentina

### **Introduction**

Reinforced concrete performance throughout its useful life is related to the intrinsic characteristics of its component materials, their interrelationship and the nature and aggressive characteristics of the surrounding environment.

Theoretical knowledge about the causes and mechanisms of portland cement concrete failure, as well as of the techniques to minimise or eliminate their consequences, is available. Laboratory experiments and concrete performance in different environments have been extensively reported in the literature. It should be borne in mind that portland cement concrete has been used for over a century and there are currently constructions that date back to that age.

As regards reinforced concrete, field experience is much more limited since its intensive use is restricted to the past five decades and, therefore, most of the structures in service are not of significant age. Rebar corrosion is the most serious problem.

This paper is part of a research project that has been carried out for many years. Its objective is to study the field performance of structures built in the province of Buenos Aires, Argentina, located in different environments (rural, urban and industrial environments, and urban-marine subenvironments) in order to contribute to the knowledge of the "in situ" performance of the material.

### **Environmental characteristics**

Temperature, rainfall and relative humidity conditions, as well as the number of clear, overcast and rainy days (National Weather Forecast - 1971-1980 period) for rural, urban and urban-marine environments are reported. Mean annual temperatures are in the range 14 - 16°C. Industrial environments are characterised by the presence of contaminants from chemical, petrochemical, and siderurgical industries.

## Evaluation methods

Evaluated structures, located in a rural environment and urban-marine subenvironment, were selected at random, considering only the characteristics of the environment to which they were exposed. The evaluations of structures located in urban and industrial environments correspond to studies conducted according to the deterioration found. A visual inspection was made first in all cases. Depth of carbonation and rebar cover thickness were determined in some instances.

Concrete cores were extracted from some structures to study the mineralogical and petrographic characteristics of the aggregates. Tests were performed by spraying uranyl acetate to detect possible signs of the alkali-silica reaction (ASR). These tests were supplemented with analysis under an optical microscope. The physical, chemical and/or mechanical properties of the material were also established. The working scheme used follows the guidelines set by *DURAR Manual de Inspeccion, Evaluacion y diagnostico de Corrosion de Estructuras de Hormigon Armado*. CYTED.

## Concluding remarks

From these findings, which will have to be supplemented with new surveys of structures, it can be concluded that:

- a) Technological developments over the past years, especially those related to concrete performance in different aggressive environments, are not applied adequately in the field.
- b) Most of the structures evaluated in different environments, which were constructed before 1950, exhibit adequate field performance, no rebar corrosion processes or concrete damage being detected.
- c) In structures exposed to rural environments (moderately aggressive) signs of rebar corrosion can be detected at ages under 20 years due to lack of or insufficient cover depth that is carbonated. In structures located in aggressive environments (marine or industrial), the problem is more critical.
- d) In structures executed with aggregates petrographically classified as non-reactive, no signs of reaction are detected, as expected. In other structures, where aggregates with high strained-quartz contents and undulatory extinction angles greater than  $20^\circ$  were used, external reaction signs (cracks, gels, etc.) appear at greater ages when the alkali content is high. It has been found that some aggregates have satisfactory performance in the structure although in accelerated tests they exhibit high reactivity or fall into a classification where late reacting deleterious aggregates coexist with others of innocuous characteristics.

## Acknowledgments

This paper was funded by CONICET (Consejo Nacional de Investigaciones Cientificas y Tecnicas) and CIC (Comision de Investigaciones Cientificas).