

**Zeitschrift:** IABSE reports = Rapports AIPC = IVBH Berichte  
**Band:** 83 (1999)

**Artikel:** Chloride ingress in blast furnace slag cement in marine concrete structures  
**Autor:** Taheri, Ali / Breugel, Klaas van  
**DOI:** <https://doi.org/10.5169/seals-62879>

### **Nutzungsbedingungen**

Die ETH-Bibliothek ist die Anbieterin der digitalisierten Zeitschriften auf E-Periodica. Sie besitzt keine Urheberrechte an den Zeitschriften und ist nicht verantwortlich für deren Inhalte. Die Rechte liegen in der Regel bei den Herausgebern beziehungsweise den externen Rechteinhabern. Das Veröffentlichen von Bildern in Print- und Online-Publikationen sowie auf Social Media-Kanälen oder Webseiten ist nur mit vorheriger Genehmigung der Rechteinhaber erlaubt. [Mehr erfahren](#)

### **Conditions d'utilisation**

L'ETH Library est le fournisseur des revues numérisées. Elle ne détient aucun droit d'auteur sur les revues et n'est pas responsable de leur contenu. En règle générale, les droits sont détenus par les éditeurs ou les détenteurs de droits externes. La reproduction d'images dans des publications imprimées ou en ligne ainsi que sur des canaux de médias sociaux ou des sites web n'est autorisée qu'avec l'accord préalable des détenteurs des droits. [En savoir plus](#)

### **Terms of use**

The ETH Library is the provider of the digitised journals. It does not own any copyrights to the journals and is not responsible for their content. The rights usually lie with the publishers or the external rights holders. Publishing images in print and online publications, as well as on social media channels or websites, is only permitted with the prior consent of the rights holders. [Find out more](#)

**Download PDF:** 01.04.2026

**ETH-Bibliothek Zürich, E-Periodica, <https://www.e-periodica.ch>**



applied exposure condition consists of a drying period of 42 hrs followed by a wetting phase of 6 hrs with salt water containing 5% NaCl. The drying phase is a thermal regime characterized by a temperature swing from 20 °C to 60 °C within a period of 12 hrs. This simulates, with some acceleration, the aggressive marine environment in hot regions with varying daily temperature including direct solar radiation.

Two types of concretes, one with ordinary Portland cement and one blended with 70% blast furnace slag cement, cured with different conditions, are used in this experiment. Two curing regimes, i.e. standard curing and elevated temperature curing, are imposed upon the specimens. In standard curing, the specimens were exposed to room temperature and humidity, for 14 days. In the case of elevated temperature curing, concrete beams and cubes were exposed to the controlled environment with a temperature of 38 °C and relative humidity of 50%, also for 14 days, to simulate the curing conditions in tropical regions.

Observations after one month and six months of exposure showed that no significant microcracks had occurred at the surface of the concrete beams. Comparison of the chloride measurements in large elements and small specimens, both exposed to temperature and hygral variations, showed that (non-intensive) microcracks at the surface layers due to restraint of temperature-induced deformations, did not promote chloride penetration rate in the large specimens noticeably. The effect of microcracking, induced by temperature variations, on the rate of chloride penetration seems to be less than what has been suggested in the literature, at least with this particular test and boundary conditions. The pronounced effect of temperature cycles, however, was found to be more through the pore structures of the concrete than through the minor microcracks.

Slag cement concrete performed better than Portland cement concrete in the simulated aggressive marine environment. Furthermore, the elevated temperature curing had a substantial effect on promoting the chloride transport in concrete with Portland cement. In slag concrete, however, the elevated temperature curing did not show increase in ingress rate.

Regarding the numerical simulation, with *time dependent* values of the chloride diffusion coefficient and surface chloride content it was found that the error function solution to Fick's second law of diffusion can, with sufficient confidence, be used for non-steady state situations, such as the simulated marine condition in the performed experiment.

In the paper the focus is only made on the beneficial use of Portland cement blended with the slag cement and the satisfactory performance of slag concrete in comparison with concrete made with only Portland cement is highlighted. The "achieved chloride diffusion coefficients" for some of the specimens of both concrete types are also presented and compared. The effect of other parameters, mentioned above, has been discussed in other papers which are referred in this paper.

The results of this investigation, in the light of the experimental and numerical simulation, contribute to conclude that when designing any structure which will be exposed to sea water, unblended Portland cement concrete can not be expected to protect the steel for long term. Many other authors on the basis of site investigations have made the similar finding on performance of marine structures made with slag cement concrete with lower w/b ratio. The results confirm that tropical marine environment provides more aggressive conditions to the concrete and enhances the deterioration rate and hence shortens the service life of structures. Ground granulated blast furnace slag concrete (or concrete with other supplementary materials, like silica fume) should always be used in such an environment.