Zeitschrift:	Helvetica Physica Acta
Band:	62 (1989)
Heft:	6-7
Artikel:	Quantum effects in amorphous superstructures
Autor:	Fiorini, P. / Seta, M. de / Evangelisti, F.
DOI:	https://doi.org/10.5169/seals-116055

Nutzungsbedingungen

Die ETH-Bibliothek ist die Anbieterin der digitalisierten Zeitschriften auf E-Periodica. Sie besitzt keine Urheberrechte an den Zeitschriften und ist nicht verantwortlich für deren Inhalte. Die Rechte liegen in der Regel bei den Herausgebern beziehungsweise den externen Rechteinhabern. Das Veröffentlichen von Bildern in Print- und Online-Publikationen sowie auf Social Media-Kanälen oder Webseiten ist nur mit vorheriger Genehmigung der Rechteinhaber erlaubt. <u>Mehr erfahren</u>

Conditions d'utilisation

L'ETH Library est le fournisseur des revues numérisées. Elle ne détient aucun droit d'auteur sur les revues et n'est pas responsable de leur contenu. En règle générale, les droits sont détenus par les éditeurs ou les détenteurs de droits externes. La reproduction d'images dans des publications imprimées ou en ligne ainsi que sur des canaux de médias sociaux ou des sites web n'est autorisée qu'avec l'accord préalable des détenteurs des droits. <u>En savoir plus</u>

Terms of use

The ETH Library is the provider of the digitised journals. It does not own any copyrights to the journals and is not responsible for their content. The rights usually lie with the publishers or the external rights holders. Publishing images in print and online publications, as well as on social media channels or websites, is only permitted with the prior consent of the rights holders. <u>Find out more</u>

Download PDF: 07.08.2025

ETH-Bibliothek Zürich, E-Periodica, https://www.e-periodica.ch

QUANTUM EFFECTS IN AMORPHOUS SUPERSTRUCTURES

P. Fiorini, M. de Seta and F. Evangelisti Dipartimento di Fisica, Università *La Sapienza*, 00185 Roma, Italy

<u>Abstract</u>: A brief survey of quantum effects in amorphous superstructures is presented, with a particular attention to optical properties. The determination of interface properties by superstructure investigation is discussed, with a special enphasys on the amorphous silicon/amorphous silicon-carbon system.

1. Introduction

Amorphous superstructures are artificial materials prepared alternating thin layers of two amorphous semiconductors different either in doping [1] or in composition [2]. In the following we will deal only with compositional superstructures which exhibit a variety of novel properties, some of them resulting from quantum confinement effects, similarly to what happens in their crystalline analogues. With respect to crystalline superlattices amorphous superstructures exhibit two important differences: 1) quantum effects are observed only for layer thicknesses below 50 Å and in semiconductors with low defect density, typically hydrogenated amorphous silicon (a-Si:H) or hydrogenated amorphous germanium (a-Ge:H). 2)since large fluctuations of bond angles ($\simeq 8\%$) and bond lengths ($\simeq 2\%$) are present in amorphous materials the problems of "lattice mismatch" at the interface are less critical than for the crystalline case. Since hundreds of interfaces are present in the same sample the preparation of these superstructures offers also the possibility of investigating interface properties using techniques appropriate for bulk analysis. The most studied systems are those of a-Si:H with a-Ge:H, or with silicon based alloys (a-Si_xC_{1-x}:H, a-Si_xN_{1-x}:H). In the following we will briefly discuss the preparation of these materials, the evidence of quantum size effects and the interface characterization, with particular attention to the $a-Si:H/a-Si_{x}C_{1-x}:H$ system that we have investigated more extensively.

2. <u>Sample preparation</u>

The most widely used method for preparing amorphous silicon and its alloys is the plasma enhanced chemical vapor deposition, consisting in exciting a plasma in a gas mixture appropriate for the desired material, e.g. in silane (SiH₄) or in silane plus methane to prepare respectively a-Si:H and a-Si_xC_{1-x}:H alloys. In order to obtain the heterojunction the two different gas mixtures are rapidly interchanged in the reactor without interrupting the discharge. If the residence time of the gas is shorter than the time necessary to grow a monolayer the resulting interfaces are expected to be atomically abrupt. Structural characterizations performed by transmission electron microscopy [3] and X-ray scattering [4] have shown that this is indeed the case.

QUANTUM EFFECTS

There are various evidences of quantum confinement effects in amorphous silicon based superstructures coming both from optical and transport measurements. As an example let us consider the behavior of the absorption coefficient α for a series of superstructures of a-Si:H/a-Si_xC_{1-x}:H having a fixed thickness (120 Å) of a-Si_xC_{1-x}:H (E_g=2.8 eV) and a variable thickness of the silicon layer (E_g=1.8 eV). When the silicon layer thickness is decreased below 50 Å the absorption coefficient shifts to higher energies by a quantity ΔE_g as indicated in Fig. 1.



Fig. 1: Gap shift ΔE_g as a function of silicon layer thickness d_s . Absorption (0) and electroabsorption (+) measurements, theory (--).



Fig. 2 Density of gap states N_d as a function of the inverse of the silicon layer thickness d_s^{-1} .

This shift can be explained assuming that the minimum transitions energy is now the one separating quantum states in the wells as sketched in the inset of Fig. 1. The energy position of the levels in the well can be computed using basic quantum mechanics and depends on bands line-up(which determines the well depth) and on the effective mass of electrons in the valence and conduction bands. Using for bands alignment the results of photoemission measurements [5] the best fit to the data of Fig.1 is obtained with $m_c=0.3 m_e$ and $m_v=0.6 m_e$. Similar data have been obtained on different systems like $a-Si:H/a-Si_xN_{1-x}:H$ [6] and a-Si:H/a-Ge:H [7]. In the case of $a-Si:H/a-Si_xN_{1-x}:H$ the same value of $m_c=0.3 m_e$ is obtained from the fit. It has been pointed out that 0.3 m_e is exactly the average over the different directions of the effective mass of electrons in c-Si [8] but the coincidence could only be accidental.

Very recently striking evidence of the presence of quantum levels in a-Si:H/a- Si_xC_{1-x} :H superstructures have been obtained from accurate measurements of photothermomodulation spectroscoppy[8]. This technique gives directly the derivative of the absorption coefficient hence the sensitivity is considerably increased. Structures corresponding to transitions between sublevels are clearly observed in the spectra. Their position well agrees with the energy determined with the simple model described above using practically the same parameters.

Further evidences for the existence of quantum levels are obtained from transport measurements perpendicular to the layers. The I-V characteristics exhibit tiny structures [9,10,11] due to carrier tunneling as happens in crystalline superlattices. The position of the structures can again be explained in terms of a simple quantum model but a larger value of effective mass for the electron must be used in this case [10].

3. Inteface characterization

Interface properties have been studied on superstructures by many groups and with different techniques like Infra-Red [12] or Raman [13] spectroscopy, absorption and electroabsorption [14]. In the following, as an example, we will discuss what information about interfaces can be obtained from measurements of photoconductivity and of absorption coefficient in the gap energy region. In amorphous materials the absorption coefficient α in the pseudo-gap exhibits an exponential region, the so called Urbach tail, which extends a few tenth of eV below the onset of the band to band transitions and, at lower energies, a region where α is a slow varying function which results from transitions between localized defect states and extended band states. Our measurements show that these general features are conserved in the multilayer structures but both the characteristic energy E_0 of the exponential region and the absorption due to defect states can be determined from the value of α in the low energy region [15] and is reported as a function of the inverse silicon thickness d_s in Fig. 2. Since the total thickness of silicon was kept constant in all samples d_s⁻¹ is proportional to the number n of a-Si:H/a-Si_xC_{1-x}:H interfaces. Therefore the linear increase of N_d with n points to the presence of a large density of localized states close to the interface. The spatial distribution of these defect states can be reasonably assumed to be an exponentially decreasing function with the maximum value N⁰_d right at the interface and with a small decay length *l*. With this assumption and if $d_s \gg l$, the absorption coefficient is given by

$$lpha \propto N_d^0 l \cdot rac{1}{d_s} = N_s/d_s$$

where $N_d^0 \cdot l$ can be defined as the number of defects at the interface N_s . The linear behavior of Fig. 2 confirms the hypothesis that $l \ll d$ even for the smallest value of d_s (20 Å). From the slope of the linear behavior we deduce a value of 2×10^{11} cm⁻² for N_s .



Fig. 3:Behavior of the mobilitylifetime product as a function of the silicon layer thickness. Experiment (\circ), theory (--).

Turning now to the photoconductivity measurements we will show how they can give informations about the electrical behavior of defect states at the interface. From the value of photoconductivity parallel to the layers it is possible to derive the mobility lifetime product $(\mu\tau)$ for the majority carriers (i.e. electrons) in the silicon layer. This quantity decreases drastically with decreasing the a-Si:H layer thickness as reported in Fig 3. We ascribe this behavior to the large density of defect states at the interfaces. Their effect has been taken into account by introducing a surface recombination velocity v_s proportional to N_s itself and by solving the diffusion equation perpendicularly to the layers in order to determine the thickness dependent distribution of excited carriers [16]. From this distribution it is easy to compute the $\mu\tau$ product and compare it with the experimental results. The best fit reported in Fig. 3 is obtained with $v_s = 5 \times 10^6$ cm/s.

4. Conclusions

We have briefly summarized the evidence of quantum confinement effects in amorphous superstructures. We have also shown that the study of heterostructures can be an effective way in determining the properties of the interfaces, which influences the performances of devices based on a-Si:H and possibly also the magnitude of quantum effects [17].

5. <u>References</u>

- [1] M. Hundhausen, L. Ley and R. Carius, Phys. Rev. Lett. 53, 1598 (1984)
- [2] B. Abeles and T. Tiedje, Semiconductors and Semimetals 21C, 375 (1984)
- [3] R. Cheng, S. Weng, J. Feng and H. Fritsche, Appl. Phys. Lett. 46, 592 (1985)
- [4] B. Abeles and T. Tiedje, Phys. Rev. Lett. 51, 2003 (1983)
- [5] M. Hirose, Technical Digest of the Third International Photovoltaic Sciences and Engineering Conference, Tokyo, 1987, ed. by k. Takahashi (Society of Photovoltaic Scientist and Engineers, Washington, DC, 1987) p. 651
- [6] T. Tiedje, B. Abeles, P.D. Persans, B.G. Brooks, G.D. Cody, J. Non-Cryst. Solids 66, 345 (1984)
- [7] T. Tiedje, C.R. Wronsky, P.D. Persans and B. Abeles, J. Non-Cryst. Solids 77-78, 1031 (1985)
- [8] K. Hattori, T. Mori, H. Okamoto and Y. Hamakawa, Phys Rev Lett. 60, 823 (1988)
- [9] I. Pereyra, M.N.P. Carreno, R.K. Omnori, C.A. Sassaki, A.M. Andrade and F. Alvarez, J. Non-Cryst. Solids 97-98, 871 (1987)
- [10] S. Miyazaki, Y. Ihara and M. Hirose, Phys. Rev. Lett 59, 125 (1987)
- [11] C.E. Nebel, F. Kessler, G. Bilger, G.H. Bauer, Y.L. Jiang, H.L. Hwang, K.C. Hsu and C.S. Hong, M.R.S. Symposia Proceedings 118, (1986)
- [12] B. Abeles, L.Yang, P.D. Persans and H. Stasiewsky, Appl. Phys. Lett. 48, 168 (1986)
- [13] P.D. Persans, A.F. Ruppert, B. Abeles and T. Tiedje, Phys. Rev. B32, 5558 (1985)
- [14] C.B. Roxlo, B. Abeles and T. Tiedje, Phys. Rev. Lett. 52, 1994, (1984)
- [15] N.M. Amer, and W.B. Jackson, Semiconductors and Semimetals 21B, 83 (1981)
- [16] M. de Seta, P. Fiorini, F. Evangelisti and A. Armigliato, Superlattices and Microstructures 5, 149 (1989)
- [17] R. Tsu, J. Non-Cryst. Solids 75, 463 (1985)