

Zeitschrift: Helvetica Physica Acta
Band: 62 (1989)
Heft: 6-7

Artikel: High energy neutron spectroscopy in crystal field split 5f systems
Autor: Amoretti, G. / Caciuffo, R. / Blaise, A.
DOI: <https://doi.org/10.5169/seals-116096>

Nutzungsbedingungen

Die ETH-Bibliothek ist die Anbieterin der digitalisierten Zeitschriften auf E-Periodica. Sie besitzt keine Urheberrechte an den Zeitschriften und ist nicht verantwortlich für deren Inhalte. Die Rechte liegen in der Regel bei den Herausgebern beziehungsweise den externen Rechteinhabern. Das Veröffentlichen von Bildern in Print- und Online-Publikationen sowie auf Social Media-Kanälen oder Webseiten ist nur mit vorheriger Genehmigung der Rechteinhaber erlaubt. [Mehr erfahren](#)

Conditions d'utilisation

L'ETH Library est le fournisseur des revues numérisées. Elle ne détient aucun droit d'auteur sur les revues et n'est pas responsable de leur contenu. En règle générale, les droits sont détenus par les éditeurs ou les détenteurs de droits externes. La reproduction d'images dans des publications imprimées ou en ligne ainsi que sur des canaux de médias sociaux ou des sites web n'est autorisée qu'avec l'accord préalable des détenteurs des droits. [En savoir plus](#)

Terms of use

The ETH Library is the provider of the digitised journals. It does not own any copyrights to the journals and is not responsible for their content. The rights usually lie with the publishers or the external rights holders. Publishing images in print and online publications, as well as on social media channels or websites, is only permitted with the prior consent of the rights holders. [Find out more](#)

Download PDF: 07.08.2025

ETH-Bibliothek Zürich, E-Periodica, <https://www.e-periodica.ch>

HIGH ENERGY NEUTRON SPECTROSCOPY IN
CRYSTAL FIELD SPLIT 5f SYSTEMS

G. Amoretti*, R. Caciuffo*, A. Blaise†, J.M. Fournier†, M.T. Hutchings‡, R. Osborn◊ and A.D. Taylor◊

*Dipartimento di Fisica dell'Università, 43100 PARMA, Italy

*Dipartimento di Scienze dei Materiali dell'Università, 60131 ANCONA, Italy

†DRF, Centre d'Études Nucléaires, 38041 GRENOBLE, France

‡Material Physics and Metallurgy Division, Harwell Lab., DIDCOT, OX11 0RA, U.K.

◊Neutron Science Division, Rutherford Appleton Lab., CHILTON, OX11 0QX, U.K.

Abstract: The new generation of spallation neutron sources, characterized by an intense epithermal flux, allows the observation of magnetic excitations up to several hundreds of *meV*. It is then possible to determine the crystal field transitions in a number of actinide systems, as it is illustrated in the case of *UO₂*, *UOS* and *NpO₂*.

1. Introduction

The knowledge of the crystal field (CF) is often essential to describe the magnetic and thermodynamic properties of actinide systems and also to answer fundamental questions about the behaviour of the 5f electrons. As known, neutron inelastic scattering provides the most effective method to observe CF transitions in opaque samples. In the case of actinide systems, the kinematic constraint of the scattering process becomes particularly severe at high energy transfer, because the form factor $f(Q)$ falls very rapidly with Q . Neutrons with high incident energy must then be used and, for this reason, spallation neutron sources with a large slowing down component in the epithermal region of the neutron spectrum are better suited than steady-state reactors. We present here a short review of some experiments recently performed on the HET spectrometer at the UK spallation source ISIS of the Rutherford Appleton Laboratory.

2. Results and Discussion

The first example is the *CaF₂* structure compound *UO₂* for which the ninefold degeneracy of the ground multiplet is resolved into two triplets, one doublet and one singlet by the cubic CF above the ordering temperature $T_N = 30.8K$. Below T_N , an internal distortion of the oxygen sublattice reduces the symmetry, giving rise to a further splitting of the levels. The inelastic neutron scattering cross section at $T = 50K$ shows two peaks, at 150 and 166 *meV*, which can be attributed to the $\Gamma_5 \rightarrow \Gamma_3$ and $\Gamma_5 \rightarrow \Gamma_4$ transitions respectively. No more excitations have been observed up to ~ 700 *meV*. This allowed the determination of the two coefficients in the CF hamiltonian, namely $V_4 = -123$ *meV* and $V_6 = 26.5$ *meV* [1,2]. It has been shown also that *J*-mixing effects are far less important than previously assumed. Below the Néel temperature, more structure appears in the

neutron spectra. Detailed CF calculations have been performed [2] assuming either a 2-k magnetic structure and monoclinic lattice distortion or a 3-k magnetic structure and lattice distortion. The comparison with the experimental splittings is in favour of the second case.

The second compound we have examined is *UOS*, which belongs to the tetragonal *PbFCl* crystal structure and orders antiferromagnetically below $T_N = 55K$. Two main excitation peaks have been found at 74 and 82 meV for $T > T_N$. A redistribution of the intensities together with a slight shift of the peak positions is observed below T_N . No other CF excitations appear up to at least 200 meV [3]. The spectra have been interpreted [3,4] in the frame of a CF model accounting for the Schottky contribution to the specific heat, from which the splitting of the $J = 4$ manifold into two groups of states with a separation not greater than 100 meV was expected. The peaks in the neutron spectra have been attributed to the transitions from the ground $\Gamma_{t5}^{(1)}$ doublet to the second group of states. The intensity variation and the level shifts have also been interpreted as an effect of the molecular field.

Finally, a neutron spectroscopy study has been performed on *NpO₂*, which is isostructural to *UO₂* and contains *Np⁴⁺* ions with $5f^3$ electronic configuration. The tenfold degeneracy of the $J = 9/2$ ground multiplet is split by the cubic CF into two quartets and one doublet. This compound presents a phase transition at $T_c = 25K$ whose origin is as yet unexplained. We have examined a sample of 32g of powder, together with a similar *ThO₂* sample, allowing us to perform a reliable phonon density of state subtraction. Although no sharp peaks have been found up to 350 meV, magnetic scattering is clearly visible from our spectra around ~ 60 meV. The difference of *NpO₂* and *ThO₂* spectra shows in fact a broad peak centered at this energy value, having ~ 20 meV FWHM. No significant changes have been observed in passing through the transition temperature. CF calculations starting from the CF parameters determined for *UO₂* predict for *NpO₂* a strong $\Gamma_8^{(2)} \rightarrow \Gamma_8^{(1)}$ transition at ~ 55 meV. We believe to have observed this CF excitation, the broadening of the peak being probably due to interaction with optical phonons at the same energy.

3. References

- [1] R. Osborn, A.D. Taylor, Z.A. Bowden, M.A. Hackett, W. Hayes, M.T. Hutchings, G. Amoretti, R. Caciuffo, A. Blaise, J.M. Fournier, J. Phys. C: Solid State Phys. **21**, L931 (1988).
- [2] G. Amoretti, A. Blaise, R. Caciuffo, J.M. Fournier, M.T. Hutchings, R. Osborn and A.D. Taylor, RAL-88-096, and Phys. Rev. B, in print.
- [3] G. Amoretti, A. Blaise, J.M. Fournier, R. Caciuffo, J. Larroque, R. Osborn, A.D. Taylor and Z.A. Bowden, J. Magn. Magn. Mat. **76-77**, 432 (1988).
- [4] G. Amoretti, A. Blaise, R. Caciuffo, J.M. Fournier, J. Larroque and R. Osborn, RAL-88-095, and J. Phys.: Condens. Matter, in print.
- [5] J.M. Fournier, A. Blaise, G. Amoretti, R. Caciuffo, J. Larroque, M.T. Hutchings, R. Osborn and A.D. Taylor, 19èmes Journées des Actinides, March 1989, Madonna di Campiglio, Italy, and to be published.