

**Zeitschrift:** Helvetica Physica Acta

**Band:** 62 (1989)

**Heft:** 6-7

**Artikel:** Fundamental optical constants of CIS polyacetylene

**Autor:** Lanzani, G. / Dellepiane, G. / Musso, G.F.

**DOI:** <https://doi.org/10.5169/seals-116131>

#### **Nutzungsbedingungen**

Die ETH-Bibliothek ist die Anbieterin der digitalisierten Zeitschriften auf E-Periodica. Sie besitzt keine Urheberrechte an den Zeitschriften und ist nicht verantwortlich für deren Inhalte. Die Rechte liegen in der Regel bei den Herausgebern beziehungsweise den externen Rechteinhabern. Das Veröffentlichen von Bildern in Print- und Online-Publikationen sowie auf Social Media-Kanälen oder Webseiten ist nur mit vorheriger Genehmigung der Rechteinhaber erlaubt. [Mehr erfahren](#)

#### **Conditions d'utilisation**

L'ETH Library est le fournisseur des revues numérisées. Elle ne détient aucun droit d'auteur sur les revues et n'est pas responsable de leur contenu. En règle générale, les droits sont détenus par les éditeurs ou les détenteurs de droits externes. La reproduction d'images dans des publications imprimées ou en ligne ainsi que sur des canaux de médias sociaux ou des sites web n'est autorisée qu'avec l'accord préalable des détenteurs des droits. [En savoir plus](#)

#### **Terms of use**

The ETH Library is the provider of the digitised journals. It does not own any copyrights to the journals and is not responsible for their content. The rights usually lie with the publishers or the external rights holders. Publishing images in print and online publications, as well as on social media channels or websites, is only permitted with the prior consent of the rights holders. [Find out more](#)

**Download PDF:** 07.08.2025

**ETH-Bibliothek Zürich, E-Periodica, <https://www.e-periodica.ch>**

## FUNDAMENTAL OPTICAL CONSTANTS OF CIS POLYACETYLENE

G.Lanzani, G.Dellepiane, G.F.Musso Ist. di Chimica Industriale  
Universita' di Genova, Corso Europa, 30 16132 GENOVA(I)  
A.Piaggi, D.Comoretto, A.Borghesi; Dip. di Fisica A.Volta  
Univ. di Pavia, via Bassi 6 27100 PAVIA(I)  
R.Tubino, Ist. di Fisica Universita' di Sassari  
Via Vienna 2, SASSARI(I)

**Abstract:** The optical reflectivity of thick films ( $20-30 \mu m$ ) of fibrous polyacetylene (PA), highly oriented by mechanical stretching has been measured using polarized light. A Kramers-Kronig analysis of the data has been used to determine the optical constants for polarization parallel and perpendicular to the chain axis.

**INTRODUCTION:** The evaluation of the anisotropy of the optical properties of PA is in principle quite important for a better understanding of the optical transitions and of the mechanism of photogeneration of the carriers in a three dimensional polymer lattice using polarized light(1-2). So far an accurate investigation of the optical properties of fully oriented PA has been carried out only on Durham-PA(3). We have felt that, in consideration of its different morphology, the measure of the optical constants of the stretch-oriented Shirakawa PA could yield an additional insight on the nature of the interband transition of this prototype semiconducting polymer.

**EXPERIMENTAL:** Highly oriented (draw ratio 7) Shirakawa PA films were a gift by Enichem Research Labs.(4). The as synthesized film exhibits a fibrillar morphology and X-ray measurements carried out on this sample indicate a degree of crystallinity of 97% with a misalignment angle of 10 degrees. The reflectivity of the samples were measured in the energy range between 0.062 and 4.2 eV with polarized light parallel and perpendicular to the stretching axis(Fig.1). The complex refractive index  $\tilde{n}(\omega)$  and the dielectric function  $\tilde{\epsilon}(\omega)$  was obtained using KK trasformation on the reflectivity data.

**DISCUSSION:** In order to detect the effects of the interchain interactions on the optical response of PA we have worked out a tight binding model extended to include the

effect of the interchain coupling on the electronic energies and on the transition moments. Some caution should however be exerted in comparing the calculated and experimental anisotropies. In fact a contribution to the perpendicular absorption and reflectivity comes from the small (but not negligible) sample misalignment. The theoretical values of the optical constants should therefore be averaged on the possible orientations of the chain with respect to the stretching direction. This calculation(5) implies that sample misalignment account for almost entirely the absorption anisotropy and masks small but not vanishing interchain contribution to the perpendicular response.




Fig.1  
Optical reflectivity measured with  
light parallel and normal to the  
stretching direction.

### References

- [1] R.Dorsinville, S.Krimchansky, R.R.Alfano, J.L.Birman, R.Tubino and G.Dellepiane, Solid State Commun. 56, 857,(1987)
- [2] P.L.Danielsen, Synth. Metals 20, 125 (1985).
- [3] P.D.Towsend and R.H.Friend, Synth. Metals 17, 631(1987)
- [4] G.Lugli,U.Pedretti and G.Perego, J.Polym.Sci., Polym.Lett.Ed. 23, 129(1985)
- [5] D.Comoretto, A.Borghesi, G.Dellepiane, G.Lanzani, G.F.Musso, A.Piaggi and R.Tubino to be published