Zeitschrift:	Helvetica Physica Acta
Band:	62 (1989)
Heft:	6-7
Artikel:	Low temperature oxidation of iron borides
Autor:	Carbucicchio, M. / Reverberi, R. / Palombarini, G
DOI:	https://doi.org/10.5169/seals-116149

Nutzungsbedingungen

Die ETH-Bibliothek ist die Anbieterin der digitalisierten Zeitschriften auf E-Periodica. Sie besitzt keine Urheberrechte an den Zeitschriften und ist nicht verantwortlich für deren Inhalte. Die Rechte liegen in der Regel bei den Herausgebern beziehungsweise den externen Rechteinhabern. Das Veröffentlichen von Bildern in Print- und Online-Publikationen sowie auf Social Media-Kanälen oder Webseiten ist nur mit vorheriger Genehmigung der Rechteinhaber erlaubt. <u>Mehr erfahren</u>

Conditions d'utilisation

L'ETH Library est le fournisseur des revues numérisées. Elle ne détient aucun droit d'auteur sur les revues et n'est pas responsable de leur contenu. En règle générale, les droits sont détenus par les éditeurs ou les détenteurs de droits externes. La reproduction d'images dans des publications imprimées ou en ligne ainsi que sur des canaux de médias sociaux ou des sites web n'est autorisée qu'avec l'accord préalable des détenteurs des droits. <u>En savoir plus</u>

Terms of use

The ETH Library is the provider of the digitised journals. It does not own any copyrights to the journals and is not responsible for their content. The rights usually lie with the publishers or the external rights holders. Publishing images in print and online publications, as well as on social media channels or websites, is only permitted with the prior consent of the rights holders. <u>Find out more</u>

Download PDF: 07.08.2025

ETH-Bibliothek Zürich, E-Periodica, https://www.e-periodica.ch

LOW TEMPERATURE OXIDATION OF IRON BORIDES

M.Carbucicchio, R.Reverberi, Department of Physics, University, Viale delle Scienze, 43100 Parma, Italy G.Palombarini and G.Sambogna, Institute of Metallurgy, University, Viale Risorgimento 4, 40137 Bologna, Italy

<u>Abstract</u>: The oxidation of pure iron borides was investigated by X-ray diffraction, surface Mössbauer spectroscopy, scanning electron microscopy and thermogravimetry. Iron borides undergo oxidation at low temperature, with formation of both oxides and oxygen-free products.

1. Introduction

The oxidation of iron borides generally has been investigated using coatings grown on iron and its alloys. Polyphase coatings on iron base substrates, however, are systems very far from equilibrium and the effects of oxidation can be masked by other thermally activated modifications.

The aim of the present work was to study the early stages of oxidation of iron borides. Single phase specimens were prepared by compacting powders in order to avoid the phenomena connected with the participation of the metal substrate in the process.

2. Experimental

Powders of 99% pure Fe_2B and FeB were cold compacted and then oxidized in the 300°-450°C range, for 1 h, in pure oxygen. The oxidized samples were studied by means of X-ray diffraction (using a computer-controlled goniometer and CoKa radiation),

Vol. 62, 1989 Condensed Matter

surface Mössbauer spectroscopy and scanning electron microscopy (carried out on both oxidized and fractured samples).

The Mössbauer measurements were performed by detecting the K X-rays (CXMS) and the K-shell conversion electrons resonantly re-emitted by the 57 Fe atoms (D-CEMS). The depth selective spectra were recorded by simultaneously detecting conversion electrons emerging at the surface with energies in ranges lying between 5.5-7.3 keV. The source was a 100 mCi 57 Co(Rh), and the spectra were computer-fitted to a series of Lorentzian peaks.

Thermogravimetric analyses were carried out on powder samples treated in the same temperature range.

3. Results

The oxidation of iron borides Fe₂B and FeB begins at temperatures much lower than those generally considered in the literature. This is an important factor to consider for practical applications in oxidizing environments.

The starting temperature of oxidation is lower for FeB ($\sim 300 \ ^{\circ}$ C) than for Fe₂B ($\sim 400 \ ^{\circ}$ C). Oxygen easily reacts with boron giving rise to B₂O₃ and liberating iron. In the case of Fe₂B, iron reacts with oxygen giving rise to Fe₂O₃, while in the case of FeB iron preferentially reacts with the FeB itself giving rise to Fe₂B.

The probability of interaction between 0 and Fe in the boride lattices is low in the temperature range investigated. In the case of FeB, this interaction can explain the formation of appreciable amounts of FeB_{x} with x slightly greater than one.