

Zeitschrift: Helvetica Physica Acta
Band: 65 (1992)
Heft: 2-3

Artikel: Conserving approximation for the multi-band Hubbard model
Autor: Putz, R. / Dieterich, P. / Hanke, W.
DOI: <https://doi.org/10.5169/seals-116470>

Nutzungsbedingungen

Die ETH-Bibliothek ist die Anbieterin der digitalisierten Zeitschriften auf E-Periodica. Sie besitzt keine Urheberrechte an den Zeitschriften und ist nicht verantwortlich für deren Inhalte. Die Rechte liegen in der Regel bei den Herausgebern beziehungsweise den externen Rechteinhabern. Das Veröffentlichen von Bildern in Print- und Online-Publikationen sowie auf Social Media-Kanälen oder Webseiten ist nur mit vorheriger Genehmigung der Rechteinhaber erlaubt. [Mehr erfahren](#)

Conditions d'utilisation

L'ETH Library est le fournisseur des revues numérisées. Elle ne détient aucun droit d'auteur sur les revues et n'est pas responsable de leur contenu. En règle générale, les droits sont détenus par les éditeurs ou les détenteurs de droits externes. La reproduction d'images dans des publications imprimées ou en ligne ainsi que sur des canaux de médias sociaux ou des sites web n'est autorisée qu'avec l'accord préalable des détenteurs des droits. [En savoir plus](#)

Terms of use

The ETH Library is the provider of the digitised journals. It does not own any copyrights to the journals and is not responsible for their content. The rights usually lie with the publishers or the external rights holders. Publishing images in print and online publications, as well as on social media channels or websites, is only permitted with the prior consent of the rights holders. [Find out more](#)

Download PDF: 15.01.2026

ETH-Bibliothek Zürich, E-Periodica, <https://www.e-periodica.ch>

Conserving Approximation for the Multi-Band Hubbard Model

R. Putz, P. Dieterich, and W. Hanke

Physikalisches Institut, Universität Würzburg, Am Hubland
D-8700 Würzburg, Germany

We study the multi-band Hubbard model within a diagrammatic expansion which is conserving in the sense of the Baym/Kadanoff formalism. One- and two-particle properties are computed in Hartree-Fock and in the Fluctuation Exchange (FLEX) approximation, a technique recently proposed by Bickers and Scalapino. The results are checked in direct comparison with exact Quantum-Monte-Carlo results. For finite hole doping the magnetic structure factor $S(\vec{q})$ exhibits a maximum away from $\vec{q} = 0$. This behavior signals the formation of an incommensurate spin ordering of the system which is observed in experimental studies of the cuprate $\text{La}_{2-x}\text{Sr}_x\text{CuO}_4$. The hypothesis of Varma which states a marginal Fermi liquid for the high temperature superconductors is object of our following investigations. We find indications for an anomalous frequency behavior of the polarisation even at $\vec{q} = 0$ near the charge transfer instability, a result which is important to describe Raman scattering experiments in high- T_c oxides.

I. Introduction

It is commonly established that CuO_2 -layers are the most relevant structure elements of high temperature superconductors and that they are responsible for the remarkable properties in the normal and superconducting state. The neighborhood of antiferromagnetism and superconductivity, and the appearance of a Mott-isolator transition, indicate that electronic correlations play an important role in these materials.

II. Model

The starting point of our calculations is the multi-band Hubbard model, which includes both O-2p and Cu-3d-orbitals:

$$H = H_0 + H_1,$$

with

$$H_0 = \sum_{i,\sigma} (E_d - \mu) d_{i\sigma}^\dagger d_{i\sigma} + \sum_{\substack{j,\sigma \\ \alpha=x,y}} (E_p - \mu) c_{j\sigma}^{(\alpha)\dagger} c_{j\sigma}^{(\alpha)} - t_{ij} \sum_{\substack{i,j \\ \alpha=x,y}} (-1)^{p_{ij}} (d_{i\sigma}^\dagger c_{j\sigma}^{(\alpha)} + h.c.)$$

$$H_1 = U_d \sum_i n_{di\uparrow} n_{di\downarrow} + U_p \sum_j n_{pj\uparrow} n_{pj\downarrow} + \frac{U_{pd}}{2} \sum_{\substack{i,j \\ \sigma\sigma'}} n_{di\sigma} n_{pj\sigma'}$$

Here $d_{i\sigma}^\dagger$ and $c_{j\sigma}^{(\alpha)\dagger}$ denote the electron creation operators for Cu d and O p orbitals at sites i and j . The one-electron part H_0 is determined by the on-site energies E_d (Cu) and E_p (O) with the charge-transfer energy $\Delta = E_p - E_d$, and a Cu-O hopping $t_{ij} = \pm t$ between nearest-neighbor sites $\langle i, j \rangle$. The chemical potential μ allows to adjust the doping. The

interaction part H_1 includes the on-site Coulomb energies U_d (Cu) and U_p (O) and the nearest-neighbor repulsion U_{pd} .

III. Conserving Approximation

We perform a perturbation expansion up to intermediate values of the correlation parameters. While a simple Random-Phase-Approximation (RPA) is far away from agreement with exact QMC-results, Bickers and Scalapino developed a perturbation expansion in the Fluctuation Exchange (FLEX) approximation [1], that leads to good results for the one-band Hubbard model. This method is based on the Conserving-Approximation (CA) formalism of Baym and Kadanoff [2], which obeys the macroscopic conservation laws even in an infinite order approximation. We have extended this CA-FLEX formalism to the multi-band Hubbard model described in the preceding section [3].

IV. Numerical Results

The magnetic susceptibilities are given by

$$\chi_{SDW/CDW}(\vec{q}, i\omega_m) = \frac{1}{N} \sum_{ij} e^{i\vec{q} \cdot (\vec{x} - \vec{x}')} \cdot \int_0^\beta d\tau d\tau' e^{-i\omega_m(\tau - \tau')} \langle (n_{i\uparrow} \mp n_{i\downarrow})(n_{j\uparrow} \mp n_{j\downarrow}) \rangle,$$

where i, j refer to copper places only. The upper signs correspond to the spin density wave (SDW), the lower to the charge density wave (CDW) susceptibility. These expressions are identical to the QMC definitions [4] and can therefore be compared directly. In Fig. 1 the static SDW-susceptibility is shown as function of the system temperature T . The point-dashed curve refers to the simplest CA: The one-particle propagator is computed in Hartree-Fock (HF) approximation and the susceptibility is calculated by ladder and bubble summation. These HF-CA results




Figure 1: The SDW susceptibility as function of temperature versus QMC results. The approximations are explained in the text.

are far away from agreement with the QMC data. We also calculated a time-dependent HF-approximation with selfconsistent one-particle FLEX propagators. Although this approximation is not conserving, we get in Fig. 1 an excellent agreement with the QMC-results for the SDW-susceptibility, which is one of the most sensitive two particle functions in our system. We extract the magnetic structure form factor $S(\vec{q})$ which delivers information about the spin ordering of the system:

$$S(\vec{q}) = \frac{1}{\beta} \sum_{\omega_m} \chi_{SDW}(\vec{q}; i\omega_m).$$




Figure 2: The magnetic structure form factor for finite hole doping.

In the undoped case ($\delta = 0$) $S(\vec{q})$ is sharply peaked at $\vec{q} = (\pi, \pi)$ which indicates the antiferromagnetic order of the system. For finite hole doping the maximum of $S(\vec{q})$ moves away from $\vec{q} = (\pi, \pi)$ as shown in




Figure 3: The CDW susceptibility in the neighborhood of the charge transfer instability.

Fig. 2 for $\delta \approx 20\%$. This shift signals the formation of an incommensurate spin ordering of the system, which was observed in experimental studies [5]. The developed perturbation expansion for the multi-band Hubbard model can also be used to study the low energy behaviour of the system. Varma's hypothesis [6] for the frequency dependence of the spin and charge polarisation should be valid for a wide range of wave vectors, especially for $\vec{q} = (0, 0)$ in order to describe Raman scattering experiments. Whereas $\text{Im} \chi_{SDW}$ decreases to zero for $\vec{q} \rightarrow (0, 0)$ the imaginary part of the charge density wave susceptibility χ_{CDW} shows the desired Varma behaviour (Fig. 3) near the charge-transfer instability which is a special feature of the multi-band Hubbard model.

Acknowledgments

Support by the DFG project Ha 1537/5-1 is acknowledged.

- [1] N. E. Bickers and D. J. Scalapino, Annals of Physics **193**, 207 (1989), N. E. Bickers and S. R. White, Phys. Rev. B **43**, 8044 (1991).
- [2] G. Baym, Phys. Rev. **127**, 1391 (1962).
- [3] P. Dieterich, R. Putz, and W. Hanke, to be published.
- [4] G. Dopf, A. Muramatsu, and W. Hanke, Phys. Rev. B **41**, 9264 (1990).
- [5] T. R. Thurston et al., Phys. Rev. B **40**, 4585 (1989).
- [6] C. M. Varma et al., Phys. Rev. Lett. **63**, 1996 (1989).