

Zeitschrift: Helvetica Physica Acta
Band: 65 (1992)
Heft: 2-3

Artikel: The hole excitation spectrum in CuO₂ plane
Autor: Kuzian, Roman O. / Barabanov, Alexander F. / Maksimov, Leonid A.
DOI: <https://doi.org/10.5169/seals-116479>

Nutzungsbedingungen

Die ETH-Bibliothek ist die Anbieterin der digitalisierten Zeitschriften auf E-Periodica. Sie besitzt keine Urheberrechte an den Zeitschriften und ist nicht verantwortlich für deren Inhalte. Die Rechte liegen in der Regel bei den Herausgebern beziehungsweise den externen Rechteinhabern. Das Veröffentlichen von Bildern in Print- und Online-Publikationen sowie auf Social Media-Kanälen oder Webseiten ist nur mit vorheriger Genehmigung der Rechteinhaber erlaubt. [Mehr erfahren](#)

Conditions d'utilisation

L'ETH Library est le fournisseur des revues numérisées. Elle ne détient aucun droit d'auteur sur les revues et n'est pas responsable de leur contenu. En règle générale, les droits sont détenus par les éditeurs ou les détenteurs de droits externes. La reproduction d'images dans des publications imprimées ou en ligne ainsi que sur des canaux de médias sociaux ou des sites web n'est autorisée qu'avec l'accord préalable des détenteurs des droits. [En savoir plus](#)

Terms of use

The ETH Library is the provider of the digitised journals. It does not own any copyrights to the journals and is not responsible for their content. The rights usually lie with the publishers or the external rights holders. Publishing images in print and online publications, as well as on social media channels or websites, is only permitted with the prior consent of the rights holders. [Find out more](#)

Download PDF: 07.08.2025

ETH-Bibliothek Zürich, E-Periodica, <https://www.e-periodica.ch>

The Hole Excitation Spectrum in CuO_2 Plane

Roman O. Kuzian, Alexander F. Barabanov

Institute for High Pressure Physics Troitsk, Moscow region, 142092, USSR

Leonid A. Maksimov

Institute for Atomic Energy, Moscow, 123182, USSR

Abstract. The hole spectrum $e(\vec{k})$ that is studied in the framework of Emery model is shown to be strongly dependent on direct $O - O$ hopping h and on doping n , the latter being modeled through the frustration α in Cu spin subsystem. The $e(\vec{k})$ demonstrates non-rigid-band behavior, its minimum value and band bottom position are changed with doping.

The CuO_2 plane hole motion is studied in the framework of strong coupling limit of Emery model with the Hamiltonian [1,2]:

$$\hat{H} = \tau \sum_{\vec{R}, \vec{a}_1, \vec{a}_2, \sigma} Z_{\vec{R}}^{\sigma_1 \sigma_2} c_{\vec{R} + \vec{a}_1, \sigma_1}^+ c_{\vec{R} + \vec{a}_2, \sigma_2} + h \sum_{\vec{R}, \vec{a} = \vec{a}_x, \vec{a}_y, \vec{b}, \sigma} c_{\vec{R} + \vec{a}, \sigma}^+ c_{\vec{R} + \vec{a} + \vec{b}, \sigma} + \hat{H}_J \quad (1)$$

$$\hat{H}_J = \hat{J}_1 + \hat{J}_2, \quad \hat{J}_1 = J \sum_{\vec{R}, \vec{a}} \hat{S}_{\vec{R}} \hat{S}_{\vec{R} + 2\vec{a}}, \quad \hat{J}_2 = \alpha J \sum_{\vec{R}, \vec{b}} \hat{S}_{\vec{R}} \hat{S}_{\vec{R} + 2\vec{b}}$$

here $\vec{R} + \vec{a}$ are four vectors of O sites nearest to Cu site \vec{R} ; \vec{b} — nearest neighbor vectors for the oxygen sublattice; $Z_{\vec{R}}^{\sigma_1 \sigma_2}$ are Hubbard projection operators for Cu sites.

We believe that the influence of finite but small doping may be modeled by including the frustration \hat{J}_2 in $Cu - Cu$ spin interaction.

It was earlier shown [2] that the carrier spectrum can be obtained by variational approach in the framework of the concept of magnetic polaron. The variational ansatz is:

$$\theta_{\vec{R}} = \frac{1}{2} \sum_{\vec{a} = \pm \vec{a}_x, \pm \vec{a}_y} \beta_{\vec{a}} (c_{\vec{R} + \vec{a}_1, +1}^+ Z_{\vec{R}}^{--} - c_{\vec{R} + \vec{a}_2, -1}^+ Z_{\vec{R}}^{+-}) |G\rangle; \quad |\beta_{\vec{a}}| = 1 \quad (2)$$

where $|G\rangle$ — the singlet wave function of Cu spin subsystem, which is described by \hat{H}_J . The properties of the state $|G\rangle$ for various values of α are discussed in [3] in detail.

In the simplest approximation $\beta_{\vec{a}} = 1$ the spectrum can be found analytically ($h = 0$):

$$e(\vec{k}) = -3.5\tau - [4J(A_3 + \alpha A_4) + (4.5A_1\tau - A_3J)\gamma_{\vec{k}} + A_2\tau(1 - 4\gamma_{\vec{k}}^2)][1 + A_1\gamma_{\vec{k}}]^{-1} \quad (3)$$

$$A_1 = 0.25 + K_1; \quad A_2 = 0.125 - K_1 + 0.5K_2; \quad A_3 = 2K_1; \quad A_4 = 2K_2; \quad K_1 = \langle \hat{S}_{\vec{R}} \hat{S}_{\vec{R} + 2\vec{a}} \rangle;$$

$$K_2 = \langle \hat{S}_{\vec{R}} \hat{S}_{\vec{R} + 2\vec{a}_1 + 2\vec{a}_2} \rangle; \quad \langle \dots \rangle \equiv \langle G | \dots | G \rangle; \quad \gamma_{\vec{k}} \equiv 0.5(\cos 2k_x a + \cos 2k_y a)$$

For $\alpha = 0, 0.2$ the correlations are $K_1 = -0.324, -0.297$; $K_2 = 0.221, 0.169$ respectively. The spectrum (3) reaches its minimum at line $\gamma_{\vec{k}} = \text{const} \approx 0$, which leads to a pronounced peak in the density of states (DOS) near the band bottom.

The results of $e(\vec{k})$ calculations with the general ansatz (2) are shown in fig. 1 a,b. To allow for direct hopping $h \neq 0$ term we add the functions $c_{\vec{R} + \vec{a}, +1}^+ |G\rangle$ to the basis set (see fig.2).

As we see from Fig. 1, 2 the $e(\vec{k})$ minimum position and Fermi surface topology strongly depend on α and h values. The DOS has a sharp peak near the band bottom. The inclusion of frustration enhances the spectrum anisotropy and DOS peak intensity. Let us note that the frustration shifts the spectrum $e(\vec{k})$ downward the energy axes. If we take into account that the increase of α is roughly proportional to the doping n , then the Fermi energy shift with doping is much less in magnitude than the shift predicted by rigid band model. Moreover the shift can have an opposite sign.

We see also that the general shape of the Fermi surface qualitatively coincides with

the numerical results on $t - J$ model: the increase of doping changes its hole character to the electronic one.




Fig.1 Equienergetic lines $e(\vec{k}) = \text{const}$, $O - O$ hopping via Cu $\tau = 1$, direct hopping $h = 0$. a) Without frustration, $\alpha = 0$. b) For $\alpha = 0.2$. Density of states is plotted in the inserts.




Fig.2 Equienergetic lines $e(\vec{k}) = \text{const}$ ($\tau = 1$) for direct $O - O$ hopping $h = 0.3$. a) Without frustration, $\alpha = 0$. b) For $\alpha = 0.2$.

References

- [1] V.J.Emery and G.Reiter, Phys. Rev. B38, 4547 (1988)
- [2] A.F.Barabanov et al., Superconductivity: Phys. Chem. Tech. 3, 8 (1990); Sov. Phys. JETP 69(2), 371 (1989)
- [3] A.F.Barabanov et al. Int. J. Mod. Phys. B4, 2319 (1990)
- [4] V.Stephan and P.Horsch, Phys. Rev. Lett. 66, 2258 (1991)