Zeitschrift: Helvetica Physica Acta

Band: 65 (1992)

Heft: 2-3

Artikel: Kinetic roughening in molecular-beam epitaxy

Autor: Nattermann, T. / Tang, L.-H.

DOI: https://doi.org/10.5169/seals-116483

Nutzungsbedingungen

Die ETH-Bibliothek ist die Anbieterin der digitalisierten Zeitschriften auf E-Periodica. Sie besitzt keine Urheberrechte an den Zeitschriften und ist nicht verantwortlich für deren Inhalte. Die Rechte liegen in der Regel bei den Herausgebern beziehungsweise den externen Rechteinhabern. Das Veröffentlichen von Bildern in Print- und Online-Publikationen sowie auf Social Media-Kanälen oder Webseiten ist nur mit vorheriger Genehmigung der Rechteinhaber erlaubt. Mehr erfahren

Conditions d'utilisation

L'ETH Library est le fournisseur des revues numérisées. Elle ne détient aucun droit d'auteur sur les revues et n'est pas responsable de leur contenu. En règle générale, les droits sont détenus par les éditeurs ou les détenteurs de droits externes. La reproduction d'images dans des publications imprimées ou en ligne ainsi que sur des canaux de médias sociaux ou des sites web n'est autorisée qu'avec l'accord préalable des détenteurs des droits. En savoir plus

Terms of use

The ETH Library is the provider of the digitised journals. It does not own any copyrights to the journals and is not responsible for their content. The rights usually lie with the publishers or the external rights holders. Publishing images in print and online publications, as well as on social media channels or websites, is only permitted with the prior consent of the rights holders. Find out more

Download PDF: 01.12.2025

ETH-Bibliothek Zürich, E-Periodica, https://www.e-periodica.ch

Kinetic Roughening in Molecular-Beam Epitaxy

T. Nattermann and L.-H. Tang Fakultät für Physik und Astronomie Ruhr-Universität-Bochum D-4630 Bochum, Germany

Abstract. Under certain conditions, kinetic roughening in vacuum deposition experiments is believed to be in a dynamic universality class different from that of the Kardar-Parisi-Zhang family due to a conservation law. We discuss results of dynamic renormalization group calculations for the dynamic scaling in the hydrodynamic regime and for the crossover from the equilibrium sine-Gordon model below the thermal roughening temperature.

The roughening of a vacuum deposited film is not only a topic of great technological importance but also of intense theoretical interest[1]. Even in the case of homoepitaxy where no mismatch between the lattice constants of the substrate and the film is present, a theoretical understanding of the growth kinetics is only begin to emerge[2,3]. For stable two-dimensional growth the driving force for surface roughness is the fluctuation in the incoming flux of particles at any given part of the surface. It is evident that, while the surface is moving at a finite velocity, its ability to relax into thermal equilibrium configurations can be kinetically constrained. Computer simulations of simple lattice models have shown that instead a nonequilibrium steady-state can be reached which exhibits interesting scaling properties both in space and time. In particular, starting from a flat surface at t=0, the width of a surface of linear size L satisfies the scaling form $w(t,L)=L^{\zeta}\Phi(t/L^z)$, where ζ and z are known as roughness and dynamic exponents, respectively.

Given the fact that dynamical scaling exists, one would like to identify universality classes and to understand what are the crucial ingredients which specify a particular class. It has been realized that one of the important elements in this respect is volumn conservation. Specifically, if we denote $Z(\mathbf{x},t)$ as the thickness of the film above a substrate site \mathbf{x} at time t in a suitable coarse-grained sense, and F the external beam intensity, volumn conservation means

$$\partial Z/\partial t = -\Omega \nabla \cdot \mathbf{j} + F \tag{1}$$

where \mathbf{j} is a particle number current density in the surface and Ω the atomic volumn of the diffusing species. Equation (1) is inconsistent with the Kardar-Parisi-Zhang equation[2] which is the generic description of kinetic roughening in the absence of the conservation law. It has been argued that, when molecular-beam epitaxy (MBE) is carried out at not too low and not too high temperatures, (e.g., between room temperature and $500^{\circ}C$,) (1) is a relevant constraint on the relaxation dynamics[3].

Under Eq. (1), a complete description of the relaxational process involves identifying the driving force for the surface diffusion current \mathbf{j} . This problem has been considered in the classical capillary wave theory by Herring and by Mullins[4]. There \mathbf{j} is assumed to be proportional to the surface gradient of the chemical potential which is in turn expressed in terms of the local curvature of the surface. Under the "shot noise", the resulting fourth order equation yields $\zeta = (4-d)/2$ and z=4. Here d is the dimension of the surface. In general, however, there is no need for the surface to

follow the dynamics derived from equilibrium thermodynamics when particles are added constantly to the surface. In fact, one can add new terms to the linear equation which maintain the conserving form of (1) but produce more efficient relaxation of surface fluctuations. One such equation was proposed by Villain[3] for MBE,

$$\partial Z/\partial t = -\gamma \nabla^4 Z + \frac{\sigma}{2} \nabla^2 (\nabla Z)^2 + F_0 + \eta, \qquad (2)$$

where we have split F into a constant part F_0 and a gaussian noise η . We[5], and independently Lai and Das Sarma[6], have performed one-loop dynamic renormalization group analysis of (2), and obtained exponents $\zeta = (4-d)/3$ and z = (8+d)/3 as conjectured by Villain[3].

In the dimension of physical interest, d=2, the above nonlinear theory predicts $\zeta=2/3$ while experimentally it is possible to achieve layer-by-layer growth at sufficiently high substrate temperatures, in which case the surface roughness is essentially absent. This raises the question concerning the applicability of hydrodynamic theories such as (2) on length and time scales of experimental interest. In the regime where the layer structure of the film can be identified, it appears sensible to consider the lattice discreteness effect on the surface dynamics. We have therefore generalized the Villain equation (2) to include a periodic term,

$$\partial Z/\partial t = -\gamma \nabla^4 Z + \frac{\sigma}{2} \nabla^2 (\nabla Z)^2 + v \nabla^2 \sin(2\pi Z/a) + F_0 + \eta. \tag{3}$$

In addition, to take into account the stochastic nature of surface diffusion on the atomic scale, we have included in η a conserving component. From a scaling analysis we found that, while the nonconserving component arising from the beam fluctuation always dominates the conserving one on sufficiently large length scales and leads to the roughening of the surface at any temperature, the conserving component can be dominant on short length scales when surface diffusion is fast. In the latter case, flat areas (or terraces) of limited size can exist if the surface is below the equilibrium roughening temperature. The relevant length scale separating the two regimes as well as the crossover behavior can be discussed quantitatively in a renormalization group treatment of (3) [5].

We wish to acknowledge many useful discussions with J. Villain and D. E. Wolf. The research is supported in part by DFG through SFB 241.

References

- [1] For reviews of recent developments see, e.g., Kinetics of Ordering and Growth at Surfaces, edited by M. Lagally (Plenum, New York, 1990).
- [2] M. Kardar, G. Parisi, and Y.-C. Zhang, Phys. Rev. Lett. 56, 889 (1986).
- [3] J. Villain, J. Phys. I (France) 1, 19 (1991), and references therein.
- [4] W. W. Mullins, in Metal Surfaces: Structure, Energetics and Kinetics, edited by W. D. Robertson and N. A. Gjostein (Am. Soc. Metals, Metals Park, OH, 1963).
- [5] L.-H. Tang and T. Nattermann, Phys. Rev. Lett. 66, 2899 (1991).
- [6] Z.-W. Lai and S. Das Sarma, Phys. Rev. Lett. 66, 2348 (1991).