Zeitschrift: Schweizerische mineralogische und petrographische Mitteilungen =

Bulletin suisse de minéralogie et pétrographie

Band: 78 (1998)

Heft: 3

Artikel: Quadratite Aq(Cd,Pb)(As,Sb)S3 - a new sulfide mineral from

Lengenbach, Binntal (Switzerland)

Autor: Graeser, Stefan / Lustenhouwer, Wim / Berlepsch, Peter

DOI: https://doi.org/10.5169/seals-59303

Nutzungsbedingungen

Die ETH-Bibliothek ist die Anbieterin der digitalisierten Zeitschriften auf E-Periodica. Sie besitzt keine Urheberrechte an den Zeitschriften und ist nicht verantwortlich für deren Inhalte. Die Rechte liegen in der Regel bei den Herausgebern beziehungsweise den externen Rechteinhabern. Das Veröffentlichen von Bildern in Print- und Online-Publikationen sowie auf Social Media-Kanälen oder Webseiten ist nur mit vorheriger Genehmigung der Rechteinhaber erlaubt. Mehr erfahren

Conditions d'utilisation

L'ETH Library est le fournisseur des revues numérisées. Elle ne détient aucun droit d'auteur sur les revues et n'est pas responsable de leur contenu. En règle générale, les droits sont détenus par les éditeurs ou les détenteurs de droits externes. La reproduction d'images dans des publications imprimées ou en ligne ainsi que sur des canaux de médias sociaux ou des sites web n'est autorisée qu'avec l'accord préalable des détenteurs des droits. En savoir plus

Terms of use

The ETH Library is the provider of the digitised journals. It does not own any copyrights to the journals and is not responsible for their content. The rights usually lie with the publishers or the external rights holders. Publishing images in print and online publications, as well as on social media channels or websites, is only permitted with the prior consent of the rights holders. Find out more

Download PDF: 28.11.2025

ETH-Bibliothek Zürich, E-Periodica, https://www.e-periodica.ch

Quadratite Ag(Cd,Pb)(As,Sb)S₃ – a new sulfide mineral from Lengenbach, Binntal (Switzerland)

by Stefan Graeser^{1,2}, Wim Lustenhouwer³ and Peter Berlepsch²

Abstract

With the mineral quadratite another new sulfide phase has been identified in the famous Lengenbach locality (Binntal, Switzerland). Like the numerous other, mainly As-sulfide minerals at this locality, quadratite occurs in small vugs in a white dolomitic rock of presumably Triassic age. Different from the new minerals discovered within the last few years, which all belong to the very special group of thallium sulfosalts and therefore always occur in close association with As-rich phases, quadratite exclusively occurs together with minerals poor in arsenic. Therefore it is closely associated with minerals like jordanite and galena, whereas realgar is clearly absent. In general, quadratite forms crystals of characteristic quadratic, sometimes octogonal shape; always tabular along the basis (001). The size is normally about 0.1 mm across, crystals with a diameter of more than 1 mm are extremely rare. With few exceptions the mineral is untwinned, one or two samples show an oriented intergrowth which may be interpreted as contact twins along (016). Small crystals are brown-red translucent, larger specimens are opaque with grey metallic luster, streak is reddish-brown. Single-crystal X-ray diffraction yielded a tetragonal cell with a = 5.499 (5) and c = 33.91 (4) Å, V =1025 (2) Å³, space group I4/amd, Z = 8. The strongest lines in the powder diagram are (d_{obs} in Å, I_{obs}, hkl): 2.77 (100) (200), 1.960 (80) (2.0.12), 1.679 (70) (2.0.16), 1.598 (70) (2.2.12;3.0.11), 1.274 (60) (4.0.10), 3.19 (50) (116). Chemical composition (electron microprobe, mean of 6 analyses, wt%) is: Ag 26.30, Cu 0.05, Tl 0.49, Cd 21.42, Pb 10.17, As 18.06, Sb 0.27, S 23.61, total 100.37 wt %. The simplified formula is close to AgCdAsS₃. The calculated density D_{calc} = 5.31 g/cm³. From the microhardness VHN (load 10 g) of 57–72 kg/mm² a Mohs hardness of ≤ 3 may be derived. Quadratite has a perfect cleavage along {001} and distinct along {110}.

The name is derived from the conspicous quadratic shape of the mineral, unique among Lengenbach sulfosalts, so far.

Keywords: quadratite, new Ag-Cd-As-sulfide mineral, single-crystal data, microprobe analyses, Lengenbach, Switzerland.

1. Introduction

The Lengenbach quarry in Binntal (Ct. Valais, Switzerland) is well known for its very uncommon sulfosalt minerals, mainly Pb–Cu–Ag–Tl–(As,Sb)-sulfides occurring in small cavities in the white dolomitic rock. With exception of some periods during the two world wars, the sulfosalt mineralisation has been mined for minerals almost professionally since more than 150 years. It was purely the scientific interest to study these minerals that was responsable for their exploitation. Starting with 1958, a Swiss syndicate consisting of

several scientific institutions (Museums, Mineralogical Institutes but also private people) has been active in Lengenbach and organized the mineral extraction until 1998. From 1958 to 1986, the works were carried out in the old classical quarry, which was abandoned in 1987 due to lack of attractive material. Since the new site was opened in 1987, a remarkable number of new mineral species has been discovered, which mainly belong to the special family of thallium sulfosalts (see e.g. Graeser and Edenharter, 1997).

In contrast to the mostly longprismatic Tl-Assulfosalts, quadratite, with Cd, Ag, As, besides sul-

¹ Naturhistorisches Museum Basel, Augustinergasse 2, CH-4001 Basel, Switzerland. <graesers@ubaclu.unibas.ch>

² Mineralogisch-petrographisches Institut, Universität Basel, CH-4056 Basel, Switzerland.

³ Institut voor Aardwetenschappen, Vrije Universiteit Amsterdam, NL-1081 HV Amsterdam, Netherlands.




Fig. 1 Quadratite crystal (0.45 mm Ø), grown on jordanite. Sample M. Siegel, photograph by W. Gabriel.


fur as main constituents, represents a completely new type of sulfide minerals in Lengenbach, a fact which is documented by the special morphology of the mineral, too. First specimens of the mineral were discovered by the mineral collectors Monika and Walter Gabriel (Basel) on the dump of the quarry in 1989. These crystals reached about 0.1 mm in diameter, a size that was suitable to establish a new species but did not allow to derive all the data necessary for the submission of a proposal to the Commission on New Minerals and Mineral Names, I.M.A. Additional material was

found in 1993, with crystals of more than 1 mm (e.g. Markus Ecker, Spiesen, Germany). These crystals enabled derivation of a complete set of data for the new mineral. Subsequently, the proposal for the new mineral was submitted to the I.M.A. commission, which accepted name and description of the new species (I.M.A. No. 94-038). Type material is preserved at the Natural History Museum Basel, and at the Mineralogical Institute, University of Basel.

2. Description

2.1. PHYSICAL AND OPTICAL PROPERTIES

It was the very uncommon morphology – thin tabular crystals of unmistakable quadratic shape, unlike any other Lengenbach mineral – that drew the attention to the unknown mineral. The thin platy crystals occur always as octogonal tablets, the smaller edge clearly corresponding to (hhl)faces (Fig. 1). One of the small crystals could be measured on an optical goniometer from which the following faces were calculated: a large pinacoid (001), two bipyramids of second order (103) and (104), which are always dominant over the two additional small bipyramids of first order (111) and (116). One unique sample (found by the German collector Ralph Cannon) displayed a very conspicous twinning law. Though the twinned crystals could not be measured goniometrically, an interpretation as penetration twins along (016) is obvious. Viewed with the naked eye, the two crystals cross at (nearly) 90°, therefore the angle ρ for the twinning-plane must be about 45°, and






Fig. 2 Shape crystal drawings (Dowty, 1997) based on optical goniometry. Left: single crystal; right: penetration twin along (016).

Tab. 1 Physical and optical properties of quadratite from Lengenbach.

Habit:	extremely thin quadratic (octogonal) laminae, often translu	cent		
Forms:	pinacoid {001}, always strongly dominant				
	first order bipyramids {103} and {104}, mostly small				
	second order bipyramids [111] and [116], dominant				
Twinning:	penetration along (016), see figure 2				
Colour:	in thin laminae reddish translucent, otherwise grey-metallic, opaque				
Streak:	reddish-brown				
Cleavage:	{001} perfect (micaceous); {110} distinct				
Tenacity:	thin laminae are ductile to flexible				
Hardness:	Mohs: ≤ 3 — according to microindentation VHN _{10g} = 63 (52–72)				
Density:	5.31 g/cm³ (calculated)				
Ore microscopic data (MPV-STAT by WILD-LEITZ)					
Colour: Internal reflexions: Pleochroism: Bireflectance:	greyish-white with bluish tint dark red reflexions along cleavage cracks (oil immersion) not observed (polished section ≈ parallel to {001}) not observed (polished section ≈ parallel to {001})				
Reflectance values:	WTiC standard				
	Wavelength	Air	Oil		
	470 nm	30.5–32.3	12.5–14.0		
	543 nm	29.6–30.8	12.2–13.3		
	587 nm	28.7–29.7	12.0–12.9		
	657 nm	26.3–28.0	11.3-12.3		

since the angle $(001^{\circ}016) = 45.6^{\circ}$, the twinningplane undoubtedly is (016), see figure 2. The extremely thin laminae appear clearly translucent and under a transmission polarizing microscope produce an indistinct nearly uniaxial figure whose character is not interpretable. With increasing thickness the crystals turn to an opaque, metallic character. In polished section under the metal microscope, quadratite appears greyish-white, with a slight bluish tint. Due to the perfect, micaceous cleavage along the basis (001), polished sections could only be prepared parallel to this face. Therethey provided few information anisotropy, bireflectance, and pleochroism. A full set of physical and optical properties is compiled in table 1.

2.2. X-RAY DIFFRACTION STUDY

The special ductile nature of the mineral provided some problems for the X-ray study. Therefore, powder data were derived mainly from diffraction patterns carried out by the Gandolfi technique (on single crystals). The patterns established with this device turned ot to be of superior quality compared to those obtained by common Debye-Scherrer-technique. The single-crystal investigation (Weissenberg and Precession methods) too, was impeded by the mineral's special properties, and was fully successful only with the better ma-

terial found in 1993. The results of this study suggest some relationship to the mineral cernyite, though the mineral formula and space group symmetry are quite different compared to quadratite. We hope that in future we will be able to separate adequate material for a complete structure determination which could solve this problem. The results of the X-ray diffraction study are given in table 2.

2.3. CHEMICAL COMPOSITION

First qualitative chemical data were obtained from EDS analyses on a SEM device (Cambridge Stereoscan Mark 2A, University of Basel), carried out with extremely fine laminae of about 0.1 mm in diameter. These analyses clearly pointed out that the mineral consisted of mainly Ag, Cd, As, and sulfur, a composition that was not known from a natural mineral, so far. Quantitative determinations, however, became feasible only with larger amounts of material discovered some years later. Chemical data are reported in table 3.

With the composition Ag(Cd,Pb,Tl)(As,Sb)S₃ for quadratite, the mineral obviously represents the first example of a Ag-Cd-As-sulfide in mineral systematics, altogether. Without a complete structure determination to date it is not possible to decide whether it belongs to the sulfosalt group s.str. (with AsS₃ pyramids) or to complex sulfides

<i>Tab. 2</i> X-	ray diffraction	data of	quadratite	from	Lengenbach.
------------------	-----------------	---------	------------	------	-------------

$I_{ m visuell}$	d _{obs} (in Å) ¹	$ m d_{calc}$	hkl	$I_{ m visuell}$	d _{obs} (in Å)	$d_{ m calc}$	hkl
30	4.23	4.239	0 0 8			ſ 1.257	2 0 24
50	3.19	3.203	1 1 6	30	1,245	₹	
100	2.77	2.750	2 0 0			L 1.237	1 1 26
< 10	2.39	2.403	2 1 3			ſ 1.236	4 0 12
10	2.33	2.312	2 1 5	10	1.237	₹	
		∫ 2.136	2 0 10			L 1.230	4 2 0
10	2.145	₹				ſ 1.226	4 2 2
		L 2.119	0 0 16	20	1.224	₹	
10	2.090	2.091	1 0 15			1.224	1 0 27
10	2.040	2.055	1 1 14			ſ 1.211	3 3 10
80	1.960	1.970	2 0 12	10	1.210	₹	point.
		ر 1.895	2 2 4			1.202	4 2 6
10	1.878	₹				∫ 1.181	4 2 8
		1.875	1 0 17	10	1.177	₹	
		ſ 1.830	3 0 1			1.178	2 0 26
10	1.827	₹					
		L 1.817	2 0 14	20	1.156	1.156	4 2 10
		ſ 1.789	2 1 13	30	1.136		
30	1.783	₹		20	1.131		
		L 1.770	3 0 5	10	1.0982		
30	1.759	1.767	2 2 8	10	1.0738		
70	1.679	1.679	2 0 16	30	1.0676		
40	1.664	1.664	2 1 15	20	1.0459		
8		ſ 1.602	2 2 12	20	1.0370		
70	1.598	₹		20	1.0198		
		1.576	3 0 11	30	0.9894		
		ſ 1.54 4	3 1 10	40	0.9816		
20	1.536	{					!
		1.524	3 2 1				
		[1.433	1 1 22				
30	1.435	{ 1.433	2 2 16				
		1.424	1 0 23				
10	1.380	1.375	4 0 0				
		ſ 1.309	4 1 5				
30	1.299	{ 1.308	4 0 8				
t		1.292	3 3 2				
60	1.274	1.274	4 0 10				

¹ Gandolfi camera 114.6 mm \emptyset , FeK_{α} radiation, intensities visually estimated

Crystal system:

tetragonal

Space group:

I4/amd

Lattice parameters (cell constants refined from Gandolfi powder data):

a = 5.499(5) Å

 $V = 1025 (2) Å^3$

c = 33.91 (4) Å

7. = 8

c/a = 6.165 (from lattice parameters) = 6.19 (from optical goniometry)

(with AsS₄ tetrahedrons), though from the general aspect of the mineral an affiliation to the complex sulfides appears more probable. Another problem arises from the question if Cd may be substituted partly by Pb, as postulated by the mineral formula. There are few minerals known in nature containing Cd as a major element (NICKEL and NICHOLS, 1997), however, among about 10 well defined species, one of them seems to repre-

sent exactly the same uncommon substitution: for the sulfide mineral shadlunite (Fe,Cu) $_8$ (Pb,Cd)S $_8$ a similar substutition is postulated by the authors (EVSTIGNEEVA et al., 1973).

Analytical work was carried out by means of an electron probe on one relatively large quadratite crystal (about 1 mm²). The chemical data are reported in table 3. A BSE-image of quadratite (Fig. 3) proofs a remarkably homogeneous

Tab. 3 Chemical composition of quadratite.

	I	II	III
Ag	26.30	26.05 - 26.88	26.30
Cu	0.05	0.04 - 0.06	
Tl	0.49	0.46 - 0.57	
Cd	21.42	21.08 - 22.06	21.91
Pb	10.17	9.31 - 10.65	10.10
As	18.06	17.74 - 18.37	18.25
Sb	0.27	0.23 - 0.32	
S	23.61	23.29 - 24.11	23.44
Total	100.37	99.76 - 101.08	100.00
Structu	ıral formula	a (based on 24 sulfur a	atoms)
Ag	7.95		8.0
Cu	0.03	$\Sigma = 7.98$	
Cd	6.27		6.0
Pb	1.61		2.0
Tl	0.08	$\Sigma = 7.96$	
As	7.92		8.0
Sb	0.07	$\Sigma = 7.99$	-,-
S	24		24

- I mean of six analyses, leading to the empirical formula $(Ag_{7.95}Cu_{0.03})_{\Sigma=7.98}(Cd_{6.27}Pb_{1.61}Tl_{0.08})_{\Sigma=7.96}(As_{7.92}Sb_{0.07})_{\Sigma=7.99}S_{24}$
- II range of data
- III theoretical composition for the simplified formula $8 \times Ag(Cd_{0.8}Pb_{0.2})AsS_3$ (based on a zell content Z = 8)

Microprobe: JEOL JXA–8800M (20 kV, 5×10^{-8} A), JEOL on-line ZAF correction using Berger & Seltzer's J/Z plus Philibert's and Duncumb & Reed's absorption correction

Standards: Ag (pure), Cu (pure), TlSbS₂ (Tl, Sb), CdS (Cd, S), PbS (Pb), InAs (As)

chemical composition of the mineral, though it is very closely intergrown with other sulfide mineral phases (jordanite, pyrite).

3. Occurrence, associated minerals

The mineral quadratite occurs in cavities formed by hydrothermal activity in the white Lengenbach dolomite. Different from the various new Tl-sulfosalts discovered within the past few years (see Graeser and Edenharter, 1997, e.g.), which are strictly associated with minerals of extremely high contents in arsenic (minerals like realgar, orpiment, etc.), quadratite exclusively occurs together with phases poorest in arsenic, mainly in association with galena, jordanite (Pb₁₄(As,Sb)₆S₂₃), pyrite, and, occasionally, sphalerite, lengenbachite and few hatchite. In most cases, quadratite is



Fig. 3 BSE-image of quadratite (dark grey), jordanite (light grey), and pyrite (black idiomorphic inclusion). Diameter of sample about 0.3 mm.

closely intergrown with jordanite, and even contains inclusions of this mineral (see Fig. 3). Quadratite is undoubtedly the product of a late hydrothermal activity by which galena, sphalerite, and jordanite were leached and partly dissolved. Silver was leached from galena (Ag-contents between 1'000-5'000 ppm), cadmium from sphalerite (Cd-contents between 1'000-2'000 ppm), arsenic and thallium presumably from jordanite and pyrite (thallium). The concentrations of minor elements in galena and sphalerite are taken from GRAESER (1969, 1971). The characteristically corroded crystals of galena and sphalerite proof the leaching process by hydrothermal fluids.

Within the first years after its discovery, quadratite remained an extremely rare species in Lengenbach, presumably as a consequence of its very small dimensions. In 1997, however, more than 30 quadratite samples existed in the official exploitation list of the "Arbeitsgemeinschaft Lengenbach". Obviously the eyes of the collectors became used to the mineral and, in particular, from the knowledge of the mineral's special occurrence, potential quadratite-bearing samples were easily discernible.

Acknowledgements

Monika and Walter Gabriel, the first discoverers of the unknown mineral kindly put all their material at our disposal for investigation. Several other collectors (Markus Ecker, Ralph Cannon, e.a.) provided us with larger samples and thus enabled the accomplishment of the study that led to the proposal for the new mineral species. Mikosch Siegel put an excellent crystal at our disposal for photographic purpose, splendidly carried out by W. Gabriel. We are greatly obliged to R. Guggenheim, M. Düggelin, and D. Mathys (SEM laboratory, University of Basel), who contributed the first chemical data of the mineral. Martin Kunz (ETH Zürich) provided valuable recommendations for the improvement of the text.

References

- Dowty, E. (1997): SHAPE, a computer program for drawing crystals, version 5.5. Evstigneeva, T.L., Genkin, A.D., Troneva, N.V., Fi-
- EVSTIGNEEVA, T.L., GENKIN, A.D., TRONEVA, N.V., FILIMONOVA, A.A. and TSEPIN, A.I. (1973): Shadlunite, a new sulfide of copper, iron, lead, manganese, and cadmium from copper-nickel ores. Zapiski Vses. Mineral. Obshch. 102, 63–74.
- Graeser, S. (1969): Minor elements in sphalerite and galena from Binntal (relations to coloration problems, isotopic compositions, etc.). Contr. Mineral. Petrol. 24, 156–163.
- Graeser, S. (1971): Mineralogisch-geochemische Untersuchungen an Bleiglanz und Zinkblende. Schweiz. Mineral. Petrogr. Mitt. 51, 415–442.
- GRAESER, S. and EDENHARTER, A. (1997): Jentschite (TlPbAs₂SbS₆) a new sulphosalt mineral from Lengenbach, Binntal (Switzerland). Min. Mag., Vol. 61, 131–137.
- NICKEL, E. and NICHOLS, M. (1997): The mineral database. Aleph Enterprises and CSIRO.

Manuscript received May 28, 1998; revision accepted July 1, 1998.